

# eurocol

# 965

the strong connection



## EUROPLAN FLEX

Fibre-reinforced self-levelling compound, on the basis of alpha hemihydrate. Ideal under parquet and on deformable substrates. From 3 mm up to 15 mm.

### PRODUCT TYPING

|             |  |
|-------------|--|
| Base        | A water-mixed alpha hemihydrate powder, filler, containing very high amounts of synthetic binders. Synthetic fibres. |
| Color       | White.   |
| Consistency | Powder.  |

- Fibre-reinforced, universal, very low-stress setting, self-levelling, cement-bound filler.
- For very high loads.
- For levelling mineral substrates, ceramic tiles, natural stone coverings, terrazzo, screwed wood-based panels (V100 P4 - P7, OSB 2 - 4) and fixed planks, parquet and mastic asphalt and on approved Eurocol decoupling boards (e.g. 823 Eurofloor Reno).
- Can be used in layer thicknesses from 3 to 15 mm, on mastic asphalt up to 5 mm, on decoupling boards (e.g. 823 Eurofloor Reno) up to 10 mm.
- For subsequent floor covering work and the laying of parquet.
- Pumpable.
- Synthetic fibres increase the flexibility of the set compound, especially when used on deformable, firm substrates such as wood-based panels.
- The product can be used on underfloor heating and is suitable for use with chair castors according to DIN EN 12529.
- For indoor use.
- Very low emission laying material, certified according to EMICODE EC1.

### PROPERTIES

|                              |   |
|------------------------------|---|
| Bureau Wheelchair resistance | From 3 mm layer thickness.                            |
| Classification               | CE: DIN EN 13813: CA-C25-F6.                          |
| Consumption                  | Approx. 1.4 kg/m <sup>2</sup> per mm layer thickness. |
| Flammability                 | Non-flammable.  |
| Frost resistance             | yes.  |
| Passableness                 | 2 - 3 hours at (18 - 20) °C.*                         |
| Special quality              | Fibre-reinforced. Free of chromate.                   |

### APPLICATION

For producing even and absorbent surfaces for floor covering and parquet work.

### PROCESSING

|                 |                |
|-----------------|----------------|
| Layer thickness | Maximum 15 mm. |
|-----------------|----------------|

965 EUROPLAN FLEX

|                        |   |
|------------------------|---|
| <b>Storage</b>         | Store in dry conditions between + 5 °C and + 30 °C  |
| <b>Tools</b>           | Trowel in combination with a spiked roller, mixing-device.  |
| <b>Mixing ratio</b>    | Add 25 kg of 965 Europlan Fibre to 6 - 6.5 litres of water.   |
| <b>Processing time</b> | Use within 20 minutes after mixing.*  |
| <b>Waiting time</b>    | Approx 3 minutes.   |
| <b>Drying</b>          | Approx. 24 hrs. by 3 mm layer thickness, for each additional 3 mm - another day of drying time is required. Allow to dry for 36 hours under parquet.  |
| <b>Shelf Life</b>      | Approx 6 Months, in unopened packaging.   |
| <b>Cleaner</b>         | Water.  |
| <b>Remarks</b>         | <p>For layer thicknesses over 10 mm, on moisture-sensitive (e.g. calcium sulphate screeds) or unstable substrates, Eurocol reactive primers, e.g. 042 Euroblock Turbo or 021 Euroblock Reno LE should be used.</p> <p>For layer thicknesses over 10 mm, on screwed wood-based panels, Eurocol reactive primers, e.g. 042 Euroblock Turbo or 021 Euroblock Reno LE should be used.</p> <p>Technical information and safety data sheets of other laying materials and floorings/parquet must be observed!</p> <p>Apply flooring to the filled area within the next few days!<br/>Maintain a minimum layer thickness of 3 mm to achieve the reinforcing effect.</p> <p>In case of multi-layer application, the layer thickness of the second application must not exceed the layer thickness of the first application.</p> <p><b>After application of levelling compound.</b></p> <ul style="list-style-type: none"> <li>• Fresh surfaces should be protected against direct sun light, draughts, high temperature (above +30°C), rain and frost.</li> <li>• To obtain the recommended long term technical performance of product, after finishing levelling works installation of floor covering should be done within the shortest period of time, which depends on product's drying time within 3 to 7 days, otherwise the surface should be protected with a suitable coating or covering.</li> </ul> <p>The readiness for laying is dependent on the thickness of the layer and depends in particular on the climatic conditions on site.</p> <p>Wear protective glasses and gloves.<br/>If the adhesive or installation material comes into contact with your eyes, wash out immediately with plenty of water and consult an ophthalmologist.<br/>Protect your hands with waterproof, robust gloves.<br/>Wear long trousers.<br/>Avoid prolonged skin contact with the adhesive or installation material. Thoroughly clean affected skin parts with water immediately.<br/>The longer fresh adhesive or installation material remains on your skin, the greater the risk of serious skin damage.<br/>Keep children away from fresh adhesive or installation material.</p> <p>Not suitable for solid planks &lt;22 mm and vertical lamella &lt;16 mm thick.EMICODE, for more information visit <a href="http://www.emicode.com">www.emicode.com</a>. For levelling work in connection with subsequent parquet adhesives using Eurocol 1K or 2K parquet adhesives, only use Eurocol 048 Europrimer Plus or reactive Eurocol primers.</p> |

\* The stated values are laboratory values which, given the large variation in climatological conditions, subfloor compositions and layer thicknesses, are only guideline values.

**Substrate:**

- The substrate must be permanently dry, resistant to pressure and tension, free from cracks and dust, even and free from layers that reduce adhesion.
- Adhesion-reducing layers, old material residues must be removed by suitable mechanical measures in accordance with the specifications of DIN 18365/DIN 18356.
- Old fixed floors, such as ceramic tiles, terrazzo, stone floors, are to be professionally cleaned with Eurocol 891 Euroclean Basic and sanded matt after drying.
- A primer coat of Eurocol adapted to the substrate and the expected layer thickness of the leveling compound is to be pre-coated. Allow the applied primer to dry thoroughly.
- Cracks or joints (except structural expansion joints) must be closed with Eurocol Europlan 913 Silicate sealing compound.
- For moisture-sensitive substrates (e.g. calcium sulphate screeds, suitable wood flooring panels) and layers thicker than 5 mm, prime with moisture-resistant, sprinkled with quartz sand Eurocol Reactive Primer.
- Appropriately dimensioned Eurocol edge strips are to be used for rising building components.
- Level out coarse unevenness in advance with stable filling compound. After complete drying, the surface must be primed again.

**965 EUROPLAN FLEX**

- In the event of defects, objections must be reported in writing.

#### Instruction manual:

- Mix the powder in the specified quantity (see technical data) with clean, cold water using an electric mixer to form a smooth, lump-free mass.
- It is recommended to keep a maturing time of 2 - 3 minutes.
- When pumping, set the mixing device so that a correct quantity of cold and clean tap water is added. Determine the spread size! Rinse the machine and hoses also during breaks to prevent hardening within the machine system. Please consult your pump manufacturer.
- Avoid overwatering, as this leads to sedimentation and the formation of unstable surface layers. Drying is also delayed.
- Apply the ready-mix within the working time in one working step if possible until the desired layer thickness is achieved. By using a squeegee and a spiked de-aeration roller, a smooth, even surface is obtained which usually does not need to be sanded.
- During the setting of the levelling compound, draughts and intensive sunlight must be avoided. This can lead to a too fast withdrawal of moisture, which "burns" the filler layer, pulverizes the surface edge zone and shrinkage cracks can occur.
- When laying on underfloor heating, the heating must be kept in operation for 3 days before, during and up to 7 days after laying with a surface temperature of 18 - 22°C.
- In the case of multi-layer levelling, apply an intermediate coat of completely set first levelling compound before applying the second, alternatively use a levelling compound suitable for the required thickness of the layer to be applied, in order to level in one operation.

#### Working conditions:

Required surrounding temperature: min. 18°C.

Material and subfloor temperature: min. 15°C.

Relative humidity: 35 - 75%, recommended <65%.

## QUALITY AND GUARANTEE



## ENVIRONMENT AND HEALTH

|                        |  |
|------------------------|--|
| GISCODE                | CP1  |
| LEED                   | VOC 0 g/l, meets: IEQ Credit 4.1   |
| DGNB                   | VOC 0 %, quality level: 4  |
| Hazard Class           | None.  |
| Safety and environment | Safety data sheets of Forbo Eurocol products according to EEG-guideline 91/155. Wear protective gloves and safety glasses! Keep out of reach of children. Do not eat, drink or smoke while processing the product. Only give completely empty containers for recycling. Material residues can be disposed of as household waste. |
| MSDS                   | For extensive information about safety and environment we refer to our website <a href="http://www.eurocol.nl">www.eurocol.nl</a> .  |

## ITEM DATA

| Article | Productname    | Packaging         | Shipping unit |
|---------|----------------|-------------------|---------------|
| 965     | Europlan Fibre | paper bag à 25 kg | 42/pallet     |

Any application method/ conditions other than specified in this Technical data sheet require explicit manufacturer's approval. In case of deviance in application method/ conditions liability by manufacturer cannot be guaranteed. This technical data sheet contains advice on handling and application of the product, based on experience and tests run by the manufacturer in laboratory and practical work. The information supplied by the manufacturer are non-binding and cannot be used as a basis for establishing the manufacturers liability for any damages caused. The values stated in this technical data sheet were measured under standard laboratory conditions. As application conditions outside the laboratory vary strongly this technical data sheet must be considered a guide only. Therefore the manufacturer does not take liability for damages caused by the customer's utilization of the technical data sheet content. As use, processing- and storage conditions on site are beyond manufacturers influence, a warranty for the processing result cannot be given. This also includes the infringement of any rights for the protection of third parties. Sufficient testing areas are to be provided before final application. Relevant national norms and regulations of the industry are to be observed. Outside Germany valid, relevant national norms and regulations, have to be taken into account and to be followed by the customer. It is the responsibility of the customer to check product suitability for the intended procedure and purposes prior to use.

This Technical Information supersedes all previously issued application data sheets and product information are no longer valid!

### 965 EUROPLAN FLEX

**965 EUROPLAN FLEX**

Forbo Eurocol Nederland B.V. | Industrieweg 1-2 | Postbus 130 | 1520 AC Wormerveer | Tel: +31 (0)75 627 16 00 | [info.eurocol@forbo.com](mailto:info.eurocol@forbo.com)  
Forbo Eurocol Deutschland GmbH | August-Röbling-Straße 2 | DE - 99091 Erfurt | PF 80 02 53 | Telefon: +49 361 730 41 0 | [info.eurocol.de@forbo.com](mailto:info.eurocol.de@forbo.com)

Eurocol is part of the Forbo Group

