

Confidential Report

Our Ref: 25/09371H/01/19



Notified Body for PPE Directive, Construction Products Regulation & Marine Equipment Directive I.D. No. 0338 & 0339



Telephone: +44 (0) 113 259 1999

Email: info@bttg.co.uk Website: www.bttg.co.uk

Date: 4 February 2019

Our Ref: 25/09371H/01/19

Your Ref:

_

Page: 1 of 8

Client: Forbo Flooring UK Limited

Unit 92 Seedlee Road Walton Summit Preston PR5 8AE

Job Title: Fire Test on One Sample of Carpet Tiles

Client's Order No: 4501024662

Date of Receipt: 10 January 2019

Description of Sample(s): One sample of carpet tiles, referenced; Chroma

Work Requested: We were asked to make the following test(s):

BS EN 13501-1

Note: This report relates only to the samples submitted and as described in the report.

- * subcontracted test, UKAS accredited
- ** subcontracted test, EN ISO/IEC 17025 accredited
- *** not UKAS accredited







Wira House, West Park Ring Road, Leeds, LS16 6QL, UK. Telephone: +44 (0) 113 259 1999

Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 4 February 2019

Our Ref: 25/09371H/01/19

Your Ref:

Page: 2 of 8

Client: Forbo Flooring UK Ltd

FIRE TESTS ACCORDING TO BS EN ISO 11925-2:2010 Reaction to fire tests for building products – Part 2: Ignitability when subjected to direct impingement of flame

Date of Test: 01/02/2019

Conditioning

Test specimens and filter paper conditioned as described in BS EN 13238:2010.

Procedure

The sample was tested in accordance with BS EN ISO 11925-2:2010.

Three specimens from each direction were tested in accordance with the above standard. Specified filter paper was placed beneath the specimen holder and replaced between tests.

The specimens were mounted vertically in the specimen holder so that one end and both sides were enclosed with the exposed end 30mm from the end of the frame. The burner was inclined at an angle of 45°. The flame height was set at 20 mm with the flame impinging on the specimen for 15 seconds on the centre line, 40 mm above the bottom edge.

A marker was placed 150 mm above the upper end of the burner and the time recorded when the flame tip reached the marker, if applicable. The following parameters were also recorded:-

- 1. If ignition occurs
- 2. Presence of flaming debris, if applicable
- 3. Ignition of the filter paper, if applicable

Duration of test

For a flame application time of 15 seconds, the total test duration is 20 seconds after application of the flame.





Telephone: +44 (0) 113 259 1999 Email: <u>info@bttg.co.uk</u>

Website: www.bttg.co.uk

Date: 4 February 2019

Our Ref: 25/09371H/01/19

Your Ref:

Page: 3 of 8

Client: Forbo Flooring UK Ltd

Classification Criteria

The samples were classified according to BS EN 13501-1:2007+A1:2009 Fire classification of Construction Products and Building Elements: Part 1 – Classification using Test Data from Reaction to Fire Tests, Table 1 – Classes of reaction to fire performance for construction products excluding floorings.

Flaming Classification			
Classification	Criteria (mean values)		
E _{FL}	Fs ≤ 150mm within 20 seconds		
F _{FL}	None (No performance determined)		

Flaming droplets / particles classification			
Classification	Criteria		
No classification	Pass		
d2	Fail (Ignition of paper)		

Results

Specimen		Ignition (Yes or No)	Tip of flame reaches 150mm		Flaming droplets		
			Yes or No	Time taken (s)	Yes or No	Ignition of Filter paper (Yes or No)	
Machine Direction	1	Yes	No	N/A	No	No	
	2	Yes	No	N/A	No	No	
	3	Yes	No	N/A	No	No	
Across Machine Direction	1	Yes	No	N/A	No	No	
	2	Yes	No	N/A	No	No	
	3	Yes	No	N/A	No	No	





Telephone: +44 (0) 113 259 1999 Email: <u>info@bttg.co.uk</u>

Website: www.bttg.co.uk

Date: 4 February 2019

Our Ref: 25/09371H/01/19

Your Ref:

Page: 4 of 8

Client: Forbo Flooring UK Ltd

FIRE TESTS ACCORDING TO BS EN ISO 9239-1:2010

Reaction to fire tests for Floorings - Part 1: Determination of the burning behaviour using a radiant heat source (ISO 9239-1:2010)

Date of Test: 01/02/2019

Conditioning

The specimens were conditioned in accordance with BS EN 13238:2010. The substrate used was a fibre cement board (ISO 390) with a thickness of (6±1)mm and a density of (1,800±200) Kg/m³ representing the standard substrate of Class A1fl or A2fl.

Procedure

The test was carried out in accordance with BS EN ISO 9239-1. The sponsor sampled and cut the specimens to the dimensions stated.

Specimens were individually placed in the combustion chamber and allowed to preheat for two minutes under a radiant panel, which gives an imposed radiant flux ranging from approximately 11.0 kW/m^2 to 1.0 kW/m^2 along the specimen.

The pilot flame used was the line burner as described and was applied to the surface of the specimen for 10 minutes and then removed.

The flame front was measured at the end of the test or at 30 minutes if applicable.

Test termination was considered to be when the flame front self extinguished or at 30 minutes, which ever is the sooner.

The heat flux from the panel incident on the specimen when self extinguished or at 30 minutes (critical heat flux CHF or HF-30) was calculated from a prior calibration.





Telephone: +44 (0) 113 259 1999 Email: <u>info@bttg.co.uk</u>

Website: www.bttg.co.uk

Date: 4 February 2019

Our Ref: 25/09371H/01/19

Your Ref:

Page: 5 of 8

Client: Forbo Flooring UK Ltd

Classification Criteria

The samples were classified according to BS EN 13501-1:2007+A1:2009: Fire classification of Construction Products and Building Elements: Part 1: Classification using Test Data from Reaction to Fire Tests.

For floorings, including their surface coverings the classes are:

Classification	Classification Criteria (mean values) (kW/m2)		
Bfl	8.0		
Cfl	4.5		
Dfl	3.0		
	Smoke Production % x min		
s1	≤ 750		
s2	Not s1		

When tested to BS EN ISO 11925-2:2010 the sample has to have a flame spread (Fs) of: Fs \leq 150mm within 20 seconds (Class Efl).

Results

The test results relate to the behaviour of the test specimens of a material under the particular conditions of test; they are not intended to be the sole criterion for assessing the full potential fire hazard of the materials in use.





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK. Telephone: +44 (0) 113 259 1999

Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 4 February 2019

Our Ref: 25/09371H/01/19

Your Ref:

Page: 6 of 8

Client: Forbo Flooring UK Ltd

Results (Continued)

Specimen No.	Direction of specimen	Smoke C Max %	bscuration <u>% x min</u>	Maximum Flame front (mm)	Critical Heat Flux (kW/m²)	Duration of Flaming (sec)
1	Machine	15	42	250	8.0	900
2	Across	18	44	240	8.3	870
3	Machine	16	51	250	8.0	902
4	Machine	18	57	250	8.0	910
Mean of 3 specimens	Machine	16	50	250	8.0	904
Distance			Time for each	ch specimen to bu	ırn (<u>s)</u>	
Burnt (n	<u>nm)</u>	<u>1</u>	<u>2</u>	<u>3</u>		<u>4</u>
50		180	183	18	5	188
100		245	226	23	5	248
150		319	280	30	0	300
200		467	500	43	8	481
250		780		82	5	800

Observations

The tests were carried out in accordance with the standard in relation to carpet tiles which means that the first cross join was situated at 250mm from the zero point. It was commented on the test that the material shrunk back at this join and that because of the gap produced the flame did not progress beyond the join. This means that the results just fall into the \mathbf{B}_{fl} classification, however had the flame propagated across the join then the classification would have been lower.

Note

One specimen was initially tested in each direction and whichever direction gave the worst result a further two specimens were tested. Only the results of the 3 specimens in the same direction were used to calculate the mean results.

The specimens of floor covering were tested stuck down onto a 6mm fibre cement board , as defined in BS EN 13238:2001 using F41 Adhesive.







Wira House, West Park Ring Road, Leeds, LS16 6QL, UK. Telephone: +44 (0) 113 259 1999

Email: info@bttg.co.uk Website: www.bttg.co.uk

Date: 4 February 2019

Our Ref: 25/09371H/01/19

Your Ref:

Page: 7 of 8

Client: Forbo Flooring UK Ltd

Comments

In our opinion, based on the tests carried out on the sample supplied;

- a) the results of the BS EN ISO 11925-2:2010 test indicate the sample meets the requirements of a Class E_{FL}. It should be noted that this is only class that can be achieved when tested to this method alone.
- b) the results of the BS EN ISO 9239-1:2010 test indicate the sample would achieve a Class B_{FI} S1 when tested to this method alone.

Conclusion

In our opinion, the results indicate that the sample when classified to BS EN 13501-1:2007+A1:2009 meets an overall classification of: Class B_{fl} s1.

Uncertainty of measurement has not been taken into account when presenting the test result. The relevant uncertainty value is included as an annex which forms an integral part of the report.

Reported by:

B Marsden (Mrs), Senior Fire Technician

Countersigned by:

P Doherty, Manager

Enquiries concerning this report should be addressed to Customer Services..





Telephone: +44 (0) 113 259 1999

Email: <u>info@bttg.co.uk</u> Website: <u>www.bttg.co.uk</u>

Date: 4 February 2019

Our Ref: 25/09371H/01/19

Your Ref:

Page: 8 of 8

Client: Forbo Flooring UK Ltd

Uncertainty Budget - Annex

The uncertainty budget for BS EN 13501-1:2007+A1:2009 was determined as follows:-

Overall (BS EN ISO 9239-1)

The uncertainty varies, therefore:

At position between a Euroclass B to C ± 15%
At position between a Euroclass C to D ± 15.5%
At position between a Euroclass D to E ± 17.5%

