

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

TEST REPORT

Client :	Forbo Flooring Systems Pty Ltd 23 Ormsby Place				Test Number : 20-005952 Issue Date : 6/01/2021 Print Date : 6/01/2021 Order Number : DJB Oct 2020			
	Wetherill Pa	ark NSW 2164						
Sample [Description	Clients Ref : "Coral B End Use : Entrance flo Nominal Composition : Nominal Mass per Unit A Nominal Thickness :	9mm thick- 2mm Ev cm	715 Charcoal Gro	ey"			
AS ISO 9239.1-2003		Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using aRadiant Heat SourceDate of Sample Arrival18-11-2020						
		Date Tested 05-01-2021						
		CHF Value	1	2	3	Mean		
		Length	10.4	10.4	10.4	10.4	kW/m²	
		Width	10.5	-	-	-	kW/m²	
		Smoke Value	1	2	3	Mean		
		Length	102	111	94	102	%.min	
		Width	86	-	-	-	%.min	
		Melting				Yes		

224377

Australian Wool Testing Authority Ltd Copyright - All Rights Reserved C

48003

Accredited for compliance with ISO/IEC 17025 - Testing



Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

12

Page 1 of 2



MICHAEL A. JACKSON B.Sc.(Hons)

APPROVED SIGNATORY



Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

TEST REPORT

Client :	Forbo Flooring Systems Pty Ltd		
	23 Ormsby Place		
	Wetherill Park NSW 2164		

 Test Number
 :
 20-005952

 Issue Date
 :
 6/01/2021

 Print Date
 :
 6/01/2021

 Order Number
 :
 DJB Oct 2020

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Results in accordance with section 8.4 have not been included in the report. They are available upon request.

HF30 not reported as flame out time occurred before 30 minutes.

Each specimen was clamped to a substrate of 6mm thick fibre reinforced cement board prior to testing.

224377

48003

C Australian Wool Testing Authority Ltd Copyright - All Rights Reserved Accredited for compliance with ISO/IEC 17025 - Testing

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

12

APPROVED SIGNATORY



Page 2 of 2

