




|  |   |   |                             |  |   |
|--|---|---|-----------------------------|--|---|
| <b>Prüfbericht-Nr.:</b><br><i>Test Report No.:</i>   | <b>89214258.02br-2</b><br><b>Supersedes 89214258.02br</b>   | <b>Auftrags-Nr.:</b><br><i>Order No.:</i>   | 214720                      | Seite 1 von 6<br>Page 1 of 6                     |   |
| <b>Kunden-Referenz-Nr.:</b><br><i>Client Reference No.:</i>  | 4501011564  | <b>Auftragsdatum:</b><br><i>Order date:</i>   | 22.10.2018                  |  |   |
| <b>Auftraggeber:</b><br><i>Client:</i>   | Forbo Flooring B.V., PO Box 13, 1560 AA Krommenie, The Netherlands  |   |                             |  |   |
| <b>Prüfgegenstand:</b><br><i>Test item:</i>  | Resilient floor covering  |   |                             |  |   |
| <b>Bezeichnung / Typ-Nr.:</b><br><i>Identification / Type No.:</i>   | Marmoleum 2,5 mm  |   |                             |  |   |
| <b>Auftrags-Inhalt:</b><br><i>Order content:</i>   | Classification of burning behaviour   |   |                             |  |   |
| <b>Prüfgrundlage:</b><br><i>Test specification:</i>  | EN 13501-1:2007+ A1:2009<br>Classification of burning behaviour<br><i>Test methods: Ignitability of products subjected to direct impingement of flame (EN ISO 11925-2:2010/C1:2011) and determination of the burning behaviour using a radiant heat source (EN ISO 9239-1:2010)</i> |   |                             |  |   |
| <b>Wareneingangsdatum:</b><br><i>Date of receipt:</i>  | 31.10.2018  |  |                             |  |   |
| <b>Prüfmuster-Nr.:</b><br><i>Test sample No.:</i>  | MT18-214720.02  |   |                             |  |   |
| <b>Prüfzeitraum:</b><br><i>Testing period:</i>   | 31.10.2018 - 03.12.2018   |   |                             |  |   |
| <b>Ort der Prüfung:</b><br><i>Place of testing:</i>  | Externally accredited Test Laboratory   |   |                             |  |   |
| <b>Prüflaboratorium:</b><br><i>Testing laboratory:</i>   | Externally accredited Test Laboratory   |   |                             |  |   |
| <b>Prüfergebnis*:</b><br><i>Test result*:</i>  | Siehe Sonstiges / See Other   |   |                             |  |   |
| <b>geprüft von / tested by:</b>  | <b>kontrolliert von / reviewed by:</b>  |   |                             |  |   |
| 06.12.2018 M.A. van de Vlekkert   | 06.12.2018 R. Boerboom   |   |                             |  |   |
| <b>Datum</b><br><i>Date</i>  | <b>Name / Stellung</b><br><i>Name / Position</i>  | <b>Unterschrift</b><br><i>Signature</i>   | <b>Datum</b><br><i>Date</i> | <b>Name / Stellung</b><br><i>Name / Position</i> | <b>Unterschrift</b><br><i>Signature</i> |
| <b>Sonstiges / Other:</b> Test result: See clause 4 on page 5.   |   |   |                             |  |   |
| <b>Zustand des Prüfgegenstandes bei Anlieferung:</b><br><i>Condition of the test item at delivery:</i>   |   | Prüfmuster vollständig und unbeschädigt<br><i>Test item complete and undamaged</i>  |                             |  |   |
| * Legende: 1 = sehr gut 2 = gut 3 = befriedigend 4 = ausreichend 5 = mangelhaft<br>P(ass) = entspricht o.g. Prüfgrundlage(n) F(ail) = entspricht nicht o.g. Prüfgrundlage(n) N/A = nicht anwendbar N/T = nicht getestet<br>Legend: 1 = very good 2 = good 3 = satisfactory 4 = sufficient 5 = poor<br>P(ass) = passed a.m. test specification(s) F(ail) = failed a.m. test specification(s) N/A = not applicable N/T = not tested                          |   |   |                             |  |   |
| <b>Dieser Prüfbericht bezieht sich nur auf das o.g. Prüfmuster und darf ohne Genehmigung der Prüfstelle nicht auszugsweise vervielfältigt werden. Dieser Bericht berechtigt nicht zur Verwendung eines Prüfzeichens.</b><br><i>This test report only relates to the a. m. test sample. Without permission of the test center this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any test mark.</i> |   |   |                             |  |   |



Prüfbericht-Nr.: 89214258.02br-2 Supersedes  
89214258.02br

Seite 3 von 6  
Page 3 of 6

**Produktbeschreibung**  
**Product description**

|                  |                   |        |       |
|------------------|-------------------|--------|-------|
| Product identity | Marmoleum 2,5 mm* | Dessin | 3642* |
| Batch            | 36928*            |        |       |

\* applicants declaration

Figure 1, Picture of the received sample




Figure 2, Picture of the received sample (back)



Prüfbericht-Nr.: 89214258.02br-2 Supersedes  
89214258.02br

Seite 4 von 6  
Page 4 of 6

|        |  |                              |            |
|--------|--|------------------------------|------------|
| Absatz | <b>EN 13501-1:2007+ A1:2009</b>                  | Messergebnisse - Bemerkungen | Bewertung  |
| Clause | Anforderungen - Prüfungen / Requirements - Tests | Measuring results - Remarks  | Evaluation |

|   |   |  |  |
|---|---|--|--|
| 1 | <b>Construction data (indicative) of the product obtained by the testlaboratory after pre-conditioning</b><br>01-4.3-P.02-322-WI01  |  |  |
|   | Test condition  | 23 ± 2°C and 50 ± 4% relative humidity   |  |
|   | Pre conditioning, duration  | ≥ 48 h & until constant mass is achieved |  |
|   | Total thickness (mm)  | 20.4                                     |  |
|   | Total mass (g/m <sup>2</sup> )  | 14130                                    |  |
|   | Density (kg/m <sup>3</sup> )  | 696                                      |  |
|   | <i>Note: the determined construction data are used for determination of constant mass, the used testmethod is not in accordance with the determination of construction data according the specification standard. Therefore the testresults should be handled as indicative. The values are measured including the Particleboard.</i> |  |  |

|  |   |  |     |     |       |     |     |
|--|---|--|-----|-----|-------|-----|-----|
| 2  | <b>Ignitability of products subjected to direct impingement of flame</b><br>EN ISO 11925-2:2010/C1:2011 |  |     |     |       |     |     |
|  | Date of testing   | 06.11.2018   |     |     |       |     |     |
|  | Pre-conditioning, climate   | 23 ± 2°C and 50 ± 4% relative humidity   |     |     |       |     |     |
|  | Pre-conditioning, duration  | ≥ 48 h & until constant mass is achieved   |     |     |       |     |     |
|  | Description of substrate  | Particleboard, thickness 20 ± 2 mm, density 680 ± 50 kg/m <sup>3</sup> conforming to EN 13238:2010 |     |     |       |     |     |
|  | Flame application   | Surface  |     |     |       |     |     |
|  | Flame application time (s)  | 15   |     |     |       |     |     |
|  | Requirements according EN 13501-1:2007+A1:2009  | See clause 5   |     |     |       |     |     |
|  | <b>Test result(s)</b>   |  |     |     |       |     |     |
|  | Orientation   | Length   |     |     | Width |     |     |
|  | Test sample   | 1  | 2   | 3   | 1     | 2   | 3   |
|  | Ignition of the sample  | Yes  | Yes | Yes | Yes   | Yes | Yes |
|  | Flame tip reached 150 mm above the application point  | No   | No  | No  | No    | No  | No  |
|  | Duration after application when the flame tip reached the 150 mm above the application point (s)        | N/A  | N/A | N/A | N/A   | N/A | N/A |
|  | Extent of damaged area, length (mm)   | 40   | 42  | 46  | 46    | 41  | 42  |
|  | Extent of damaged area, width (mm)  | 10   | 11  | 12  | 11    | 11  | 10  |
|  | Material melts  | Yes  | Yes | Yes | Yes   | Yes | Yes |
| Shrinks away from flame without being ignited                    | No  | No   | No  | No  | No    | No  |     |
| After glowing  | No  | No   | No  | No  | No    | No  |     |
| Flaming droplets/particles which caused ignition of filter paper | No  | No   | No  | No  | No    | No  |     |

Prüfbericht-Nr.: 89214258.02br-2 Supersedes  
89214258.02br

Seite 5 von 6  
Page 5 of 6

|        |  |                              |            |
|--------|--|------------------------------|------------|
| Absatz | <b>EN 13501-1:2007+ A1:2009</b>                  | Messergebnisse - Bemerkungen | Bewertung  |
| Clause | Anforderungen - Prüfungen / Requirements - Tests | Measuring results - Remarks  | Evaluation |

|  |  |  |     |     |     |            |
|--|--|--|-----|-----|-----|------------|
| <b>3</b>   | <b>Determination of the burning behaviour using a radiant heat source</b><br><i>EN ISO 9239-1:2010</i> |  |     |     |     |            |
|  | Date of testing  | 03.12.2018   |     |     |     |            |
|  | Pre-conditioning, climate  | 23 ± 2°C and 50 ± 4% relative humidity   |     |     |     |            |
|  | Pre-conditioning, duration   | ≥ 48 h & until constant mass is achieved   |     |     |     |            |
|  | Description of substrate   | Particleboard, thickness 20 ± 2 mm, density 680 ± 50 kg/m <sup>3</sup> conforming to EN 13238:2010 |     |     |     |            |
|  | Fixing method  | The samples are glued to the substrate with Eurocol 614.   |     |     |     |            |
|  | Requirements according EN 13501-1:2007+ A1:2009  | See clause 5   |     |     |     |            |
|  | <b>Test result(s)</b>  |  |     |     |     |            |
|  | Test sample  | 1  | 2   | 3   | 4   | Mean       |
|  | Orientation (Length: ↑, Width: T)  | ↑  | T   | T   | T   | T          |
|  | Flame spread (cm)  | 36   | 37  | 39  | 40  | <b>39</b>  |
|  | CHF / HF-30 (kW/m <sup>2</sup> )   | 6.1  | 5.9 | 5.6 | 5.4 | <b>5.6</b> |
|  | Smoke production (%.min)   | 454  | 482 | 482 | 522 | <b>495</b> |
| Observations:<br>Specimen 1, 2, 3 and 4: Extinguished naturally before the end of the test duration. |  |  |     |     |     |            |

|   |   |                       |
|---|---|-----------------------|
| <b>4</b>  | <b>Classification of burning behaviour</b><br><i>EN 13501-1:2007+A1:2009</i>  |                       |
|   | The product, <b>Marmoleum 2,5 mm</b> , in relation to its reaction to fire behaviour is classified:   | <b>C<sub>fl</sub></b> |
|   | The additional classification in relation to smoke production is:   | <b>s1</b>             |
|   | <b>Reaction to fire classification : C<sub>fl</sub> – s1</b>  |                       |
|   | Field of application <ul style="list-style-type: none"> <li>- As a floor covering in accordance with the nominal product parameters given on page 3.</li> <li>- On end use substrates of wood and of classes A1 and A2-s1,d0 according to EN 13238:2010.</li> <li>- Glued down with Eurocol 614.</li> </ul> |                       |
| Statements <ul style="list-style-type: none"> <li>- This document does not represent type approval or certification of the product.</li> <li>- The test results only relate to the behaviour of the test specimens of the examined product under the -particular conditions of the test in laboratory conditions; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.</li> <li>- The validity of this report will expire directly after alterations or modifications of the examined product (combination)(s) and/or the criteria.</li> </ul> |   |                       |

Prüfbericht-Nr.: 89214258.02br-2 Supersedes  
89214258.02br

Seite 6 von 6  
Page 6 of 6

|        |  |                              |            |
|--------|--|------------------------------|------------|
| Absatz | EN 13501-1:2007+ A1:2009                         | Messergebnisse - Bemerkungen | Bewertung  |
| Clause | Anforderungen - Prüfungen / Requirements - Tests | Measuring results - Remarks  | Evaluation |

|  |   |  |  |                               |
|--|---|--|--|-------------------------------|
| 5  | <b>Potential classes of reaction to fire performance for floorings</b>  |  |  |                               |
|  | EN 13501-1:2007+A1:2009   |  |  |                               |
|  | Class   | Test method(s)                                   | Classification criteria  |                               |
|  | A1 <sub>fi</sub>  | EN ISO 1182 <sup>a</sup><br>and                  | $\Delta T \leq 30 \text{ °C}$ ; and<br>$\Delta m \leq 50 \%$ ; and<br>$t_f = 0$ (i.e. no sustained flaming)  | -                             |
|  |   | EN ISO 1716                                      | $PCS \leq 2.0 \text{ MJ/kg}^a$ and<br>$PCS \leq 2.0 \text{ MJ/m}^2^b$ and<br>$PCS \leq 1.4 \text{ MJ/m}^2^c$ and<br>$PCS \leq 2.0 \text{ MJ/kg}^d$ | -                             |
|  | A2 <sub>fi</sub>  | EN ISO 1182 <sup>a</sup><br>or                   | $\Delta T \leq 50 \text{ °C}$ and<br>$\Delta m \leq 50 \%$ and<br>$t_f \leq 20 \text{ s}$  | -                             |
|  |   | EN ISO 1716<br>and                               | $PCS \leq 3.0 \text{ MJ/kg}^a$ and<br>$PCS \leq 4.0 \text{ MJ/m}^2^b$ and<br>$PCS \leq 4.0 \text{ MJ/m}^2^c$ and<br>$PCS \leq 3.0 \text{ MJ/kg}^d$ | -                             |
|  |   | EN ISO 9239-1 <sup>e</sup>                       | $CHF \geq 8.0 \text{ kW/m}^2$  | Smoke production <sup>g</sup> |
|  | B <sub>fi</sub>   | EN ISO 9239-1 <sup>e</sup><br>and                | $CHF \geq 8.0 \text{ kW/m}^2$  | Smoke production <sup>g</sup> |
|  |   | EN ISO 11925-2 <sup>h</sup> :<br>Exposure = 15 s | $F_s \leq 150 \text{ mm}$ within 20 s  | -                             |
|  | C <sub>fi</sub>   | EN ISO 9239-1 <sup>e</sup><br>and                | $CHF \geq 4.5 \text{ kW/m}^2$  | Smoke production <sup>g</sup> |
|  |   | EN ISO 11925-2 <sup>h</sup> :<br>Exposure = 15 s | $F_s \leq 150 \text{ mm}$ within 20 s  | -                             |
|  | D <sub>fi</sub>   | EN ISO 9239-1 <sup>e</sup><br>and                | $CHF \geq 3.0 \text{ kW/m}^2$  | Smoke production <sup>g</sup> |
| EN ISO 11925-2 <sup>h</sup> :<br>Exposure = 15 s |   | $F_s \leq 150 \text{ mm}$ within 20 s            | -  |                               |
| E <sub>fi</sub>                                  | EN ISO 11925-2 <sup>h</sup> :<br>Exposure = 15 s  | $F_s \leq 150 \text{ mm}$ within 20 s            | -  |                               |
| F <sub>fi</sub>                                  | No performance determined   |  |  |                               |
| <sup>a</sup>                                     | For homogeneous products and substantial components of non-homogeneous products.  |  |  |                               |
| <sup>b</sup>                                     | For any external non-substantial component of non-homogeneous products.   |  |  |                               |
| <sup>c</sup>                                     | For any internal non-substantial component of non-homogeneous products.   |  |  |                               |
| <sup>d</sup>                                     | For the product as a whole.   |  |  |                               |
| <sup>e</sup>                                     | Test duration = 30 min.   |  |  |                               |
| <sup>f</sup>                                     | Critical flux is defined as the radiant flux at which the flame extinguishes or the radiant flux after a test period of 30 min, whichever is the lower (i.e. the flux corresponding with the furthest extent of spread of flame). |  |  |                               |
| <sup>g</sup>                                     | s1 = Smoke $\leq 750 \%$ minutes;<br>s2 = not s1.   |  |  |                               |
| <sup>h</sup>                                     | Under conditions of surface flame attack and, if appropriate to the end use application of the product, edge flame attack.  |  |  |                               |