

**Technical specifications**

Desktop meets the requirements of EN 688

Walton Crocodiles meets the requirements of EN 548

|  |                         | <b>desktop®</b> | <b>walton crocodiles</b>  |
|--|-------------------------|-----------------|---|
|  | Total Thickness         | EN 428          | 2.0 mm<br>2.5 mm  |
|  | Collection size         |                 | 20<br>24  |
|  | Roll width              | EN 426          | 1.83 m<br>2.00 m  |
|  | Roll length             | EN 426          | ≤ 30 m<br>≤ 32 m  |
|  | Total weight            | EN 430          | 2.1 kg/m <sup>2</sup><br>2.9 kg/m <sup>2</sup>  |
|  | Indentation-residual    | EN 433          | < 0.20 mm<br>0.08 mm*   |
|  | Light fastness          | ISO 105-B02     | Method 3: blue scale minimum 6.   |
|  | Gloss level             | ISO 2813        | < 5<br>8*   |
|  | Resistance to chemicals | EN 423          | Resistant to diluted acids, oils, fats and to the conventional solvents such as alcohol, white spirit, etc. Not resistant to prolonged exposure to alkalis. |
|  | Flexibility             | EN 435          | ø 50 mm   |
|  | Heat resistance         | EN 433          | 70 °C<br>-  |
|  | Life Cycle Assessment   |                 | LCA is the foundation for securing the lowest environmental impact  |

\* Typical value

**Desktop meets the requirements of EN 14041**

|  |              |         |                  |
|--|--------------|---------|------------------|
|  | Body voltage | EN 1815 | < 2 kV<br>< 2 kV |
|--|--------------|---------|------------------|

The above information is subject to modifications for the benefit of further improvements.