






















Technical specifications

Step meets the requirements of EN - ISO 10582 and EN 13845

		Surestep Original Surestep Star	Surestep Wood Surestep Stone Surestep Mineral Surestep Texture	
	Total thickness	EN - ISO 24346	2.0 mm	2.0 mm
	Thickness wear layer	EN - ISO 24340	0.7 mm	0.7 mm
	Collection size		24/13	12/8/5/5
	Commercial very heavy	EN - ISO 10874	Class 34	Class 34
	Industrial heavy	EN - ISO 10874	Class 43	Class 43
	Roll width	EN - ISO 24341	2.00 m	2.00 m
	Roll length	EN - ISO 24341	20 - 27 m	20 - 27 m
	Total weight	EN - ISO 23997	2.75 kg/m ²	2.75 kg/m ²
	Dimension stability	EN - ISO 23999	< 0.1%	< 0.1%
	Residual indentation	EN - ISO 24341-1	≤ 0.05 mm	≤ 0.05 mm
	Castor chair continuous use	EN 425	No effect	No effect
	Use in Wet areas	EN 13533	Yes	No
	Light fastness	EN ISO 105 B-02	≥6	≥6
	Flexibility	EN-ISO 24344	ø 10 mm	ø 10 mm
	Resistance to chemicals	EN-ISO 26987	Very good	Very good
	Slip resistance	EN 13845 Annex C	ESf	ESf
		EN 13845 Annex D 50.000 revolutions <10% loss	Pass	Pass
		DIN 51130	R10	R10
		DIN 51097	-	-
		TRRL Pendulum – Wet test – slider 96	≥ 36	≥ 36
		Surface roughness Rz	≥ 20	≥ 20
	Electrical resistance	EN 1081 (R1)	> 1.10 ⁹ Ω	> 1.10 ⁹ Ω

Step meets the requirements of EN 14041



	Reaction to fire	EN 13501-1	B _{fl} -s ₁	B _{fl} -s ₁
	Slip resistance	EN 13893	DS: ≥0.30	DS: ≥0.30
	Body voltage	EN 1815	< 2kV	< 2kV
	Thermal conductivity	EN 12524	0.25 W/m·K	0.25 W/m·K

Recommended adhesives

Our recommended adhesive for the Step collection is Eurosafe special 540.

For Surestep Wood Decibel technical specification, please see page 130.