













## Technical specifications

	Total thickness	ISO 1765	Approx. 9 mm						
	Area of use		Heavy use						
	Roll width		185 cm						
	Roll length		Roll length approx 27.5 m (customisable)						
	Colour fastness ratings:								
	Light	EN ISO 105/B02	> 5						
	Rubbing	EN ISO 105/X12	4						
	Water	EN ISO 105/E01	4-5						
	Seawater	EN ISO 105/E02	4						
	Shampoo	BS 1006	4-5						
	Organic solvents	EN ISO 105/X05	5						
	Construction		Tufted, 5/32" cut-pile						
	Designs		Mottled						
	Pile material		60% Wool / 40% polyamide						
	Tuft base		Non-woven polyester						
	Backing		FR latex						
	Total weight	ISO 8543	Approx. 2550 gram/m <sup>2</sup>						
	Pile installation weight	ISO 8543	Approx. 1120 gram/m <sup>2</sup>						
	Pile thickness	ISO 1766	Approx. 6 mm						
	Pile density	ISO 8543	0.141 gram/cm <sup>3</sup>						
	Number of tufts	ISO 1763	Approx. 96,400/m <sup>2</sup>						
	Impact noise reduction	EN ISO 717-2	Δ Lw 31dB						
	Sound absorption	EN ISO 354:2003	f(Hz):	125	250	500	1000	2000	4000
			αp:	0.05	0.05	0.1	0.3	0.55	0.6
	Slip resistance	EN 13893	DS						
	Body voltage	ISO 6356	< 2.0 kV antistatic						
	Thermal resistance	ISO 8302	0.125 m <sup>2</sup> K/W						
	Fire rating:								
	IMO Resolution A653(16)		Pass						
	IMO Resolution MSC 307(88) Annex 1 Parts 2 and 5		Pass						
	US Coast Guard approval ref: 164.117EC0493		EC0493/17						

IMO tested and approved adhesives can be recommended upon request.

Final production might vary within commercial tolerances from sample.

Manufacturing specifications subject to normal industry tolerances.

Forbo reserves the right to improve the specification of its products without giving prior notice.

Errors and omissions excepted.



0493/17 164.117/EC0493/Forbo\_2017\_0001