Technical specifications

Flotex naturals meets the requirements of EN 1307







			Flotex naturals
	Total thickness	ISO 1765	4.3 mm
ΪÅ	Commercial use	EN-ISO 10874	Class 33
	Collection size		20
	Roll width		2.0 m
Q ↔	Roll length		± 30 m
S	Total weight	ISO 8543	1800 g/m²
	Pile composition		100% polyamide 6.6
K N	Dimension stability	ISO 2551	≤ 0.2%
	Abrasion resistance	EN 1307 annex F	> 1000 cycles
	Water impermeability	EN 1307 annex G	Pass
	Castor chair continuous use	ISO 4918	r≥2.4
F	Colour fastness to light	EN-ISO 105-B02	≥5
98	Slip resistance	BS 7976-2 (UK SRG pendulum)	Dry : low slip risk Wet : low slip risk
9	Acoustic impact noise reduction	EN-ISO 717-2	ΔL _w ≥ 21 dB
(m)	Acoustic sound absorption	ISO 354	$\alpha_{w} = 0.10 \text{ (H)}$
	Creating better environments		
\vec{A}	Renewable electricity		Flotex is manufactured using 100% electricity made from renewable sources
O	Recycled content		Flotex sheet contains up to 20% recycled content by weight
rigi	Indoor air quality		Flotex is approved by Allergy UK. All Flotex products are tested for indoor air emissions in accordance with EN16516 after 3 days and 28 days. Flotex sheet has ultra low emissions.
	SKA		Flotex meets SKA Rating criteria for M12 for soft floor coverings in office, retail and higher education scheme
LCA	LCA		LCA is the foundation for securing the lowest environmental impact
			EN 14041
	Flotex naturals meets the requirements of EN 14041: 2004		C € 1200301-DoP-107
L CS	Reaction to fire	EN 13501-1	B _n -s1, L, CS
(SS)			



Slip resistance

Body voltage

Thermal conductivity

Content of specific dangerous substance

All Forbo Flooring Systems' sales organisations worldwide have a certified Quality Management System in accordance with ISO 9001.

All Forbo Flooring Systems' manufacturing operations have a certified Environmental Management System in accordance with ISO 14001.

The Life Cycle Assessment (LCA) of Forbo Flooring Systems' products is documented in individual Environmental Product Declarations (EPD's) which can be found on

 $\mu \geq 0.30$

≤ 2.0 kV

0.06 W/mk

Compliant

Our recommended adhesive for Flotex Sheet is 640 Eurostar Special. Please contact customer services for more information.

EN 13893

ISO 6356

EN 12524

EN 14041

