

Forbo Adhesive Fast Facts Chart

Forbo Adhesive	Adhesive Type	Packaging	Max Surface Moisture	Max MVE (per 1,000 ft ²)	Max RH	Max pH ¹	Approximate Spread Rate (ft ² / gallon)	Adhesive Color	Trowel Notch	Freeze/Thaw Stability	Shelf Life (Unopened)
L 885	Acrylic Polymer	1 Gallon 4 Gallon	n/a	8	85%	10	125	Light tan	1/16" x 1/16" x 1/16" square notch	1 Cycle at 20°F (-6° C)	2 Years
T 940	Acrylic Polymer	1 Gallon 4 Gallon	n/a	5	75%	10	125	White	1/16" x 1/16" x 1/16" square notch	1 Cycle at 20°F (-6° C)	2 Years
Sustain 885m	Dual Acrylic Polymer	1 Gallon 4 Gallon	n/a	8	85%	10	125	Grey	1/16" x 1/16" x 1/16" square notch	1 Cycle at 20°F (-6° C)	2 Years
Sustain 1195	Dual Acrylic Polymer	4 Gallon	n/a	10	95%	11	125	Green	1/16" x 1/16" x 1/16" square notch	1 Cycle at 20°F (-6° C)	2 Years
Sustain 1299²	Dual Acrylic Polymer	4 Gallon	< 5	n/a	99%	12	125	Yellow	1/16" x 1/16" x 1/16" square notch	1 Cycle at 20°F (-6° C)	2 Years
V 885	Acrylic Polymer	4 Gallon	n/a	8	85%	10	175	Light tan	1/32" x 1/16" x 1/32" fine notch	1 Cycle at 20°F (-6° C)	2 Years
FRS 885	Acrylic Polymer	4 Gallon	n/a	8	85%	10	125	Light tan	1/16" x 1/16" x 1/16" square notch	1 Cycle at 20°F (-6° C)	2 Years
FRT 950	Pressure Sensitive	4 Gallon	n/a	8	85%	10	300	White; Dries Clear	3/8" nap roller	1 Cycle at 20°F (-6° C)	2 Years
FST 1299²	High Quality Acrylic Emulsion	4 Gallon	< 5	n/a	99%	12	125	White; Dries Clear	1/16" x 1/16" x 1/16" square notch OR 3/8" nap roller	1 Cycle at 20°F (-6° C)	2 Years
C 930	Acrylic Polymer	4 Gallon	n/a	8	85%	10	125	White with grey conductive fibers	1/16" x 1/16" x 1/16" square notch	1 Cycle at 20°F (-6° C)	2 Years
L 910W	Acrylic Polymer	1 Gallon 4 Gallon	n/a	n/a	n/a	n/a	Varies ³	Light tan	1/8" x 1/8" x 1/16" V notch OR 1/16" x 1/16" x 1/16" square notch	1 Cycle at 20°F (-6° C)	2 Years
660 (2-Part)	Polyurethane	1/2 Gallon 1 Gallon 2 Gallon	n/a	6	80%	9	Varies ⁴	Grey	1/16" x 1/16" x 1/16" square notch OR 1/32" x 1/16" x 1/32" fine notch	Do NOT Freeze	1 Year

- 1: Concrete substrates with pH readings lower than 7.0 pH or in excess of the numbers listed above will require remediation prior to installation.
- 2: Sustain 1299 and FST 1299 are **NOT** applicable for all installations. Refer to the Technical Data Sheets for additional information and contact Forbo's Product Support & Education Services **PRIOR** to installing with this adhesive.
- 3: Spread rate is approx. 90 ft²/gallon when using a 1/8" x 1/8" x 1/16" V notch trowel **OR** approx. 125 ft²/gallon when using a 1/16" x 1/16" x 1/16" square notch trowel.
- 4: Spread rate is approx. 110-120 ft²/gallon when using a 1/16" x 1/16" x 1/16" square notch trowel **OR** approx. 150-160 ft²/gallon when using a 1/32" x 1/16" x 1/32" fine notch trowel.

Please contact Forbo Product Support & Education Services for additional information.