

eurocol

543

the strong connection



EUROSAFE DECO

Dyspersyjny klej o wysokiej sile klejenia oraz bardzo długim czasie stosowania. Do montażu okładzin ściennych PVC oraz płytek winylowych LVT. Możliwość aplikacji wałkiem. Charakteryzuje się niskim zużyciem. Odporny na wysoką temperaturę.

OPIS PRODUKTU

Baza surowcowa	Dyspersja akrylowa.
Kolor	Jasny niebieski.
Konsystencja	Płynna.

- Trwała lepkość (klei do 48h)
- Łatwość aplikacji także wałkiem
- Odporność na wysokie temperatury
- Niskie zużycie (150g/mkw)
- Najwyższa siła klejnia
- System EKO

DANE TECHNICZNE

Zużycie	150-200 g/m ²
Czas wiązania	24 hours.*
Palność	Niepalny.
Odporność na mróz	Nie.
Gęstość	1.04 kg/l.

ZASTOSOWANIE

For the installation of dimensionally stable PVC sheet, strips and tiles on levelled subfloors. Suitable for pressure sensitive installation. Also high temperature resistant, up to a structural surface temperature of maximum 50 °C, for installation in areas with direct sunlight.

STOSOWANIE

Magazynowanie	Oryginalnie, szczelnie zamknięte opakowania w temperaturze poniżej 30 °C
Narzędzia	Eurocol spreader no. 852/A2.
Czas odparowania/oczekiwania	None.
Środek czyszczący	Woda.

*-orientacyjne dane laboratoryjne, mogą ulegać zmianie w zależności od warunków na budowie

543 EUROSAFE DECO

Podłoże:

- 543 Eurosafe Deco is suitable for any type of subfloor that has good tensile and compression strength. The subfloor should also be even, clean, permanently dry and free from grease and dirt according to the requirements of BS 8203 or DIN 18 365.
- Anhydrite floors should be sandpapered. Thereafter make the floor dust free and prime with 044 Europrimer Multi. This layer has to dry sufficiently.
- For an optimal final result, apply a 2 mm levelling compound layer on the subfloor.
- In advance always seek our technical data sheets. In doubt about the application ask for technical advice.

Sposób użycia:

- It is very important to acclimatize the PVC-material for at least 48 hours in the room where it will be installed.
- Apply the 543 Eurosafe Deco with a Fur roller and/or brush.
- The sheets, strips or tiles can be placed directly into the wet, semi moist or dry adhesive.
- Drying time is depending on temperature, relative humidity and the porosity of the subfloor.
- After applying carefully roll and firmly rub the strips or tiles in to the adhesive line.
- Drying time minimal 24 hours.
- Remove fresh adhesive spots immediately with a clean damp cloth.

Working conditions:

Required surrounding temperature : 18 - 23 °C

Temperature for material and subfloor : min. 15° - max. 20 °C.

Relative humidity : 40-80%.

High temperature characteristics: underfloor heating systems and direct sunlight:

543 Eurosafe Deco can be applied on underfloor heating systems. The start protocol of the floor heating needs to be completely executed in accordance with the directives of the supplier. Turn off the heater 24 hours before fixation. Do not heat again until at least 24 hours after fixation, in steps of maximum 5 °C water temperature per day.

If there is the possibility that the PVC- strips or tiles will get warmer than 50 °C (also by sunlight), you have to choose for a polyurethane bonding.

543 Eurosafe Deco is tested in combination with high temperatures. The adhesive is tested suitable for installing PVC-material, exposed to higher temperatures such as direct sunlight provided the surface does not exceed 50 °C. Installation in wet adhesive is preferred for such conditions.

Contains methylchloroisothiazolinone and methylisothiazolinone (3:1) and benzisothiazolinone. May produce an allergic reaction.

GWARANCJA JAKOŚCI



OCHRONA ZDROWIA(BHP) I ŚRODOWISKA

Klasa zagrożenia	Brak.
Karta charakterystyki	Więcej informacji znajduje się w karcie charakterystyki dostępnej na stronie www.forbo-eurocol.de
Telefon kontaktowy dla alergików	Informacje dla alergików: +49 361 730410, +48 61 862 13 82.

OPAKOWANIA

Article	Definition	Packaging	EAN-code
543	Eurosafe Deco	10 kg bucket.	8 710345 543002

543 EUROS SAFE DECO