

## 414 EUROFLEX LINO PLUS

Linoleum adhesive with a high initial grab.



---

### Product Typification

---

Basis : Synthetic resin dispersion.  
Colour : Beige.  
Consistency : Thick liquid.

- Non-flammable
- Easy and safe to apply
- High initial adhesion strength
- Favourable spreading capacity
- Roller-castor-chair resistant

---

### Performances

---

Consumption : 400 - 450 g/m<sup>2</sup>.  
Flammability : Non-flammable.  
Specific weight : 1.30 kg/l.

---

### Application

---

#### For installing:

- linoleum in sheets and tiles
- colovinyl
- linoleum in decorative designs and mosaic.

---

### Working Process

---

Storage : Store cool and free from frost.  
Tools : Eurocol spreader no. 850/B1.  
Open time : 15-20 minutes.\*  
Latency : None.  
Drying time : 24 hours.\*  
Shelf Life : 12 months, in unopened packaging.

\* The mentioned values have been established in our laboratory and must be considered as guidelines in view of possible variations in climatic circumstances, subfloor compositions and layer thickness.

#### Substrate:

- 414 Euroflex Lino Plus is suitable for any type of subfloor that has a good tensile and compression strength. The subfloor should also be even, clean, permanently dry and free from grease and dirt, according to the requirements of BS 8203 or DIN 18 365.
- In advance always seek our technical data sheets. In doubt about the application ask for technical advice.

User manual:

Working conditions:

Required surrounding temperature : 18 - 23 °C.  
Temperature for material and subfloor : min. 15° - max. 20 °C.  
Relative humidity : 40 - 80%.

Directions for use:

- Apply the adhesive with a regular notched adhesive spreader (Eurocol spreader no. 850/B1).
- On absorbent subfloors apply the floor covering directly into the wet adhesive. On low absorbent subfloors keep a waiting time of approx. 10 minutes.
- Roll the floor covering carefully. Sheet-ends, possible bight marks and longitudinal joints are to be pressed firmly.
- On low absorbent subfloors, rolling and pressing should be repeated after approx. 15 minutes (depending on temperature, relative humidity and subfloor).
- Remove fresh adhesive spots immediately with water.

Underfloor heating systems:

414 Euroflex Lino Plus can be applied on underfloor heating systems. The startprotocol of the floorheating needs to be completely executed in accordance with the directives of the supplier. Turn off the heater 24 hours before application. Do not heat again until at least 24 hours after installation, in steps of 5 °C per day.

Contains methylchloroisothiazolinone and methylisothiazolinone (3:1) and benzisothiazolinone. May produce an allergic reaction.

---

## Environment and health

---

Safety and environment : Safety data sheets of Forbo Eurocol products according to EEG-guideline 91/155.  
MSDS : Available on request.

---

## Articles

---

Article	Definition	Packaging	EAN-code
414	Eurosafe Lino Plus	14 kg Bucket	8 710345 414302