

TECHNICAL SPECIFICATIONS

Marmoleum Modular meets the requirements of EN-ISO 24011

	Total thickness	EN-ISO 24346	2.50 mm			
	Domestic: heavy	EN-ISO 10874	Class 23			
	Commercial: very heavy	EN-ISO 10874	Class 34			
	Light Industrial: heavy	EN-ISO 10874	Class 43			
	Dimensions (length x width)	EN-ISO 24342	25 x 25 cm	50 x 25 cm	50 x 50 cm	75 x 50 cm
	Squareness and straightness	EN-ISO 24342	≤ 0.25 mm	≤ 0.35 mm	≤ 0.35 mm	≤ 0.35 mm
	Indentation residual	EN-ISO 24343-1	≤ 0.15 mm			
	Castor chair continuous use	EN 425	Suitable for office chairs with castors			
	Light fastness	EN-ISO 105-B02	Method 3: blue scale minimum 6			
	Resistance to chemicals	EN-ISO 26987	Resistant to diluted acids, oils, fats and to conventional solvents. Not resistant to prolonged exposure to alkalis			
	Bacteriostatic properties		Marmoleum has natural bacteriostatic properties, which are confirmed by independent laboratories, even against the bacteria MRSA			
	Cigarette resistance	EN 1399	Marks left on linoleum as a result of stubbed-out cigarettes can be removed			
	Slip resistance	DIN 51130	R9			
	Acoustical impact sound reduction	EN ISO 717-2	≤ 5 dB			
	Life Cycle Assessment		LCA is the foundation for securing the lowest environmental impact			

EN 14041

 0200203-DoP-306

Marmoleum meets the requirements of EN 14041

	Reaction to fire	EN 13501-1	Cfl-s1			
	Slip resistance	EN 13893	DS: ≥ 0.30			
	Body voltage	EN 1815	< 2 kV			
	Thermal conductivity	EN 12524	0.17 W/m-K			