MATERIAL SAFETY DATA SHEET

Page 1 of 2

Forbo Flooring, Inc., P.O. Box 667, Hazleton, PA. 18202 24-Hour Emergency Telephone: (800) 424-9300

PRODUCT NAME:	FORBO WALL BASE	E			
WHMIS CLASS:					
DESCRIPTION:	Vinyl Compound (P	VC)			
TRANSPORT:	DOT: Not regulated				
HMIS CODE:	HEALTH (0) F	IRE (0) REACTIVITY	(0) SPECIFIC (0)		
	0: Minimal; 1	.: Light; 2: Moderate	e; 3: High;	4: Dangerous	
SUPPLIER:	Forbo Flooring Syst	tems			
	P.O. Box 667				
	Hazleton, PA 18202	2			
	Phone: (800) 842-7	7839			
	EMERGENCY PHON	NE NUMBER: (800) 424-9	9300		
SECTION 2. HAZARI	DOUS INGREDIENTS				
	CAS	% by			
Chemical Name	<u>Number</u>	<u>Weight</u>	ACGIH TLV	<u>OSHA PEL</u>	
None					
SECTION 3. PHYSIC	AL PROPERTIES				
BOILING POINT (°F): N			SPECIFIC GRAVITY (WATER = 1): 1.6 (Approx.)		
APOR PRESSURE: N/A		VAPOR	VAPOR DENSITY (air=1): N/A		
% VOLATILE BY WEIGH	IT: N/D	pH: N//			
% VOLATILE BY WEIGH MELTING POINT (°F): I	IT: N/D N/A	pH: N// EVAPO			
% VOLATILE BY WEIGH MELTING POINT (°F): I SOLUBILITY IN WATER	IT: N/D N/A (%): Essentially insolub	pH: N// EVAPO le	A RATION RATE: N/A		
% VOLATILE BY WEIGH MELTING POINT (°F): I SOLUBILITY IN WATER	IT: N/D N/A (%): Essentially insolub	pH: N// EVAPO	A RATION RATE: N/A		
% VOLATILE BY WEIGH MELTING POINT (°F): I SOLUBILITY IN WATER APPEARANCE AND OD	IT: N/D N/A (%): Essentially insolub	pH: N// EVAPO le file extrusion - characte	A RATION RATE: N/A		
% VOLATILE BY WEIGH MELTING POINT (°F): I SOLUBILITY IN WATER APPEARANCE AND OD	IT: N/D N/A (%): Essentially insolub OR: Flexible rubber pro ID EXPLOSION HAZAF	pH: N// EVAPO le file extrusion - characte	A RATION RATE: N/A		
% VOLATILE BY WEIGH MELTING POINT (°F): I SOLUBILITY IN WATER APPEARANCE AND OD SECTION 4. FIRE-AN	IT: N/D N/A (%): Essentially insolub OR: Flexible rubber pro ID EXPLOSION HAZAF	pH: N// EVAPO le file extrusion - characte	A RATION RATE: N/A		
% VOLATILE BY WEIGH MELTING POINT (°F): I SOLUBILITY IN WATER APPEARANCE AND OD SECTION 4. FIRE-AN FLAMMABLE: Yes I IF YES, IN WHICH CON	IT: N/D N/A (%): Essentially insolub OR: Flexible rubber pro ID EXPLOSION HAZAF () No (X) DITIONS:	pH: N// EVAPO le file extrusion - characte	A RATION RATE: N/A		
% VOLATILE BY WEIGH MELTING POINT (°F): I SOLUBILITY IN WATER APPEARANCE AND OD SECTION 4. FIRE-AN FLAMMABLE: Yes	IT: N/D N/A (%): Essentially insolub OR: Flexible rubber pro ID EXPLOSION HAZAF () No (X) DITIONS:	pH: N// EVAPO le file extrusion - characte	A RATION RATE: N/A		
% VOLATILE BY WEIGH MELTING POINT (°F): I SOLUBILITY IN WATER APPEARANCE AND OD SECTION 4. FIRE-AN FLAMMABLE: Yes (IF YES, IN WHICH CON FLASH POINT (°)F: N/E METHOD: N/D	IT: N/D N/A (%): Essentially insolub OR: Flexible rubber pro ID EXPLOSION HAZAF () No (X) DITIONS:	pH: N// EVAPO ofile extrusion - characte RD DATA	A RATION RATE: N/A		
% VOLATILE BY WEIGH MELTING POINT (°F): I SOLUBILITY IN WATER APPEARANCE AND OD SECTION 4. FIRE-AN FLAMMABLE: Yes (IF YES, IN WHICH CON FLASH POINT (°)F: N/D METHOD: N/D AUTO-IGNITION TEMP FLAMMABLE LIMITS (9	IT: N/D N/A (%): Essentially insolub OR: Flexible rubber pro ID EXPLOSION HAZAF () No (X) DITIONS: 0. ERATURE (°F): Excess 6 6 VOL. IN AIR):	pH: N// EVAPO ofile extrusion - characte RD DATA 500 °F LOWER LIMIT: N/D	A RATION RATE: N/A		
% VOLATILE BY WEIGH MELTING POINT (°F): I SOLUBILITY IN WATER APPEARANCE AND OD SECTION 4. FIRE-AN FLAMMABLE: Yes (IF YES, IN WHICH CON FLASH POINT (°)F: N/D AUTO-IGNITION TEMP FLAMMABLE LIMITS (9 EXTINGUISHING MEDI	IT: N/D N/A (%): Essentially insolub OR: Flexible rubber pro ID EXPLOSION HAZAF () No (X) DITIONS: D. ERATURE (°F): Excess 6 6 VOL. IN AIR): A: Water spray, CO2 and	pH: N// EVAPO ofile extrusion - characte RD DATA 500 °F LOWER LIMIT: N/D	A RATION RATE: N/A ristic rubber odor	i/D	
% VOLATILE BY WEIGH MELTING POINT (°F): I SOLUBILITY IN WATER APPEARANCE AND OD SECTION 4. FIRE-AN FLAMMABLE: Yes (IF YES, IN WHICH CON FLASH POINT (°)F: N/E METHOD: N/D AUTO-IGNITION TEMP FLAMMABLE LIMITS (9 EXTINGUISHING MEDI SPECIAL FIRE-FIGHTIN	AT: N/D N/A (%): Essentially insolub OR: Flexible rubber pro ID EXPLOSION HAZAF () No (X) DITIONS: D. ERATURE (°F): Excess 6 6 VOL. IN AIR): A: Water spray, CO2 and G PROCEDURES: N/A	pH: N// EVAPO offile extrusion - characte RD DATA 500 °F LOWER LIMIT: N/D d dry chemical	A RATION RATE: N/A ristic rubber odor UPPER LIMIT: N	I/D	
% VOLATILE BY WEIGH MELTING POINT (°F): I SOLUBILITY IN WATER APPEARANCE AND OD SECTION 4. FIRE-AN FLAMMABLE: Yes (IF YES, IN WHICH CON FLASH POINT (°)F: N/D AUTO-IGNITION TEMP FLAMMABLE LIMITS (? EXTINGUISHING MEDI SPECIAL FIRE-FIGHTIN UNUSUAL FIRE AND E?	IT: N/D N/A (%): Essentially insolub OR: Flexible rubber pro ID EXPLOSION HAZAF () No (X) DITIONS: 0. ERATURE (°F): Excess 6 6 VOL. IN AIR): A: Water spray, CO2 and G PROCEDURES: N/A (PLOSION HAZARDS: Hy	pH: N// EVAPO ofile extrusion - characte RD DATA 500 °F LOWER LIMIT: N/D	A RATION RATE: N/A ristic rubber odor UPPER LIMIT: N	I/D	
% VOLATILE BY WEIGH MELTING POINT (°F): I SOLUBILITY IN WATER APPEARANCE AND OD SECTION 4. FIRE-AN FLAMMABLE: Yes (IF YES, IN WHICH CON FLASH POINT (°)F: N/D METHOD: N/D AUTO-IGNITION TEMP FLAMMABLE LIMITS (? EXTINGUISHING MEDI SPECIAL FIRE-FIGHTIN UNUSUAL FIRE AND EX SECTION 5. REACTIV	IT: N/D N/A (%): Essentially insolub OR: Flexible rubber pro ID EXPLOSION HAZAF () No (X) DITIONS:). ERATURE (°F): Excess 6 6 VOL. IN AIR): A: Water spray, CO ₂ and G PROCEDURES: N/A (PLOSION HAZARDS: Hy VITY DATA	pH: N// EVAPO offile extrusion - characte RD DATA 500 °F LOWER LIMIT: N/D d dry chemical	A RATION RATE: N/A ristic rubber odor UPPER LIMIT: N	I∕D	
% VOLATILE BY WEIGH MELTING POINT (°F): I SOLUBILITY IN WATER APPEARANCE AND OD SECTION 4. FIRE-AN FLAMMABLE: Yes (IF YES, IN WHICH CON FLASH POINT (°)F: N/D METHOD: N/D AUTO-IGNITION TEMP FLAMMABLE LIMITS (? EXTINGUISHING MEDI SPECIAL FIRE-FIGHTIM UNUSUAL FIRE AND EX SECTION 5. REACTIV STABILITY: Unstable (IT: N/D N/A (%): Essentially insolub OR: Flexible rubber pro ID EXPLOSION HAZAF () No (X) DITIONS: 0. ERATURE (°F): Excess 6 6 VOL. IN AIR): A: Water spray, CO2 and G PROCEDURES: N/A KPLOSION HAZARDS: Hy VITY DATA	pH: N// EVAPO offile extrusion - characte RD DATA 500 °F LOWER LIMIT: N/D d dry chemical	A RATION RATE: N/A ristic rubber odor UPPER LIMIT: N	J∕D	
% VOLATILE BY WEIGH MELTING POINT (°F): I SOLUBILITY IN WATER APPEARANCE AND OD SECTION 4. FIRE-AN FLAMMABLE: Yes (IF YES, IN WHICH CON FLASH POINT (°)F: N/C METHOD: N/D AUTO-IGNITION TEMP FLAMMABLE LIMITS (? EXTINGUISHING MEDI SPECIAL FIRE-FIGHTIN UNUSUAL FIRE AND EX SECTION 5. REACTIV STABILITY: Unstable (CONDITIONS TO AVOI	IT: N/D N/A (%): Essentially insolub OR: Flexible rubber pro ID EXPLOSION HAZAF () No (X) DITIONS: 0. ERATURE (°F): Excess 6 6 VOL. IN AIR): A: Water spray, CO2 and G PROCEDURES: N/A KPLOSION HAZARDS: Hy VITY DATA) Stable (X) D: None	pH: N// EVAPO ofile extrusion - characte RD DATA 500 °F LOWER LIMIT: N/D d dry chemical ydrogen Chloride Gas lib	A RATION RATE: N/A ristic rubber odor UPPER LIMIT: N	I/D	
% VOLATILE BY WEIGH MELTING POINT (°F): I SOLUBILITY IN WATER APPEARANCE AND OD SECTION 4. FIRE-AN FLAMMABLE: Yes (IF YES, IN WHICH CON FLASH POINT (°)F: N/E METHOD: N/D AUTO-IGNITION TEMP FLAMMABLE LIMITS (? EXTINGUISHING MEDI SPECIAL FIRE-FIGHTIN UNUSUAL FIRE AND EX SECTION 5. REACTIV STABILITY: Unstable (CONDITIONS TO AVOI HAZARDOUS POLYME	IT: N/D N/A (%): Essentially insolub OR: Flexible rubber pro ID EXPLOSION HAZAF () No (X) DITIONS:). ERATURE (°F): Excess 6 6 VOL. IN AIR): A: Water spray, CO2 and G PROCEDURES: N/A KPLOSION HAZARDS: Hy VITY DATA) Stable (X) D: None RIZATION: May Occur (pH: N// EVAPO ofile extrusion - characte RD DATA 500 °F LOWER LIMIT: N/D d dry chemical ydrogen Chloride Gas lib	A RATION RATE: N/A ristic rubber odor UPPER LIMIT: N	4/D	
% VOLATILE BY WEIGH MELTING POINT (°F): I SOLUBILITY IN WATER APPEARANCE AND OD SECTION 4. FIRE-AN FLAMMABLE: Yes (IF YES, IN WHICH CON FLASH POINT (°)F: N/E METHOD: N/D AUTO-IGNITION TEMP FLAMMABLE LIMITS (? EXTINGUISHING MEDI SPECIAL FIRE-FIGHTIN UNUSUAL FIRE AND E? SECTION 5. REACTIV STABILITY: Unstable (CONDITIONS TO AVOI HAZARDOUS POLYME CONDITIONS TO AVOI	AT: N/D N/A (%): Essentially insolub OR: Flexible rubber pro ID EXPLOSION HAZAF () No (X) DITIONS:). EERATURE (°F): Excess 6 6 VOL. IN AIR): A: Water spray, CO2 and G PROCEDURES: N/A KPLOSION HAZARDS: Hy VITY DATA () Stable (X) D: None RIZATION: May Occur (D: None known	pH: N// EVAPO offile extrusion - characte RD DATA 500 °F LOWER LIMIT: N/D d dry chemical ydrogen Chloride Gas lib	A RATION RATE: N/A ristic rubber odor UPPER LIMIT: N erated in combustion		
% VOLATILE BY WEIGH MELTING POINT (°F): I SOLUBILITY IN WATER APPEARANCE AND OD SECTION 4. FIRE-AN FLAMMABLE: Yes (IF YES, IN WHICH CON FLASH POINT (°)F: N/C METHOD: N/D AUTO-IGNITION TEMP FLAMMABLE LIMITS (9 EXTINGUISHING MEDI SPECIAL FIRE-FIGHTIN UNUSUAL FIRE AND E2 SECTION 5. REACTIV STABILITY: Unstable (CONDITIONS TO AVOI INCOMPATIBILITY (ma	IT: N/D N/A (%): Essentially insolub OR: Flexible rubber pro ID EXPLOSION HAZAF () No (X) DITIONS:). ERATURE (°F): Excess 6 6 VOL. IN AIR): A: Water spray, CO2 and G PROCEDURES: N/A (PLOSION HAZARDS: Hy VITY DATA) Stable (X) D: None RIZATION: May Occur (D: None known terials to avoid): Avoid	pH: N// EVAPO ofile extrusion - characte RD DATA 500 °F LOWER LIMIT: N/D d dry chemical ydrogen Chloride Gas lib	A RATION RATE: N/A ristic rubber odor UPPER LIMIT: N erated in combustion		
% VOLATILE BY WEIGH MELTING POINT (°F): I SOLUBILITY IN WATER APPEARANCE AND OD SECTION 4. FIRE-AN FLAMMABLE: Yes (IF YES, IN WHICH CON FLASH POINT (°)F: N/D AUTO-IGNITION TEMP FLAMMABLE LIMITS (? EXTINGUISHING MEDI SPECIAL FIRE-FIGHTIN UNUSUAL FIRE AND EX SECTION 5. REACTIV STABILITY: Unstable (CONDITIONS TO AVOI HAZARDOUS POLYME	AT: N/D N/A (%): Essentially insolub OR: Flexible rubber pro ID EXPLOSION HAZAF () No (X) DITIONS:). ERATURE (°F): Excess 6 6 VOL. IN AIR): A: Water spray, CO2 and G PROCEDURES: N/A (PLOSION HAZARDS: Hy VITY DATA) Stable (X) D: None RIZATION: May Occur (D: None known terials to avoid): Avoid essing.	pH: N// EVAPO offile extrusion - characte RD DATA 500 °F LOWER LIMIT: N/D d dry chemical ydrogen Chloride Gas lib	A RATION RATE: N/A ristic rubber odor UPPER LIMIT: N erated in combustion		
% VOLATILE BY WEIGH MELTING POINT (°F): I SOLUBILITY IN WATER APPEARANCE AND OD SECTION 4. FIRE-AN FLAMMABLE: Yes (IF YES, IN WHICH CON FLASH POINT (°)F: N/C METHOD: N/D AUTO-IGNITION TEMP FLAMMABLE LIMITS (9 EXTINGUISHING MEDI SPECIAL FIRE-FIGHTIN UNUSUAL FIRE AND E2 SECTION 5. REACTIV STABILITY: Unstable (CONDITIONS TO AVOI HAZARDOUS POLYME) CONDITIONS TO AVOI INCOMPATIBILITY (ma	AT: N/D N/A (%): Essentially insolub OR: Flexible rubber pro ID EXPLOSION HAZAF () No (X) DITIONS:). ERATURE (°F): Excess 6 6 VOL. IN AIR): A: Water spray, CO2 and G PROCEDURES: N/A (PLOSION HAZARDS: Hy VITY DATA) Stable (X) D: None RIZATION: May Occur (D: None known terials to avoid): Avoid essing. WA	pH: N// EVAPO offile extrusion - characte RD DATA 500 °F LOWER LIMIT: N/D d dry chemical /drogen Chloride Gas lib	A RATION RATE: N/A ristic rubber odor UPPER LIMIT: N erated in combustion		

MATERIAL SAFETY DATA SHEET

SECTION 6. PREVENTATIVE MEASURES				
VENTILATION:	When heated, provide adequate ventilation to remove smoke and			
	fumes from work area.			
RESPIRATORY PROTECTION:	None required with adequate ventilation			
EYE PROTECTION:	Safety glasses			
HAND PROTECTION:	Gloves			
OTHER PROTECTIVE EQUIPMENT:	None			
HANDLING:	Practice good personal hygiene			
STORAGE:	N/A			
SECTION 7. SPILL OR LEAK PROCEDURES				
STEPS TO BE TAKEN IF MATERIAL	Material may be swept, shoveled or vacuumed into containers for			
IS RELEASED OR SPILLED:	reuse or disposal. Use NIOSH approved respiratory equipment where dust is possible.			
WASTE DISPOSAL METHOD:	Sanitary landfill or incineration in accordance with Federal, State or local regulations. If incineration is used, recognition should be made that corrosive Hydrogen Chloride is generated.			
OTHER INFORMATION:				
SECTION 8. HEALTH HAZARD DATA				
ABSORPTION ROUTE:	Skin () Eyes ()			
	Inhalation () INGESTION ()			
EFFECTS OF OVEREXPOSURE:	The ingredients listed in Section 2 are incorporated into the product and will not be released. They are provided for information. No acute effect expected.			
SKIN:	Contact not expected to be harmful.			
EYES:	Not expected to be harmful.			
INHALATION:	Not expected to be harmful.			
INGESTION:	N/A			
SECTION 9. FIRST AID PRCEDURES				
SKIN: Wash with soap and wa	Wash with soap and water.			
	Flush with water and remove the dirt particles.			
	Move person to fresh air, give artificial respiration if necessary.			
INGESTION: Call a physician.				
SECTION 10. PREPARATION INFORMATION				

DATE ISSUED: June 1, 2015 [Rev. 3]

Forbo Flooring Systems has compiled the information and recommendations contained in this Material Safety Data Sheet from sources believed to be reliable and to represent the most reasonable current opinion on the subject when the MSDS was prepared. No warranty, guaranty or representation is made as to the correctness or sufficiency of the information. The user of this product must decide for himself what safety measures are necessary to safely use this product, either alone or in combination with other products.

N/A: Not applicable N/D: Not determined N/E: Not established