












Technical specifications

Coral meets the requirements of EN 1307

Coral move FR

	Total thickness	ISO 1765	8 mm
	Roll width	EN-ISO 24341	185 cm (customizable)
	Roll length	EN-ISO 24341	27.5 m (customizable)
	Minimum order quantity		500 m ²
	Total weight	ISO 8543	3000 gram/m ²
	Pile installation weight	ISO 8543	750 gram/m ²
	Pile thickness	ISO 1766	5.5 mm
	Pile material		100% polyamide BCF ECONYL [®]
	Colour fastness ratings:		
	Light	EN ISO 105/B02	8
	Rubbing	EN ISO 105/X12	4-5
	Water	EN ISO 105/E01	4-5
	Seawater	EN ISO 105/E02	5
	Water stains	EN 1307 annex G	5
	Shampoo	BS 1006	4-5
	Organic solvents	EN ISO 105/X05	5
	Contact sound insulation	EN ISO 717-2	$\Delta L_w = 28$ dB
	Application	EN 1307	Class 32
	TVOC after 28 days	ISO 16000-9	<50 µg/m ³
	Tested flammability standards	EN 45545-2	HL3 Subfloor: Plywood Adhesive: Eurocol 640
	Coral meets the requirements of EN 14041		 EN 14041
	Fire behaviour	EN 13501-1	B _{fl} -s1
	Body voltage	ISO 6356	< 2 kV
	Thermal conductivity	EN 12524	0.108 m ² K/W

Coral move FR is made to order