

FORBO MARMOLEUM MODULAR TECHNICAL DATA

1. PRODUCT NAME & MANUFACTURER

1.1 Product:

Forbo Marmoleum Modular linoleum tile resilient floor covering

1.2 Manufacturer:

Forbo Flooring Systems Humboldt Industrial Park Hazleton, PA 18202

www.forboflooringNA.com

Phone: +1-800-842-7839 (US)

+1-800-268-8108 (CA) topshield

Fax: +1-570-450-0258

1.3 Product Description:

Construction: Marmoleum Modular is a homogeneous floor covering made from natural ingredients including flax seed oil, rosin binders, wood flour, limestone and dry pigments which are mixed and then calendared onto a polyester backing to ensure optimum dimensional stability.

Topshield is a high-performance finish. Its double UV cured double layer technology delivers extraordinary performance and clear and vibrant colors that remain over time. Topshield creates a 'ready to use' Marmoleum that requires no initial maintenance or polymer application. The surface can be repaired or refreshed in cases of accidents or after years of intensive use.

1.4 Physical Characteristics:

(dimensions are approximate)

Size 9.8" x 9.8" (25 cm x 25 cm)
9.8" x 19.69" (25 cm x 50 cm)
19.69" x 19.69" (50 cm x 50 cm)
Gauge 1/10" (2.5 mm)
Backing Polyester
Packaging 9.8" x 9.8": 40 tiles (26.91 ft ² or 2.5 m ²)
9.8" x 19.69": 40 tiles (53.82 ft ² or 5 m ²)
19.69" x 19.69": 20 tiles (53.82 ft ² or 5 m ²)

2. PRODUCT PERFORMANCE & TECHNICAL DATA

2.1 Reference Specification:

Meets or exceeds all technical requirements as set forth in ASTM F 2195 Standard Specification for Linoleum Tile Flooring.

Type I

2.2 Environmental:

100% USDA Certified BioBased Product. Compliant with CDPH 01350 requirements for VOC emissions and indoor air quality. Forbo Marmoleum Modular contributes to LEED v4.1 credits. For additional information, contact Forbo Flooring Systems.

2.3 Static Load Limit:

Residual compression of 0.002" with 250 pounds per square inch when tested in accordance with ASTM F 970-17, Standard Test Method for Static Load Limit.

2.4 Slip Resistance:

Meets or exceeds the industry recommendation of >0.5 for flat surfaces when tested in accordance with ASTM D 2047, Standard Test Method for Static Coefficient of Friction.

2.5 Castor Resistance:

Suitable for office chairs with castors when tested in accordance with ISO 4918, Castor Chair Test.

2.6 Impact Sound Reduction:

5dB when tested in accordance with ISO 717-2, Impact Sound Insulation Test.

2.7 Resistance to Bacteria:

Provides a self-sanitizing quality in the form of a bactericidal effect. Independent testing has shown that a sterile zone around the material inhibits the growth of organisms such as staphylococcus aureus and Clostridium difficile.

2.8 Anti-Static Properties:

Naturally anti-static. This property makes cleaning easier because dirt and dust does not cling to the surface as it may with other materials.

2.9 Fire Testing:

Class 1 when tested in accordance with ASTM E 648/ NFPA 253, Standard Test Method for Critical Radiant Flux. Meets 450 or less when tested in accordance with ASTM E 662/ NFPA 258, Standard Test Method for Smoke Density.

FSR – 115; SDC – 205 when tested in accordance to CAN/ULC S102.2, Standard Test Method for Flame Spread Rating and Smoke Development of Flooring Materials. Class C when tested in accordance to ASTM E 84/ NFPA 255, Standard Test Method for Surface Burning Characteristics.

2.10 Cigarette Resistance:

Resists cigarette burns. Burning cigarettes will leave only a brown mark, which can be rubbed out using steel wool or a scouring pad.





2.11 Chemical Resistance:

(Exposure Time - 1h)*

Diluted Acids – Sulfuric, Nitric, Hydrochloric, Acetic,	
Lactic, CitricIsopropyl Alcohol (70%)	No Change
Isopropyl Alcohol (70%)	No Change
Sodium Hydroxide (5%)	No Change
Ammonia (5%), Acetone	No Change
Soda Solution, Soap Solution	
(Slightly Alkaline)	No Change
Gasoline, Kerosene, White Spirit, Paraffin	No Change
Benzene, Toluene, Methyl Alcohol,	
Ethyl Acetate	No Change
Methyl Ethyl Ketone, Ether, Phenol (5%)	
Mineral Oil, Olive Oil, Vegetable Oil,	
Animal Fat	
Blood, Urine, Excrement	- No Change
Formaldehyde, Hydrogen Peroxide 3%	No Change
Hot Chili Paste, Iodine, Betadine, Hair Dye	No Change
Shoe Polish, Lipstick	
Silver Nitrate	
Bitumen, Salt Water	
Methylene Blue	
Gel-Based Hand Sanitizer, Bleach	No Change
Tested in accordance with ASTM F 925, Standard Test	
Method Resistance to Chemicals of Resilient Flooring.	
*Marmoleum is NOT resistant to prolonged e	xposure to
high alkalis.	

3. INSTALLATION

3.1 Adhesive:

Use Forbo EZ-ON 100, Forbo Sustain 100, Forbo T 940, Forbo Sustain 1195, or Forbo 660 adhesive.

3.2 Heat Welding:

Heat welding is not necessary for all installations, however it is optional. For seamless, hygienic watertight installation requirements, use Forbo Marmoweld welding rod.

Welding rod dimensions: 4 mm; 165 linear feet per spool.

3.3 Heat Welding Is Not Required:

Forbo Marmoweld ETU is a color-matched sealant used to complete the installation of Forbo Marmoleum in place of heat welding. To use, sparingly apply Forbo Marmoweld ETU to all seams on the floor with a 1" (2.54cm) putty knife or plastic applicator. Ensure there are no sharp or damaged edges on the applicator that might scratch or damage the Forbo Marmoleum. Wipe all excess Forbo Marmoweld ETU off the surface of the Forbo Marmoleum with a clean, damp white cloth.

3.4 Installation Guidelines:

Forbo does NOT recommend the application of adhesive tape on Marmoleum. Adhesive tape may cause damage to the factory coating of resilient flooring products. When using floor protection materials, tape the seams of the floor protection together and secure the floor protection by weighing down in corners and against walls. DO NOT secure floor protection materials by taping them directly to the surface of resilient floor coverings.

Refer to Forbo's Installation Guidelines for complete installation recommendations.

4. WARRANTY

Limited 30-year warranty. For complete details, contact Forbo Flooring.

5. CARE & CLEANING

Refer to Forbo's Floor Care Guidelines for complete care recommendations.

