

























Technical specifications

Sphera StarT meets the requirements of EN ISO 10581

	Total thickness	EN ISO 24346	2.0 mm
	Surface finish		PUR
	Binder content	EN ISO 10581	Type 1
	Collection size		16
	Domestic use	EN ISO 10874	Class 23
	Commercial use	EN ISO 10874	Class 34
	Light industrial use	EN ISO 10874	Class 43
	Roll width	EN ISO 24341	2.0 m
	Roll length	EN ISO 24341	≤ 20 m
	Total weight	EN ISO 23997	2800 g/m ²
	Dimensional stability <i>Typical value</i>	EN ISO 23999	≤ 0.25 %
	Slip resistance (ramp test)	DIN 51130	R9
	Castor chair continuous use	ISO 4918	Pass
	Residual indentation <i>Typical value</i>	EN ISO 24343-1	~ 0.02mm
	Colour fastness to light	EN ISO 105-B02 method 3	≥ 6
	Indoor Air Emissions: TVOC after 28 days	EN 16516	A+
	Resistance to chemicals	EN ISO 26987	Very good
	Flexibility	EN ISO 24344	0.7 mm
	Use in wet areas	EN 13553	Yes
	Bacteria resistance	EN ISO 846	Does not support growth

Sphera StarT meets the requirements of EN 14041:2004

EN 14041
CE
0200301 - DOP - 605

	Reaction to fire	EN 13501-1	B _n -s1, G, CS
	Slip resistance	EN 13893	μ ≥ 0.30
	Thermal conductivity	EN 12524	0.25 W/mK
	Body voltage	EN 1815	≤ 2.0 kV