

eurocol

509

the strong connection

7-6-2026



EUROSAFE TEX

Carpet adhesive with a high initial grab.

PRODUCT TYPING

Base Synthetic resin dispersion.

- Non-flammable
- Easy and safe to apply
- High initial adhesion strength
- Favourable spreading capacity
- Roller-castor-chair resistant

PROPERTIES

Consumption 325 - 425 g/m².

Flammability Non-flammable.

Sensitive to frost Yes.

Specific weight 1.55 kg/l.

APPLICATION

For installing:

- synthetic backed carpet
- hessian-backed carpet
- needlefelt
- fillerfree carpet.

PROCESSING

Storage Store cool and free from frost.

Tools Eurocol spreader no. 850/B1.

Curing 24 hours.*

Open time 15 - 30 minutes.*

Waiting time 0-10 minutes.*

Shelf Life Approx 15 months, in unopened packaging.

Cleaner Water.

** The stated values are laboratory values which, given the large variation in climatological conditions, subfloor compositions and layer thicknesses, are only guideline values.*

509 EUROSAFE TEX

Substrate:

- 509 Eurosafe Tex is suitable for any type of subfloor that has a good tensile and compression strength. The subfloor should also be even, clean, permanently dry and free from grease and dirt, according to the requirements of BS 8203 or DIN 18 365.
- Only use pervious floor covering on impervious subfloors.
- When installing fillerfree carpet on impervious subfloors apply a 2 mm levelling compound layer.
- In advance always seek our technical data sheets. In doubt about the application ask for technical advice.

Instruction manual:

- Apply the adhesive with a regular notched adhesive spreader (Eurocol spreader no. 850/B1).
- On absorbent subfloors apply the floor covering directly into the wet adhesive. On low absorbent subfloors or impervious subfloors keep a waiting time of approx. 10 minutes (depending on porosity subfloor, temperature and relative humidity).
- When installing fillerfree carpet the subfloor should be moisture absorbent and keep a waiting time of approx. 20 minutes. Install fillerfree carpet only on absorbent subfloors.
- Roll the floor covering carefully. Sheet-ends and longitudinal joints are to be pressed firmly.
- On low absorbent subfloors, in case of impervious back qualities and/or when circumstances are less ideal, rolling and pressing should be repeated after approx. 15 minutes (depending on temperature, relative humidity, subfloor and floor covering).
- Remove fresh adhesive spots immediately with water.

Working conditions:

Required surrounding temperature : 18 - 23 °C.

Temperature for material and subfloor : min. 15° - max. 20 °C.

Relative humidity : 40 - 80%.

Underfloor heating systems:

509 Eurosafe Tex can be applied on underfloor heating systems. The startprotocol of the floorheating needs to be completely executed in accordance with the directives of the supplier. Turn off the heater 24 hours before application. Do not heat again until at least 24 hours after installation, in steps of maximum 5 °C water temperature per day.

Contains methylchloroisothiazolinone and methylisothiazolinone (3:1) and benzisothiazolinone. May produce an allergic reaction.

ENVIRONMENT AND HEALTH

Hazard Class	None.
Safety and environment	Safety data sheets of Forbo Eurocol products according to EEG-guideline 91/155. Keep out of reach of children. Do not eat, drink or smoke while processing the product. Only give completely empty containers for recycling. Material residues can be disposed of as household waste.
MSDS	For extensive information about safety and environment we refer to our website www.eurocol.nl .

ITEM DATA

Article	Definition	Packaging	EAN-code
509	Eurosafe Tex	15 kg Bucket	8 710345 521406

509 EUROS SAFE TEX