















## Technical specifications

**marmoleum<sup>®</sup>** real FR

Marmoleum real FR meets the requirements of EN 1307

	Total thickness	EN 428 / ISO 1765	2.5 mm
	Roll width	EN 426	200 cm
	Roll length	EN 426	≤ 32 m
	Total weight	EN 430 / ISO 8543	Approx. 2900 gram/m <sup>2</sup>
	Indentation residual	EN 433 / ISO 24343-1	≤ 0.15 mm
	Light fastness	EN ISO 105/B02	≥ 6
	Flexibility	EN 435 / ISO 24344	∅ 40 mm
	Resistance to chemicals	EN 423 / ISO 26787	Resistant to diluted acids, oils, fats and to the conventional solvents. Not resistant to prolonged exposure to alkalis
	Electrical resistance	EN 1081 / ISO 10965	1-10 <sup>6</sup> <R1<1-10 <sup>8</sup> Ω
	Contact sound insulation	ISO 717-2 ISO 140-8	Δ Lw = approx. 5 dB
	Tested flammability standards	EN 45545-2	HL2
		BS6853	1a
		DIN 5510-2	SF 1-3
		ASTM E.648-08 ASTM E.662-06	Class 1 pass
	Slip resistance	EN 13893 DIN 51130	≥ 0.30, R9
	Personal charging	ISO 6356	< 2 kV
	Heat transmission resistance	EN 12524	0.17 m <sup>2</sup> K/W

### All countries

Forbo Flooring Systems  
High Holborn Road  
Ripley  
Derbyshire DE5 3NT  
UK

Tel: +44 (0) 1773 744121  
Fax: +44 (0) 1773 744142

Email: [info@forbo-transportflooring.com](mailto:info@forbo-transportflooring.com)  
[www.forbo-flooring/transportation](http://www.forbo-flooring/transportation)

### Registered Office:

Forbo Flooring UK Limited  
High Holborn Road, Ripley  
Derbyshire DE5 3NT  
Registered in England: 9200318