

# eurocol

the strong connection

7-4-2026

# 444



## EUROFLEX MULTI

Multi-purpose floor covering adhesive with a high initial grab.

### PRODUCT TYPING

Base	Synthetic resin dispersion.
Color	Beige.
Consistency	Thick liquid.

- Non-flammable
- Easy and safe to apply
- Multi-purpose application
- High initial adhesion strength
- Favourable spreading capacity
- Roller-castor-chair resistant

### PROPERTIES

Consumption	375 - 450 g/m <sup>2</sup> .
Flammability	Non-flammable.
Sensitive to frost	Yes.
Specific weight	1.47 kg/l.

### APPLICATION

For installing:

- synthetic backed carpet
- hessian-backed carpet
- needlefelt
- linoleum
- corkment
- vinyl with a back of jute/polyester felt
- cushion vinyl (e.g. Novilon).

### PROCESSING

Storage	Store cool and free from frost.
Tools	Eurocol spreader no. 850/B1.
Curing	24 hours.*
Open time	15 - 20 minutes.*
Waiting time	None.

**444 EUROFLEX MULTI**

Shelf Life	12 months, in unopened packaging.
Cleaner	Water.

\* The stated values are laboratory values which, given the large variation in climatological conditions, subfloor compositions and layer thicknesses, are only guideline values.

Substrate:

- 444 Euroflex Multi is suitable for any type of subfloor that has a good tensile and compression strength. The subfloor should also be even, clean, permanently dry and free from grease and dirt, according to the requirements of BS 8203 or DIN 18 365.
- Only use pervious floor coverings on impervious subfloors.
- In advance always seek our technical data sheets. In doubt about the application ask for technical advice.

Instruction manual:

- Apply the adhesive with a regular notched adhesive spreader (Eurocol spreader no. 850/B1).
- On absorbent subfloors apply the floor covering directly into the wet adhesive. On low absorbent subfloors keep a waiting time of approx. 10 minutes.
- Roll the floor covering carefully. Sheet-ends, possible bight marks and longitudinal joints are to be pressed firmly.
- On low absorbent subfloors, in case of impervious back qualities and/or when circumstances are less ideal, rolling and pressing should be repeated after approx. 15 minutes.
- Remove fresh adhesive spots immediately with water.

Working conditions:

Required surrounding temperature : 18° - 23 °C.  
 Temperature for material and subfloor : min. 15° - max. 20 °C.  
 Relative humidity : 40 - 80%.

Underfloor heating systems:

444 Euroflex Multi can be applied on underfloor heating systems. The startprotocol of the floorheating needs to be completely executed in accordance with the directives of the supplier. Turn off the heater 24 hours before application. Do not heat again until at least 24 hours after installation, in steps of 5 °C per day.

Contains methylchloroisothiazolinone and methylisothiazolinone (3:1) and benzisothiazolinone . May produce an allergic reaction.

---

**ENVIRONMENT AND HEALTH**

---

Hazard Class	None.
Safety and environment	Safety data sheets of Forbo Eurocol products according to EEG-guideline 91/155.
MSDS	For extensive information about safety and environment we refer to our website <a href="http://www.eurocol.nl">www.eurocol.nl</a> .

---

**ITEM DATA**

---

Article	Definition	Packaging	EAN-code
444	Euroflex Multi	14 kg Bucket	8 710345 444101

**444 EUROFLEX MULTI**