

FORBO ETERNAL STEP SR AQUA TECHNICAL DATA

1. PRODUCT NAME & MANUFACTURER

1.1 Product:

Forbo Eternal Step SR Aqua vinyl sheet resilient floor covering

1.2 Manufacturer:

Forbo Flooring Systems US 8 Maplewood Drive Hazleton, PA 18202 1-800-842-7839

Forbo Flooring Systems Canada 3983 Nashua Drive, Unit 1 Mississauga, ON L4V 1P3 1-800-268-8108 (English) 1-800-567-9268 (French)

www.forboflooringNA.com

1.3 Product Description:

Construction: Eternal Step SR Aqua vinyl sheet floor covering is a heterogeneous product with a compact calendared backing and a flexible reinforced glass fleece innerlayer for dimensional stability. The scratch resistant PUR wearlayer contains transparent anti-slip crystals. The unique embossed shape is designed for wet room or barefoot areas.

1.4 Physical Characteristics:

(dimensions are approximate)

Gauge ----- 0.080" (2.0 mm) Width ---- 79" (2 meters) Wear layer ----- 0.0275" (0.7 mm) Length---- 82' (25 meters) Roll Size ---- 60 yards² (50 meters²)

2. PRODUCT PERFORMANCE & TECHNICAL DATA

2.1 Reference Specification:

Meets or exceeds all technical requirements as set forth in ASTM F 1303, Standard Specification for Vinyl Sheet Floor Covering With Backing

Type 1, Grade 1, Class B Backing

2.2 Environmental:

Compliant with CDPH 01350 requirements for VOC emissions and indoor air quality.

Forbo Eternal Step SR Aqua contributes to LEED v4.1 credits. For additional information, contact Forbo Flooring Systems.

2.3 Static Load Limit:

Residual compression of 0.002" with 250 pounds per square inch when tested in accordance with ASTM F 970-17, Standard Test Method for Static Load Limit.

2.4 Slip Resistance:

Meets or exceeds the industry recommendation of >0.5 for flat surfaces when tested in accordance with ASTM D 2047, Standard Test Method for Static Coefficient of Friction.

Suitable for use on flat or inclined surfaces.

2.5 Castor Resistance:

Suitable for office chairs with castors when tested in accordance with ISO 4918, Castor Chair Test.

2.6 Fire Testing:

Class 1 when tested in accordance with ASTM E 648/ NFPA 253, Standard Test Method for Critical Radiant Flux. Meets 450 or less when tested in accordance with ASTM E 662/ NFPA 258, Standard Test Method for Smoke Density.

2.7 Chemical Resistance:

(Exposure Time - 1h)

Isopropyl Alcohol No Effect Sodium Hydroxide (5%) No Effect Hydrochloric Acid (5%) No Effect Sulfuric Acid	Acetic Acid (5%)	No Effect
Hydrochloric Acid (5%)	Isopropyl Alcohol	No Effect
Sulfuric Acid — No Effect Ammonia (5%) — No Effect Bleach — No Effect Phenol (5%) — No Effect Gasoline — No Effect Kerosene — No Effect Brown or Black Shoe Polish — Moderate Color Change Iodine — Severe Color Change Betadine — No Effect Mineral Oil — No Effect Tested in accordance with ASTM F 925, Standard Test	Sodium Hydroxide (5%)	No Effect
Ammonia (5%)	Hydrochloric Acid (5%)	No Effect
Bleach No Effect Phenol (5%) No Effect Gasoline No Effect Kerosene No Effect Brown or Black Shoe Polish Moderate Color Change lodine Severe Color Change Betadine No Effect Mineral Oil No Effect Tested in accordance with ASTM F 925, Standard Test		
Phenol (5%) No Effect Gasoline No Effect Kerosene No Effect Brown or Black Shoe Polish Moderate Color Change Iodine Severe Color Change Betadine No Effect Mineral Oil No Effect Tested in accordance with ASTM F 925, Standard Test	Ammonia (5%)	No Effect
Gasoline No Effect Kerosene No Effect Brown or Black Shoe Polish Moderate Color Change Iodine Severe Color Change Betadine No Effect Mineral Oil No Effect Tested in accordance with ASTM F 925, Standard Test	Bleach	No Effect
Kerosene No Effect Brown or Black Shoe Polish Moderate Color Change Iodine Severe Color Change Betadine No Effect Mineral Oil No Effect Tested in accordance with ASTM F 925, Standard Test		
Brown or Black Shoe Polish Moderate Color Change lodine Severe Color Change Betadine No Effect Mineral Oil No Effect Tested in accordance with ASTM F 925, Standard Test	Gasoline	No Effect
lodine Severe Color Change Betadine No Effect Mineral Oil No Effect Tested in accordance with ASTM F 925, Standard Test	Kerosene	No Effect
Betadine No Effect Mineral Oil No Effect Tested in accordance with ASTM F 925, Standard Test		
Mineral Oil No Effect Tested in accordance with ASTM F 925, Standard Test	lodine Severe Colo	or Change
Tested in accordance with ASTM F 925, Standard Test	Betadine	No Effect
,	Mineral Oil	No Effect
Method for Resistance to Chemicals of Resilient Flooring	Tested in accordance with ASTM F 925, Standard	d Test
method for hesistance to chemicals of hesilient i looning.	Method for Resistance to Chemicals of Resilient	Flooring.

3. INSTALLATION

3.1 Adhesive:

Use Forbo 660 adhesive.

3.2 Heat Welding:

Seams must be heat welded. Use only Forbo Eternal Step SR Agua welding rod.

Welding rod dimensions: 4 mm; 165 linear feet per spool.

3.3 Flash Coving (OPTIONAL):

Flash cove up walls to the desired height. Use Forbo 660 adhesive.

3.4 Installation Guidelines:

Forbo does NOT recommend the application of adhesive tape on Eternal. Adhesive tape may cause damage to the factory coating of resilient flooring products. When using floor protection materials, tape the seams of the floor protection together and secure the floor protection by weighing down in corners and against walls. DO NOT secure floor protection materials by taping them directly to the surface of resilient floor coverings.

Refer to Forbo's Installation Guidelines for complete installation recommendations.



4. WARRANTY

Limited 10-year warranty. For complete details, contact Forbo Flooring.

5. CARE & CLEANING

Refer to Forbo's Floor Care Guidelines for complete care recommendations.