Technical specifications

Marmoleum meets the requirements of EN-ISO 24011 Marmoleum Acoustic meets the requirements of EN 687 Marmoleum Decibel meets the requirements of EN 686











			Marmoleum Real/Fresco 2.0 mm	Real/Fresco/Vivace/ Splash/Terra 2.5 mm	Marmoleum Real/Fresco 3.2 mm	Marmoleum Decibel	Marmoleum Acoustic	
<u>`</u>	Total thickness	EN-ISO 24346	2.0 mm	2.5 mm	3.2 mm	3.5 mm	4.0 mm	
	Surface finish		Topshield Pro	Topshield Pro	Topshield Pro	Topshield Pro	Topshield Pro	
Å	Domestic use	EN-ISO 10874	Class 23	Class 23	Class 23	Class 23	Class 23	
	Commercial use	EN-ISO 10874	Class 32	Class 34	Class 34	Class 33	Class 33	
	Light industrial use	EN-ISO 10874	Class 41	Class 43	Class 43	Class 41	Class 41	
	Collection size		29 colours	90 colours	8 colours	14 colours All items available as made to order	6 colours	
3	Roll width	EN-ISO 24341	2.00 m	2.00 m	2.00 m	1.90 / 2.00 m	2.00 m	
Ŋ	Roll length	EN-ISO 24341	≤ 33 m	≤ 33 m	≤ 33 m	≤ 33 m	≤ 33 m	
	Total weight Typical value	EN-ISO 23997	2300 g/m ²	2900 g/m²	3900 g/m²	3100 g/m ²	4000 g/m ²	
	Residual indentation Typical value	EN-ISO 24343-1	≤ 0.15 mm ~0.07 mm	≤ 0.15 mm ~0.08 mm	≤ 0.15 mm ~0.10 mm	≤ 0.30 mm ~0.20 mm	≤ 0.40 mm ~0.25 mm	
	Castor chair continuous use	ISO 4918/EN 425	Suitable for office chairs with castors					
7	Light fastness	EN-ISO 105-B02	Method 3: blue scale minimum 6					
2	Flexibility	EN-ISO 24344	ø 30 mm	ø 40 mm	ø 50 mm	ø 40 mm	ø 60 mm	
9	Resistance to chemicals EN-ISO 26987 Resistant to diluted acids, oils, fats and to the conventional solvents. Not resistant to prolonged exposure to alkalis						osure to alkalis	
7	Bacteriostatic properties* Marmoleum has natural bacteriostatic properties which are confirmed by independent laboratories, even against the bacteria MRS							
	Cigarette resistance EN 1399 There is no melting of the surface by cigarettes. Marks left on Marmoleum as a result of stubbed-out cigarettes can be removed							
	Slip resistance	DIN 51130	R9	R9	R9	R9	R9	
3	Electrical resistance Marmoleum Ohmex	EN 1081	-	$1-10^6 < R1 < 1-10^8 \Omega$ static dissipative	-	-	-	
	Acoustical impact sound reduction	EN-ISO 717-2	≤ 4 dB	≤ 5 dB	≤ 6 dB	≤ 18 dB	≤ 14 dB	
_ A	Life Cycle Assessment			LCA is the foundation	n for securing the lowest en	vironmental impact		
<u></u>	Creating Better Environments							
leum	Climate positive	Climate positive		Marmoleum 2.0mm and 2.5mm are produced climate positive (cradle to gate)**				
⊀	renewable electricity		Marmoleum is manufactured using 100% electricity from renewable sources					
	natural materials (e.g. linseed oil, jute, tree resin, wood flour, limestone) —		Marmoleum is made of 94-98% natural materials					
			Marmoleum contains PEFC certified wood flour					
			Marmoleum is free of PVC, PET, synthetic rubber and plasticizers					
Š	recycled conten	t	Marmoleum contains recycled content					
	Application on underfloor h	neating	yes	yes	yes	yes	yes	
	Marmoleum meets the requirements of EN 14041							
	Product code	EN 14041	0100201_DoP_306	0100201_DoP_306	0100201_DoP_306	0100207_DoP_306	0100206_DoP_3	
	Reaction to fire	EN 13501-1	C _{ff} -s1, G, CS	C _n -s1, G, CS***	C _n -s1, G, CS	C _n -s1, G, CS	C _n -s1, G, CS	
	Slip resistance	EN 13893	μ ≥ 0.30	μ ≥ 0.30	μ≥ 0.30	μ ≥ 0.30	μ≥ 0.30	
	Body voltage	EN 1815	≤ 2 kV	≤ 2 kV	≤ 2 kV	≤ 2 kV	≤ 2 kV	
kV 23	Thermal resistance	EN 12524	0.17 W/m·K	0.17 W/m-K	0.17 W/m·K	0.17 W/m·K	0.17 W/m·K	
····	Indoor Air Emissions:	EN 16516	< 0.05 mg/m ³	< 0.05 mg/m ³	< 0.05 mg/m ³	< 0.05 mg/m ³	< 0.05 mg/m ³	
	TVOC at 28 days Content of specific	EN 14041	Compliant,	Compliant,	Compliant,	Compliant,	Compliant,	
	dangerous substances	LIV ITOT I	not actively added	not actively added	not actively added	not actively added	not actively add	



^{**}For verification and details please consult our Marmoleum EPD.

Recommended adhesives: For the latest installation instructions and recommended adhesives

please visit www.forbo-flooring.co.uk/installation All Forbo Flooring Systems' sales organisations worldwide have a certified Quality Management

System in accordance with ISO 9001.

All Forbo Flooring Systems' manufacturing operations have a certified Environmental Management

System in accordance with ISO 14001.

The Life Cycle Assessment (LCA) of Forbo Flooring Systems' products is documented in individual Environmental Product Declarations (EPD's) which can be found on all of our websites. Marmoleum is manufactured in a facility certified to SA8000 and OHSAS 18001.



Whilst Forbo Flooring UK Limited does its best to ensure that the contents of this specification whist folior inclining of chimical does in best to enable that the contents of units specification are correct and accurate at the time of publication, to the fullest extent permitted by law, Forbo Flooring UK Limited makes no, and expressly disclaims all, guarantees of any kind, express or implied in respect of the information, content, materials or products displayed in this specification and does not represent that the information is accurate, complete or current.





For more information:

e: info.flooring.uk@forbo.com

t: **0800 121 4780**

w: forbo-flooring.co.uk/marbled



^{***}Marmoleum 2.5mm is available in reaction to fire classification $B_{\tilde{n}}$ s1, G, CS. Available on request, contact sales support for leadtime.