

# eurocol

# 049

the strong connection

5-4-2026



## EUROPRIMER ABS

Ready-to-use, strong impregnating primer to improve the adhesion of, among other things, levelling compounds and floor covering adhesives on absorbent gypsum and cement-based walls and floors, sheet material, etc. Suitable for indoor and outdoor use. Thanks to EMICODE EC 1PLUS (very low emission) also suitable for BREEAM projects.

### PRODUCT TYPING

Base	Acrylic dispersion.
Color	Pink.
Consistency	Thin liquid.

- Very low emission
- EMICODE EC 1PLUS
- User friendly
- Non-flammable
- Favourable spreading capacity
- High penetration capacity

### PROPERTIES

Classification	Emicode EC 1PLUS tested conform EN 13999-2/4.
Consumption	100 - 150 g/m <sup>2</sup> .*
Sensitive to frost	Good resistance after complete drying.
Specific weight	1.0 kg/l.

### APPLICATION

Primer for:

- improving the adhesion of levelling compounds on absorbent and stony subfloors
- improving the top-layer of absorbent and stony subfloors
- self-levelling anhydrite floors, that must be levelled and/or on which a floor covering must be applied.

### PROCESSING

Storage	Store free from frost. Protect against high temperatures.
Tools	Lambswool roller, brush or spray-gun.
Drying	1 - 2 hours.*

049 EUROPRIMER ABS

Shelf Life	12 months, in unopened packaging.
Cleaner	Water.

\* The stated values are laboratory values which, given the large variation in climatological conditions, subfloor compositions and layer thicknesses, are only guideline values.

#### Substrate:

- The subfloor must be moisture-absorbent and have a good tensile and compression strength. The subfloor should also be clean, permanently dry and free from grease, dirt and dust, according to the requirements of BS 8203 or DIN 18 365.
- For the requirements pertaining to calcium sulphate-bound cast floors we refer to the CUR recommendation [Cast floors with calcium sulphate as a binding agent] (Foundation CUR in Gouda), number 107.
- On very porous anhydrite subfloors we advice, to avoid the chance of an orange peel effect, to apply 2 coats of 044 Europrimer Multi or 1 coat of 043 Europrimer Alphy.
- In advance always seek our technical data sheets. In doubt about the application ask for technical advice.

#### Instruction manual:

- Apply 049 Europrimer ABS evenly and covered with a lambswool roller and/or brush.
- If required 049 Europrimer ABS can also be applied with a spray-gun.
- After drying the subfloor can be treated as required.
- Clean tools immediately after use with water.
- Remove fresh spots immediately with water.
- Avoid contact with eyes and skin and use suitable personal protection equipment (please refer to our safety sheet).
- Product residues and cleaning water drains according to local applicable environmental rules and do not drain in the sewer.

#### Working conditions:

Intended surrounding temperature : 15° - 23 °C.

Material and subfloor temperature : min. 10° - max 25 °C.

Relative humidity : 40 - 70%.

Contains methylchloroisothiazolinone and methylisothiazolinone (3:1). May produce an allergic reaction.

---

## QUALITY AND GUARANTEE

---




---

## ENVIRONMENT AND HEALTH

---

Hazard Class	None.
Safety and environment	Safety data sheets of Forbo Eurocol products according to EEG-guideline 91/155.
MSDS	Available on request.

---

## ITEM DATA

---

Article	Definition	Packaging	EAN-code
049	Europrimer ABS	10 kg jerry can	8 710345 049016

### 049 EUROPRIMER ABS