

FORBO MARMOLEUM TEXTURA TECHNICAL DATA

1. PRODUCT NAME & MANUFACTURER

1.1 Product:

Forbo Marmoleum Textura linoleum sheet resilient floor covering

1.2 Manufacturer:

Forbo Flooring Systems US 8 Maplewood Drive Hazleton, PA 18202 1-800-842-7839

Forbo Flooring Systems Canada 3983 Nashua Drive, Unit 1 Mississauga, ON L4V 1P3 1-800-268-8108 (English) 1-800-567-9268 (French)

topshield

www.forboflooringNA.com

1.3 Product Description:

Construction: Forbo Marmoleum Textura is a homogeneous floor covering made from natural ingredients including flax seed oil, rosin binders, wood flour, limestone and dry pigments which are mixed and then calendared onto a natural jute backing. After calendaring, a roll embosses a 3D pattern in the linoleum. Topshield is a high-performance finish. Its double UV cured double layer technology delivers extraordinary performance and clear and vibrant colors that remain over time. Topshield creates a 'ready to use' Marmoleum that requires no initial maintenance or polymer application. The surface can be repaired or refreshed in cases of accidents or after years of intensive use.

1.4 Physical Characteristics:

(dimensions are approximate)

Gauge	1/10" (2.5 mm)
Backing	Jute
Width	79" (2 meters)
Length	105' (32 meters)
Roll Size	77 yards ² (64 meters ²)

2. PRODUCT PERFORMANCE & TECHNICAL DATA

2.1 Reference Specification:

Meets or exceeds all technical requirements as set forth in ASTM F 2034 Standard Specification for Linoleum Sheet Flooring, Type I.

2.2 Environmental:

100% USDA Certified BioBased Product. Compliant with CDPH 01350 requirements for VOC emissions and indoor air quality. Forbo Marmoleum Textura contributes to LEED v4.1 credits. For additional information, contact Forbo Flooring Systems.

2.3 Flexibility:

Forbo Marmoleum Textura will not crack or break when bent around a 1.4" (3.5mm) diameter cylinder.

2.4 Static Load Limit:

Residual compression of 0.002" with 250 pounds per square inch when tested in accordance with ASTM F 970-17, Standard Test Method for Static Load Limit.

2.5 Slip Resistance:

Meets or exceeds the industry recommendation of >0.5 for flat surfaces when tested in accordance with ASTM D 2047, Standard Test Method for Static Coefficient of Friction.

2.6 Castor Resistance:

Suitable for office chairs with castors when tested in accordance with ISO 4918, Castor Chair Test.

2.7 Impact Sound Reduction:

6dB when tested in accordance with ISO 717-2, Impact Sound Insulation Test.

2.8 Resistance to Bacteria:

Provides a self-sanitizing quality in the form of a bactericidal effect. Independent testing has shown that a sterile zone around the material inhibits the growth of organisms such as staphylococcus aureus and Clostridium difficile.

2.9 Anti-Static Properties:

Naturally anti-static. This property makes cleaning easier because dirt and dust does not cling to the surface as it may with other materials.

2.10 Fire Testing:

Class 1 when tested in accordance with ASTM E 648/ NFPA 253, Standard Test Method for Critical Radiant Flux. Meets 450 or less when tested in accordance with ASTM E 662/ NFPA 258, Standard Test Method for Smoke Density.

Class C when tested in accordance with ASTM E 84/ NFPA 255, Standard Test Method for Surface Burning Characteristics.

FSR – 150; SDC – 145 when tested in accordance with CAN/ULC S102.2, Standard Test Method for Flame Spread Rating and Smoke Development of Flooring Materials. FSR – 165, SDC – 145 when tested in accordance with CAN/ULC S102, Standard Test Method for Flame Spread Rating and Smoke Development of Wall Materials.

2.11 Cigarette Resistance:

Resists cigarette burns. Burning cigarettes will leave only a brown mark, which can be rubbed out using steel wool or a scouring pad.



2.12 Chemical Resistance: (Exposure Time – 1h)*

(Exposure rime - rii)	
Acetic Acid (5%)	
Acetone	
Ammonia (5%)	No Effect
Betadine	
Bleach	
Brown or Black Hair Dye	
Brown or Black Shoe Polish	No Effect
Gasoline	No Effect
Gel Hand Sanitizer	No Effect
Hot Chili Paste	No Effect
Hydrochloric Acid (5%)	No Effect
Iodine S	light Color Change
Isopropyl Alcohol (70%)	No Effect
Kerosene	No Effect
Methylene Blue	No Effect
Mineral Oil	
Olive Oil	
Phenol (5%)	No Effect
Sodium Hydroxide (5%)	No Effect
Sodium Hypochlorite (5%)	No Effect
Sulfuric Acid (5%)	No Effect
Tested in accordance with ASTM F 925, Standard Test	
Method Resistance to Chemicals of Resilient Flooring.	
*Forbo Marmoleum Textura is NOT resistant to	
prolonged exposure to high alkalis.	
· · · ·	

3. INSTALLATION

3.1 Adhesive:

Use Forbo Sustain 1195, Forbo Sustain 100, Forbo L 885, or Forbo 660 adhesive.

3.2 Heat Welding Is Not Required:

Forbo Marmoweld ETU is a color-matched sealant used to complete the installation of Forbo Marmoleum in place of heat welding. To use, sparingly apply Forbo Marmoweld ETU to all seams on the floor with a 1" (2.54cm) putty knife or plastic applicator. Ensure there are no sharp or damaged edges on the applicator that might scratch or damage the Forbo Marmoleum. Wipe all excess Forbo Marmoweld ETU off the surface of the Forbo Marmoleum with a clean, damp white cloth.

3.3 Flash Coving (OPTIONAL):

Flash cove up walls to the desired height. Use Forbo Sustain 1195, Forbo Sustain 100, or Forbo L 885 adhesive.

3.4 Installation Guidelines:

Forbo does NOT recommend the application of adhesive tape on Marmoleum. Adhesive tape may cause damage to the factory coating of resilient flooring products. When using floor protection materials, tape the seams of the floor protection together and secure the floor protection by weighing down in corners and against walls. DO NOT secure floor protection materials by taping them directly to the surface of resilient floor coverings.

FLOORING SYSTEMS

Refer to Forbo's Installation Guidelines for complete installation recommendations.

4. WARRANTY

Limited 30-year warranty. For complete details, contact Forbo Flooring.

5. CARE & CLEANING

Refer to Forbo's Floor Care Guidelines for complete care recommendations.

