



Forbo Flooring Coral nv
Postbus 17
1560 AA KROMMENIE
Netherlands

Your notice of
17-11-2020

Your reference

Date
18-01-2021

Analysis Report 20.07046.04


Required tests :

EN 13501-1 (2019)

Sample id	Information given by the client	Date of receipt
T2024823	Coral Grip HD EV	17-11-2020

Kristina De Temmerman
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



Reference: T2024823 - Coral Grip HD EV

Information given by the client

Product standard	EN 13501-1 (2019)
Production batch/piece number	0001014778
Date of carpet finishing	26-10-2020
FR treated	yes
FR-surface treatment	no
Use-surface	PVC non-woven
Backing layer	Vinyl
Total mass	8100 g/m ²
Total thickness	17 mm
Surface structure	Loop pile

Notified body No: 0493

Reference: T2024823 - Coral Grip HD EV

Reaction to fire tests – Ignitability of building products subjected to direct impingement of flame - Single-flame source test

Date of ending the test 15-01-2021
Standard used EN ISO 11925-2 (2010)
Product standard EN 13501-1 (2019)

Floor covering

Deviation from the standard -

Conditioning 23°C, relative humidity 50%
Minimum 14 days or until constant mass is achieved

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Substrate Fibre cement board - density (1800 ± 200) kg/m³
Mounting Loose-laid

Specimens have not been cleaned

Flame application time (s) 15
Flame application Surface

	Length			Width		
	1	2	3	4	5	6
Time to reach 150 mm mark (s)	*	*	*	*	*	*

* = time to reach the mark > 20 s or mark not reached


Criteria Floorcoverings

time to reach the mark: - > 20 s : Class Efl
- ≤ 20 s : Class Ffl

Classification Class E_n

Limitations

This classification document does not represent type approval or certification of the product.



Reference: T2024823 - Coral Grip HD EV

Reaction to fire tests for floorings - Determination of the burning behaviour using a radiant heat source

Date of ending the test	14-01-2021
Standard used	EN ISO 9239-1 (2010)
Product standard	EN 13501-1 (2019)
Deviation from the standard	-
Conditioning	23°C, relative humidity 50% Minimum 14 days or until constant mass is achieved

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Test specimen

Substrate	Fibre cement board - density (1800 ± 200) kg/m ³
Mounting	Stuck down with Eurocol 640 with spatula A2
Specimens have not been cleaned	

Radiant heat flux

	Flame spread distance (cm)			Flame time	Heat flux * kW/m ²
	10 min	20 min	30 min		
Length					
#1	15	15	15	12 min 18 s	10.4
Width					
#1	16	16	16	12 min 32 s	10.2
#2	16	16	16	12 min 15 s	10.2
#3	15	15	15	12 min 16 s	10.4
Average					10.3

* Heat flux at the time of flame extinguishment or after a test duration of 30 minutes.

Fire classification in accordance with EN 13501-1 (2019)		
Class	EN ISO 11925-2 or CWFT	EN ISO 9239-1 (test duration = 30 min)
B _{fl}	E _{fl}	heat flux ≥ 8,0 kW/m ²
C _{fl}	E _{fl}	heat flux ≥ 4,5 kW/m ²
D _{fl}	E _{fl}	heat flux ≥ 3,0 kW/m ²

Smoke production: Light attenuation

	Maximum (%)	Total (%.min)
Length		
#1	60	323
Width		
#1	58	354
#2	59	360
#3	62	324
Average		346

Additional classification in accordance with EN 13501-1 (2019)	
smoke production ≤ 750%.min	s1
smoke production > 750%.min	s2



Reaction to fire classification : B_n/ s1
*Glued on a non-combustible substrate**

** End use substrates of classes A1 or A2-s1,d0 (EN 13238:2010 § 5.2.2)*

Limitations

This classification document does not represent type approval or certification of the product.