

eurocol

300

the strong connection



BASECOAT

Ready-to-use lacquer for applying a base coat on a 305 BetonDesign, 395 FloorDesign and 390 FloorColouring substrate as an impregnation layer and adhesion improver for the 310 FinishCoat. Shake the closed bottle well for at least 1 minute before use.

PRODUCT TYPING

Base	Acrylate Copolymer.
Color	Milky white.
Consistency	Thin liquid.

- Ready for use
- Easy to process
- Impregnating property
- Adhesion enhancer
- Solvent-free
- Neutral smell

PROPERTIES

Consumption	100 – 120 g/m ² per coat.
Flammability	Non-flammable.
Sensitive to frost	Yes.
Specific weight	1.04 kg/l.

APPLICATION

For applying a base coat to BetonDesign and FloorDesign base to impregnate and enhance adhesion for the 310 FinishCoat.

PROCESSING

Storage	Store in a cool, frostproof place (between 5 – 25 °C).
Tools	Paint roller type microfiber 9 mm.
Drying	At least 2 hours, finish within 24 hours with 310 FinishCoat.
Shelf Life	12 months, in unopened packaging.
Cleaner	Water.

** The stated values are laboratory values which, given the large variation in climatological conditions, subfloor compositions and layer thicknesses, are only guideline values.*

Substrate:

300 BASECOAT

- The 305 BetonDesign and 395 FloorDesign must have been created in accordance with the steps described in the instruction manual. The surface must be clean, consistently dry, and free from grease, dirt and dust.

Instruction manual:

- Shake well (minimum 1 minute) before use.
- When applying the product to the floor wear shoe covers to prevent foot prints.
- 300 BaseCoat is applied by means of a 9 mm microfiber paint roller. This coat has impregnating capacity and ensures proper adhesion of the 310 FinishCoat.
- The coating must be applied evenly and without pressure across the entire surface. We advise that you roll the coating in every direction.
- After a drying time of at least 2 hours, yet no more than 24 hours, the 310 FinishCoat must be applied also by means of a 9 mm microfiber paint roller. Allow a minimum drying time of 12 hours.
- It takes approximately 8 days for the finishing coat to become resistant. Thus it is important that within these 8 days the floor does not get stained and/or damp, as this may lead to a damaged finishing.
- Fresh product stains should always be removed with water immediately.
- Always consult our technical production information sheets first. When in doubt about the use of the product, please contact our Technical Help Desk.
- Product residues and cleaning water drains according to local applicable environmental rules and do not drain in the sewer.
- Avoid contact with eyes and skin and use proper protecting equipment (see our safety sheet).

Contains methylchloroisothiazolinone and methylisothiazolinone (3:1). May cause an allergic reaction.

Conditions for processing:

Desired room temperature : 18 - 23 °C

Temperature for material and subfloor : min. 15° – max. 20 °C

Relative humidity : 40 - 70%.

ENVIRONMENT AND HEALTH

Hazard Class	None.
Safety and environment	Safety data sheets of Forbo Eurocol products according to EEG-guideline 91/155.
MSDS	Available on request.

ITEM DATA

Article	Definition	Packaging	EAN-code
300	BaseCoat	1 kg bottle	8 710345 300131
300	BaseCoat	Box of 12 bottles of 1 kg	8 710345 300124



Package 1kg

300 BASECOAT