













## Technical specifications

Flotex meets the requirements of EN 1307

## Flotex FR

## Flotex vision FR

	Total thickness	ISO 1765	3.3 mm
	Roll width	EN-ISO 24341	200 cm
	Roll length	EN-ISO 24341	30 m
	Total weight	ISO 8543	1225 g/m²
	Pile installation weight		250 g/m²
	Pile thickness	ISO 1766	Approx 2 mm
	Pile material		100% polyamide
	Dimensional stability	ISO 2551	≤ 0.20%
	Light fastness	EN-ISO 105/B02	≥ 6
	Electrical resistance	ISO 10965	≥ 10⁹ Ω
	Impact noise reduction	EN-ISO 717-2	Δ Lw ≥ 22 dB
	Area of use		Heavy Use
	Tested flammability standards	EN 45545-2	HL2*
		BS6853	1b
		ASTM E.648 ASTM E.662	Class 1 Pass
	Slip resistance	EN 13893	μ ≥ 0.30
	Body voltage	ISO 6356	< 2 kV
	Thermal resistance	EN 12667	0.04 m²K/W

\*EN45545-2 testing has been carried out on different substrates/adhesives. This is the highest achieving result.  
For a full overview of specific results on aluminium and plywood subfloors please ask.

Forbo Flooring Systems does its best to ensure that the contents of these technical documents are accurate at the time of publication.  
However for up to date technical specifications please refer to our website at: [www.forbo-flooring.com/transport](http://www.forbo-flooring.com/transport)

