



















# Technical specifications

Allura decibel meets the requirements of EN 651

		Allura Decibel 0,35	Allura Decibel 0,8
	Total thickness	EN-ISO 24346 3,15 mm	4,00 mm
	Wearlayer thickness	EN-ISO 24340 0,35 mm	0,80 mm
	Collection size	30	30
	Domestic use	EN-ISO 10874 23	23
 	Commercial/light industrial use	EN-ISO 10874 32	34 / 42
	Tile size	EN-ISO 24342 50 x 50 cm / 100 x 100 cm	50 x 50 cm / 100 x 100 cm
	Plank size	EN-ISO 24342 100 x 16,6 cm / 100 x 20 cm / 120 x 20 cm	100 x 16,6 cm / 100 x 20 cm / 120 x 20 cm
	Packaging per carton tiles	50 x 50 cm: 20 per box (5m <sup>2</sup> ) 100 x 100 cm: on request	50 x 50 cm: 16 per box (4m <sup>2</sup> ) 100 x 100 cm: on request
	Packaging per carton planks	100 x 16,6 cm: 30 per box (4,98m <sup>2</sup> ) 100 x 20 cm: 27 per box (5,40m <sup>2</sup> ) 120 x 20 cm: 19 per box (4,56m <sup>2</sup> )	100 x 16,6 cm: 24 per box (3,98m <sup>2</sup> ) 100 x 20 cm: 22 per box (4,40m <sup>2</sup> ) 120 x 20 cm: 16 per box (3,84m <sup>2</sup> )
	Total weight	ISO 23997 2300 g/m <sup>2</sup>	3600 g/m <sup>2</sup>
	Castor chair continuous use	ISO 4918 Yes	Yes
	Slip resistance	DIN 51130 R9 / R10*	R9 / R10*
	Acoustical impact noise reduction	EN-ISO 717-2 19dB	19dB
	Residual indentation typical value	ISO 24343-1 ≤ 0,20 mm ~0,12 mm	≤ 0,20 mm ~0,11 mm
	Light fastness	ISO 105-B02 ≥6	≥6
	Indoor Air Emissions: TVOC after 28 days	EN 16516 < 0,01 mg/m <sup>3</sup>	< 0,05 mg/m <sup>3</sup>
	Resistance to chemicals	EN-ISO 26987 Good	Good
	Dimension stability (after exp. to heat)	EN-ISO 23999 ≤ 0,05%	≤ 0,05%
	Surface treatment	Overclean	Overclean XL
	Allura meets the requirements of EN 14041	EN 14041 <b>CE</b> 0200879-DoP-908	EN 14041 <b>CE</b> 0200880-DoP-908
	Reaction to fire	EN 13501 C <sub>s</sub> -s1, L, CS	C <sub>s</sub> -s1, L, CS
	Slip resistance	EN 13893 μ > 0,30	μ > 0,30
	Thermal conductivity	EN 12524 0,25 W/mK	0,25 W/mK
	Body voltage	EN 1815 < 2kV	< 2kV

\* R10 for wood embossing

All Forbo Flooring Systems' sales organisations worldwide have a certified Quality Management System in accordance with ISO 9001.  
All Forbo Flooring Systems' manufacturing operations have a certified Environmental Management System in accordance with ISO 14001.



## Poland

Forbo Flooring Polska  
ul. Jeleniogórska 16  
60-179 Poznań  
T: +48 (61) 862 13 82  
F: +48 (61) 622 71 75  
info.pl@forbo.com  
www.forbo-flooring.pl

## Portugal

Forbo-Revestimentos, SA  
Zona Industrial da Maia I, Sector VII  
Tv. Eng. Nobre da Costa, 87  
Apartado 6091  
4476-908 Maia  
T: +351 229 996 900  
F: +351 229 996 909  
info.revestimentos@forbo.com  
www.forbo-flooring.com.pt

## Norway

Forbo Flooring AS  
Hagaløkkveien 7  
1383 Asker  
T: 66 77 12 00  
F: 66 77 12 40  
info.norway@forbo.com  
www.forbo-flooring.no

## Schweiz

Forbo - Giubiasco SA  
Via Industrie 16  
CH-6512 Giubiasco  
T: +41-(0) 91 - 850 01 11  
F: +41-(0) 91 - 850 01 41  
customerservice.ch@forbo.com  
www.forbo-flooring.ch

## Belgium

Forbo Flooring  
't Hofveld 4B 001  
1702 Groot-Bijgaarden  
T: + 32 2 464 10 10  
F: +32 2 464 10 11  
info.belgium@forbo.com  
www.forbo-flooring.be

## Other countries

Forbo Flooring B.V.  
P.O. Box 13  
1560 AA Krommenie  
The Netherlands  
T: +31 75 647 74 77  
F: +31 75 647 77 01  
contact@forbo.com  
www.forbo-flooring.com

Find us on



creating better environments

FLOORING SYSTEMS