



## Technical specifications

Onyx impact meets the requirements of EN 15102 and EN 233

|                                                                                    |                                          |              |                          |
|------------------------------------------------------------------------------------|------------------------------------------|--------------|--------------------------|
|   | Total thickness                          | EN ISO 24346 | 1,50 mm                  |
|   | Thickness wear layer                     | EN ISO 24340 | 0,10 mm                  |
|                                                                                    | Surface finish                           |              | PUR                      |
|   | Collection size                          |              | 6                        |
|   | Roll width                               | EN ISO 24341 | 2,0 m                    |
|   | Roll length                              | EN ISO 24341 | 21 m                     |
|   | Total weight                             | EN ISO 23997 | 2500 g/m <sup>2</sup>    |
|   | Dimensional stability                    | EN ISO 23999 | ≤ 0,4 %                  |
|   | Light fastness                           | ISO 105-B02  | ≥ 6                      |
|   | Resistance to chemicals                  | EN ISO 26987 | good                     |
|   | Impact resistance                        | EN 235       | resistant to impact      |
|   | Indoor Air Emissions: TVOC after 28 days | ISO 16000-6  | ≤ 0,01 mg/m <sup>3</sup> |
|   | Bacteria and fungi resistance            | ISO 846      | does not favour growth   |
|                                                                                    | Cleanroom particle emission              | ISO 14644-1  | ISO 3                    |
|   | Washability                              | EN 233       | washable and scrubbable  |
|   | Recycled content                         |              | ≥ 20%                    |
| Onyx impact meets the requirements of EN 15102                                     |                                          |              |                          |
|  | Reaction to fire                         | EN 13501-1   | B-s2,d0                  |

