## AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

## **TEST REPORT**

Client: Forbo Flooring Systems Pty Ltd

23 Ormsby Place

Wetherill Park NSW 2164

Test Number :

19-005372

**Issue Date Print Date** 

17/09/2019

9/01/2020 9/01/2020

Mean

Clients Ref: "Tessera Teviot" **Sample Description** 

Nominal Thickness:

Loop pile carpet tiles with non woven backing

Nominal Composition: 100% Solution dyed polyamide (Nylon 6)

2.8mm

Nominal Mass per Unit Area/Density:

3835q/m2

AS/ISO 9239.1-2003

Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a **Radiant Heat Source** 

Date of Sample Arrival

**Date Tested** 08/01/2020

**CHF Value** 1 2 3 Mean Length 6.5 kW/m² Width 5.1 5.1 5.1 5.1 kW/m² HF-30 Value 2 3 Mean 1

Length kW/m² Width 5.1 kW/m² 5.1

Smoke Value 2 3 Length 109 %.min Width 252 106 84 147 %.min

Melting Yes

1

190540 39113 Page 1 of 2

Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing - Chemical Testing - Mechanical Testing

: Accreditation No.

983



Samples and their identifying descriptions have been provided by the client unless otherwise stated.

Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test

relate only to the sample or samples tested. This document shall not be reproduced except in full and

APPROVED SIGNATORY

A. JACKSON B.Sc.(Hons)

## AWTA Product Testing

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

## **TEST REPORT**

Client: Forbo Flooring Systems Pty Ltd

23 Ormsby Place

Wetherill Park NSW 2164

Test Number : 19-005372 **Issue Date** 

9/01/2020

**Print Date** 9/01/2020

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Results in accordance with section 8.4 have not been included in the report. They are available upon request.

HF30 not reported as flame out time occurred before 30 minutes.

Each specimen was adhered to a substrate of 6mm thick fibre reinforced board using Eurocol 540 adhesive and clamped prior to testing

190540

39113

Page 2 of 2

983





Accredited for compliance with ISO/IEC 17025 - Testing - Chemical Testing - Mechanical Testing

: Accreditation No.

Samples and their identifying descriptions have been provided by the client unless otherwise stated.

Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test

relate only to the sample or samples tested. This document shall not be reproduced except in full and

A. JACKSON B.Sc.(Hons)

APPROVED SIGNATORY