

Installation Guidance Note: Flotex tiles and planks

General Advice

The appearance, performance and durability of the installed floorcovering will be determined to a large extent by the quality of the prepared subfloor and the conditions in which they are laid.

The installation of Flotex tiles and planks should be carried out in accordance with the national code of practice for the installation of resilient floor coverings if applicable. Areas to receive flooring should be clean, free from other trades, fully enclosed and weather tight. Subfloors should be clean, smooth, sound and permanently dry.

The drying time of tackifiers and open time open time of permanent bond adhesives will depend on site conditions and porosity of the base. It is best practice to conduct an adhesive bond test before starting the installation. Bond testing will assist in identifying both the working characteristics of the adhesive (waiting and working time) for the site conditions, and also any potential bonding problems.

Always conduct moisture tests on **all** substrates. All ground based level floors should have an effective moisture barrier.

Problems associated with plasticizer migration from PVC materials can lead to dimensional instability in Flotex tiles and planks. All subfloors of this type must be removed before installation.

It is impossible to ensure that wood block floors are not loose or contain latent defects through aging. It is therefore strongly recommended that these are removed and that the subfloor is correctly prepared and, if necessary, a surface damp proof membrane or an asphalt screed applied before installation of Flotex tiles and planks.

Raised access flooring panels have a tendency to settle shortly after installation and this should be taken into account when assessing the appearance of the Flotex tile/plank installation fitted onto such flooring systems. Ridges between uneven raised access floor panels will telegraph through to the finished tile installation. Uneven or loose floor panels should be levelled or re-fixed before installing Flotex tiles or planks.

Areas to receive flooring shall be adequately lit to allow for proper inspection of the substrate, installation and for final inspection.

It is essential that the laying area is at a steady temperature of 17°C for 48 hours prior to, during, and for 48 hours after installation. Prior to installation, the Flotex tiles and planks must be allowed to acclimatise in opened boxes for at least 48 hours in the above conditions. This is particularly important if the tiles/planks have been stored or delivered in conditions of extreme temperature and/or humidity. Where national codes of practice exist they take precedence over these guidelines.

As with any floor covering, the use of different production batches will always result in visible shade differences. It is essential that different batches are not mixed in the same area. When ordering tiles/planks, each floor area (plus spares) must be specified from the same batch. The batch number is clearly marked on the packaging and on the reverse side of each Flotex tile or plank and must be checked before commencement of installation.

Boxes should be checked to ensure that the correct tile type, colour, batch number and quantity have been received and that the tiles/planks are in good condition. No claim will be accepted for incorrect colour, pattern or obvious damage if the tiles/planks have been fitted.

Adhesive Recommendations and application

Flotex tiles and Planks must be adhered using a high grab, all-over tackifier adhesive system; Forbo Eurocol 542 Eurofix Tack Plus is recommended. If alternative products are to be used consult with the supplier for more information, guidance and warranty.

Forbo Flooring Systems does not recommend the installation of Flotex Tiles & Planks over an underlay. Installation over an underlay will invalidate the product warranty.

The tackifier adhesive must be spread evenly over the entire floor area with particular attention to edges – this will ensure any perimeter tiles/planks cuts are fully bonded. Failure to fully bond all full tiles/planks and tiles/planks cuts may result in individual tiles shifting and lifting.

Where perimeter tiles/planks are not constrained by fixtures e.g. walls, edge strips etc., it is recommended that such tiles/planks are adhered using a permanent adhesive; Forbo Eurocol 640 Eurostar Special is recommended.

In most applications Forbo Eurocol 542 tackifier adhesive will be sufficient heavy commercial usage areas, however, where tiles or planks are liable to be subject to heavy static or dynamic loads they should be fully adhered using Forbo Eurocol 640 Eurostar Special.

Adhesives must be applied according to the manufacturer's instructions and it is essential that tackifier adhesives are allowed to dry to a clear, tacky finish before laying the Flotex tiles/planks. Failure to do so could result in a permanent non-release bond.

Note: the tackifier must be applied with a suitable short pile roller to ensure full contact of the tile/plank backing with the adhesive.

If alternative adhesives are to be used consult with the supplier for usage information, guidance and warranty.

Note: adhesive coverage rates will be reduced on very porous subfloors such as plywood or sand cement screeds.

Always clean away excess adhesive with a damp cloth before it is allowed to dry.

Do **NOT** use bleaching agents or strong solvents as they can be harmful to both people and to your floor.

Underfloor heating

Forbo flooring products may be installed over underfloor heated floors providing the maximum surface temperature of the substrate does not exceed 27°C under any condition of use. To enable a secure bond of the adhesive to the substrate, the underfloor heating system should be turned off, or set to the lowest temperature, for a minimum of 48 hours prior to installation of the Forbo flooring material. The temperature of the substrate must not exceed 18 °C during the installation of the flooring material. If necessary, an alternate heating source should be used to maintain the room temperature at a minimum of 18°C prior to, during, and for 72 hours after installation. The temperature of the underfloor heating system can be increased 72 hours following the installation. When raising the floor temperature, do so gradually so the substrate and flooring material can adapt to the temperature change together. A rapid temperature change could result in bonding problems.

Installation

The following instructions are intended to draw the fitter's attention to current "Best Practice", and must be followed for the relevant product guarantees to be valid. Installation must be carried out in accordance with the requirements of this guidance along with local codes of practice where applicable.

Conditioning

Prior to installation, the Flotex tiles/planks must be allowed to acclimatise in opened boxes in the laying area at a steady temperature of 18 to 27°C, no more than six boxes high, for at least 24 hours. This is particularly important if the tiles/planks have been stored or delivered in conditions of extreme temperature and/or humidity.

Setting Out

The location of the starting point in an installation is usually determined by the fitter to maximize the yield. This may be anywhere in the room, but would normally be located as near to the true centre as possible.

Having established the starting point for the installation, making some check measurements or dry laying a few rows of tiles/planks will help to identify any potential problems or necessary adjustments to avoid small perimeter cuts.



FLOORING SYSTEMS

Pile Direction

The arrow marks on the reverse of every tile/plank indicate the direction of pile lay. The preference of the specifier as to monolithic*, tessellated or other visual effects must be confirmed before tiles/planks are installed.

When laying tile or planks in a monolithic format follow the direction of the arrows, which should, where possible, point towards the main light source**.

Options for the direction of tile and plank installation will vary between product designs. The installation options are indicated on product sample books and below, but if there is any doubt check with Forbo Flooring prior to installation.

***Note:** the term 'broadloom' is often used as an alternative description of monolithic. Whichever term is used, it refers to the installation direction of the tiles/planks. It does not mean that the installation will be viewed as seamless.

****Note:** To prevent potential problems of deviation of wheeled traffic travelling across the dense pile of Flotex; it is strongly recommended that tiles and planks are laid with the pile running lengthways in the main direction of traffic when fitting in monolithic format. We suggest that with other installation formats, some tiles/planks are dry laid to decide upon the optimum direction to suit the specific location requirements.

Cutting and Fitting

Flotex tiles and planks can be easily cut using a utility knife. Tiles and planks must be laid butt jointed, fitted tightly and cut accurately at perimeters.

On completion of the installation

First impressions may have more impact on the client than hours of skilled fitting.

The completed installation should be cleared of scrap material and debris, the floor vacuumed and any traces of adhesive residues removed from the floor and skirtings.


Note: Upright vacuum cleaners with an electrically powered brush should be used on all Flotex tiles and planks.

If the floor covering is to be protected from other trades or site traffic prior to project completion, a protection product should be chosen that is appropriate for the type and level of traffic likely to be experienced.


If the optimum performance of any new floor covering is to be achieved, it is important that the correct cleaning and maintenance procedures are used from day one. Cleaning and maintenance guides for all Forbo Flooring Flotex ranges are available for download at: www.forbo-flooring.com/floorcare

Cleaning and maintenance guides should be passed onto the main contractor, client or end user as appropriate on completion of the installation, and before any hand over clean is started.


Flotex tile installation options:




Tessellated



Monolithic/Broadloom



Brick




Half drop




FLOORING SYSTEMS

Flotex Tile Range	Recommended laying options
Flotex Colour	broadloom, tessellated, brick and half drop
Flotex Advance	broadloom, tessellated, brick and half drop


Flotex Plank installation options




Brick installation-1




Brick installation-2




Double herringbone installation-1




Double herringbone installation-2




Herringbone installation-1



Herringbone installation-2



Weave installation-1



Weave installation-2

All designs of the Flotex planks collection can be installed in all these directions.

Please note that for each installation method above we have shown two images of each method with arrows pointing in different directions. It does not matter in which direction the design is installed but it is important that once an installation method has been chosen all planks get installed in the same direction.

Flotex Plank Range

Seagrass, Wood, Concrete, Ombré, Montage, Converge, Converge plain, Sierra, Travertine, Neo-Concrete, Intersect, Serif, Panama, Calico

Flotex planks feature a random design and should be installed in a fully random layout. Do not attempt to sort or preselect planks, as variation is intentional and essential to achieve the desired visual effect.

If in any doubt contact us:

question@forbo.com



FLOORING SYSTEMS