

644 Multi Plus

FIBER-REINFORCED ADHESIVE

PRODUCT DESCRIPTION

High quality, fiber-reinforced, strong, dispersion-based adhesive with long open time, which achieves a very high final strength. Consumption-optimized. Recommended for improving the dimensional stability and indentation behavior of bonded floor coverings.

The adhesive is suitable for bonding of rubber floor coverings in sheets with sanded backing (e.g. Noraplan) as well as in tiles up to 1 m x 1 m, up to 4 mm thickness (e.g. Norament), for LVTs, vinyl- and CV- floor coverings in sheets and tiles, vinyl composite floor coverings, textile floor coverings with different backings, needle felt, linoleum in sheets and in tiles (e.g. Modular), as well for approved Eurocol insulating underlays on absorbent subfloors conforming to standards.

Suitable over underfloor heating systems and castor wheel resistant according to DIN EN 12529. Suitable for shampooing according to RAL 991 A2.

For indoor use only.

Very low VOC emission. EMICODE EC 1 Plus, GISCODE D 1,



PRODUCT FEATURES

- high initial power, short flash-off time
- very easy to spread
- very versatile applicable
- solvent free
- optimizes the impression behavior of coverings in the early phase after bonding
- suitable for chair castors and for use on underfloor heating
- 10 - 15 % lower consumption, thus lower m² costs
- easy to apply, even on large surfaces
- short flash-off time, thus fast and effective working
- fast strength build-up, reduced "floating" and faster walkability
- extended insertion time, also for angled rooms
- optimized thermal stability

TECHNICAL DATA

Base	acrylate dispersion, filler, thickener, wetting agent, defoaming agent, water, preservative
Colour	white
Density	approx 1,12 g/cm ³
Consistency	paste-like, medium viscosity
Cleaning agent	water
Processing conditions	not below 15 °C on the subfloor, minimum 18°C material- and room temperature 35-75% relative air moisture, recommended <65%
Mode of application	spatula TKB/A1 – A1 - A2 – B1 – B2
Consumption	approx. 190 - 390 g/m ² , depending on floor covering and spatula

644

Eurostar Multi Plus

Drying time	approx. 5 - 10 minutes, depending on floor covering
Installation time	approx 40 minutes, depending on floor covering
Curing time	approx 24 - 48 hrs
Permitted shelf-life	within approx. 15 months, opened packaging to be tightly closed and to be consumed as soon as possible
Storage condition	packaging to be tightly closed at a dry place, temperature: 5 - 30 °C,
Frost sensitivity	yes
Code acc. to GHS	none
Under-floor heating systems	suitable, maximum temperature on top 29 °C
Environment/Work safety	GISCODE: D 1 EMICODE: EC 1 Plus DIBt: Z-155.20-208 DGNB: VOC 0 %, quality level: 1 LEED: VPC 0 g/l Contains 1,2-benzisothiazol-3(2H)-one, reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one and 2-methyl-2H-isothiazol-3-one (3:1). May produce an allergic reaction.

FLOOR PREPARATION

The subfloor must meet the requirements according to national standards, regulations and norms. The subfloor must have a sufficient compression and tensile strength, load-bearing capacity, dimensional stability, dry, crack and dust free and free of any contaminants which will impact bonding and it must be even acc. To DIN 18202 German standards. Defective subfloors shall be treated by taking appropriate measures e.g. grinding, priming or applying Eurocol self-levelling compound. In the event of any discrepancy, the installer must always inform the client of his concerns in writing. Cracks or joints (except for building expansion joints) must be closed with suitable Eurocol product (913 Europlan Silicat). The laying materials to be used must satisfy in accordance to the subfloor and its intended use.

APPLICATION

Stir well before use!
Adhesive must be applied equally on the subfloor (full area bonding) with a full-length spatula. Avoid puddles!
Spread the adhesive evenly with a spatula over an area of subfloor that can be covered whilst the adhesive remains receptive and gives good transfer.
Worn-out spatulas need to be replaced in time in order to guarantee the minimum adhesive consumption.

Rubber (TKB A2) and **Linoleum** (TKB B1) to be laid into the wet adhesive airing time 10 - 15 minutes. The airing time depends on the moisture content and the absorbency of the sub-floor, an exact time for airing is for this reason not possible. The adhesive must have a soft centre, making a finger test the adhesive must be tacky, edgings to be pushed into place and not pressed exactly.

PVC and Design Coverings (TKB A2) are to be laid within 30 minutes well pressed and rolled.

Vinyl Flooring the toothed spatula size can be reduced A1. Thus, reducing the airing time.

Carpet and Needle Felt (TKB B1-B2) are to be laid within 30 Min well pressed and rolled.

Please avoid direct sunlight and point pressure. Any spillages should be cleaned away with clean water.

Afterwards install the floor covering and rub it down well. Roll with an articulated floor roller afterwards.
Rubber floor covering needs to be installed into the wet adhesive.
Make sure that the adhesive remains receptive and gives good transfer, otherwise the airing time should be slightly extended.
Rub the floor covering down well, repeat the rubbing down after 20 - 30 minutes.
During the setting phase, the direct influence of heat/solar radiation as well as dynamic and point loads must be avoided.

644

Eurostar Multi Plus

NOTES

Please pay attention to the technical data sheet issued by the floor covering manufacturer.
Relevant norms and regulations of the branch are to be respected.
Outside Germany relevant national regulations are to be applied which must be known by the user
Allow the floor covering to be acclimatized before laying. The laying materials must be relaxed and plane.
Welding / grouting the flooring at the earliest on the next day.

PACKAGING

12 kg nonreturnable package (44 buckets/ pallet)

SPECIAL NOTE

Any application method/ conditions other than specified in this Technical data sheet require explicit manufacturer's approval. In case of deviance in application method/ conditions liability by manufacturer cannot be guaranteed.

This technical data sheet contains advice on handling and application of the product, based on experience and tests run by the manufacturer in laboratory and practical work.

The information supplied by the manufacturer are non-binding and cannot be used as a basis for establishing the manufacturers liability for any damages caused. The values stated in this technical data sheet were measured under standard laboratory conditions. As application conditions outside the laboratory vary strongly this technical data sheet must be considered a guide only. Therefore the manufacturer does not take liability for damages caused by the customer's utilization of the technical data sheet content.

As the usage, processing- and storage conditions on site are beyond the manufacturers influence, a warranty for the processing result cannot be given. This also includes the infringement of any rights for the protection of third parties. Sufficient testing areas are to be provided before final application. Relevant national norms and regulations of the industry are to be observed. Outside Germany valid, relevant national norms and regulations, have to be taken into account and to follow by the customer. It is the responsibility of the customer to check product suitability for the intended procedure and purposes prior to use. This Technical Information supersedes all previously issued application data sheets and product information are no longer valid!

Technical information and Material Safety Data Sheets of concomitantly used installation materials must be followed carefully.

The products delivered by the manufacturer are for professional use only. Keep away from children.
The manufacturer's terms and conditions are binding

Last updated 2020-07-09
Supersedes issue as of 2020-02-21

Version Nr.: 04
BG132644_644-005