


eurocol

813

the strong connection



EUROFLOOR FORCE FIBRE

Reinforcing scrims, for load distribution, before levelling work, the fibre scrims are separated into individual fibres and which additionally reinforce the levelling compound.

PRODUCT TYPING

Base	Fibreglass.
Format	Length 50 m. Width 0,97 mm.

- Special fibre reinforcement, in sheets, for use on unstable substrates and for bridging dry shrinkage cracks in selflevelling compounds.
- Especially suitable for screeds in need of renovation.
- Non-rotting.
- Moisture resistant.

PROPERTIES

Flammability	Non-flammable.
Frost resistance	yes.

APPLICATION

For use on unstable substrates and for bridging dry shrinkage cracks

PROCESSING

Storage	Store cool and dry in unopened packaging.
Shelf Life	Minimum 72 Months, in unopened packaging.
Remarks	Technical information and safety data sheets of other laying materials must be observed!
	Do not use in combination with fibre levelling compounds.

** The stated values are laboratory values which, given the large variation in climatological conditions, subfloor compositions and layer thicknesses, are only guideline values.*

Substrate:

- The subfloor must be prepared professionally according to the conditions, so that with levelling and filling work can be started.
- A system-compliant primer is applied, as far as the connection with the selected levelling compound is necessary.

Instruction manual:

- Reinforcing scrims should be rolled out and cut off in one direction of travel, overlapping.
- Pouring in the levelling compound must be carried out in such a way that the direction of flow overflows the overlap of the scrim and does not flow under the reinforcing scrim.

813 EUROFLOOR FORCE FIBRE

- When wetted with the mixing water, the fibre binder dissolves very quickly and the special fibres are distributed within the liquid levelling compound. The fibres are completely bound over the entire cross-section of the filler and thus provide excellent reinforcement of the system.

Attention - only deaerate the levelling compound, under no circumstances squeegee, otherwise the fibres will be combed out of the liquid compound!

The self-levelling filler must be applied in a minimum layer thickness of 5 - 8 mm.

If necessary, especially with thin smooth coverings, fine adjustment of the surface or fine sanding can be carried out.

Processing conditions:

at least 15 °C floor temperature,
at least 18°C material and room temperature,
35-75% relative humidity, recommended <65%

ENVIRONMENT AND HEALTH

Safety and environment Keep out of reach of children. Do not eat, drink or smoke while processing the product. Only give completely empty containers for recycling. Material residues can be disposed of as household waste.

ITEM DATA

artikel	productname	packaging	shipping unit
813	Eurofloor Force Fibre	roll à (50*0,97) m	28 rolls/pallet

Any application method/ conditions other than specified in this Technical data sheet require explicit manufacturer's approval. In case of deviance in application method/ conditions liability by manufacturer cannot be guaranteed. This technical data sheet contains advice on handling and application of the product, based on experience and tests run by the manufacturer in laboratory and practical work. The information supplied by the manufacturer are non-binding and cannot be used as a basis for establishing the manufacturers liability for any damages caused. The values stated in this technical data sheet were measured under standard laboratory conditions. As application conditions outside the laboratory vary strongly this technical data sheet must be considered a guide only. Therefore the manufacturer does not take liability for damages caused by the customer's utilization of the technical data sheet content. As use, processing- and storage conditions on site are beyond manufacturers influence, a warranty for the processing result cannot be given. This also includes the infringement of any rights for the protection of third parties. Sufficient testing areas are to be provided before final application. Relevant national norms and regulations of the industry are to be observed. Outside Germany valid, relevant national norms and regulations, have to be taken into account and to be followed by the customer. It is the responsibility of the customer to check product suitability for the intended procedure and purposes prior to use.

This Technical Information supersedes all previously issued application data sheets and product information are no longer valid!

BG144513, Version 02, Stand 2019-06-06, ersetzt Ausgabe vom 2014-08-19.

813 EUROFLOOR FORCE FIBRE