

Prüfbericht-Nr.: <i>Test Report No.:</i>	89212164.06br	Auftrags-Nr.: <i>Order No.:</i>	154951	Seite 1 von 14 Page 1 of 14
Kunden-Referenz-Nr.: <i>Client Reference No.:</i>	N/A	Auftragsdatum: <i>Order date:</i>	07.08.2017	
Auftraggeber: <i>Client:</i>	Forbo Novilon, De Holwert 12, 7741 KC COEVORDEN, The Netherlands			
Prüfgegenstand: <i>Test item:</i>	Resilient flooring			
Bezeichnung / Typ-Nr.: <i>Identification / Type No.:</i>	Allura 0.7			
Auftrags-Inhalt: <i>Order content:</i>	Determination of burning behaviour			
Prüfgrundlage: <i>Test specification:</i>	EN 13501-1:2007+ A1:2009 Classification of burning behaviour Test methods: Ignitability of products subjected to direct impingement of flame (EN ISO 11925-2:2010/C1:2011) and determination of the burning behaviour using a radiant heat source (EN ISO 9239-1:2010)			
Wareneingangsdatum: <i>Date of receipt:</i>	21.09.2017			
Prüfmuster-Nr.: <i>Test sample No.:</i>	MT17-154951.07			
Prüfzeitraum: <i>Testing period:</i>	21.09.2017 – 28.09.2017			
Ort der Prüfung: <i>Place of testing:</i>	Westervoortsedijk 73, 6827 AV Arnhem, Netherlands			
Prüflaboratorium: <i>Testing laboratory:</i>	TÜV Rheinland Nederland B.V.			
Prüfergebnis*: <i>Test result*:</i>	Siehe Sonstiges / See Other			
geprüft von / tested by:		kontrolliert von / reviewed by:		
02.10.2017	M.A. van de Vlekkert	02.10.2017	J. de Wolff	
Datum <i>Date</i>	Name / Stellung <i>Name / Position</i>	Unterschrift <i>Signature</i>	Datum <i>Date</i>	Name / Stellung <i>Name / Position</i>
Sonstiges / Other: Test result: See clause 4 on page 6.				
Zustand des Prüfgegenstandes bei Anlieferung: <i>Condition of the test item at delivery:</i>		Prüfmuster vollständig und unbeschädigt <i>Test item complete and undamaged</i>		
* Legende: 1 = sehr gut 2 = gut 3 = befriedigend 4 = ausreichend 5 = mangelhaft P(ass) = entspricht o.g. Prüfgrundlage(n) F(ail) = entspricht nicht o.g. Prüfgrundlage(n) N/A = nicht anwendbar N/T = nicht getestet Legend: 1 = very good 2 = good 3 = satisfactory 4 = sufficient 5 = poor P(ass) = passed a.m. test specification(s) F(ail) = failed a.m. test specification(s) N/A = not applicable N/T = not tested				
Dieser Prüfbericht bezieht sich nur auf das o.g. Prüfmuster und darf ohne Genehmigung der Prüfstelle nicht auszugsweise vervielfältigt werden. Dieser Bericht berechtigt nicht zur Verwendung eines Prüfzeichens. <i>This test report only relates to the a. m. test sample. Without permission of the test center this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any test mark.</i>				

V04

Prüfbericht-Nr.: 89212164.06br
Test Report No.:

Seite 2 von 14
Page 2 of 14

Liste der verwendeten Prüfmittel
List of used test equipment

[illegible]

Prüfbericht-Nr.: 89212164.06br
Test Report No.:

Seite 3 von 14
Page 3 of 14

Produktbeschreibung
Product description

Product identity	Allura 0.7*	Total thickness (mm)	2.50*
Pattern/Colour number	Unknown	Total mass per unit area in (g/m ²)	3600*
Classification standard	EN ISO 10582*		
Product type	Heterogeneous PVC floor covering*		
Type of additional backings	-		

* applicants declaration

Figure 1, Picture of the received sample (surface)





Figure 2, Picture of the received sample (back)



Prüfbericht-Nr.: 89212164.06br
Test Report No.:

Seite 4 von 14
Page 4 of 14

Absatz	EN 13501-1:2007+ A1:2009	Messergebnisse - Bemerkungen	Bewertung
Clause	Anforderungen - Prüfungen / Requirements - Tests	Measuring results - Remarks	Evaluation

1	Construction data (indicative) of the product obtained by the testlaboratory after pre-conditioning <i>01-4.3-P.02-322-WI01</i>	
	Test condition	23 ± 2°C and 50 ± 4% relative humidity
	Pre conditioning, duration	≥ 48 h & until constant mass is achieved
	Total thickness (mm)	2.6
	Total mass (g/m ²)	3693
	Density (kg/m ³)	1437
	<i>Note: the determined construction data are used for determination of constant mass, the used testmethod is not in accordance with the determination of construction data according the specification standard. Therefore the testresults should be handled as indicative.</i>	

2	Ignitability of products subjected to direct impingement of flame <i>EN ISO 11925-2:2010/C1:2011</i>						
	Date of testing	28.09.2017					
	Pre-conditioning, climate	23 ± 2°C and 50 ± 4% relative humidity					
	Pre-conditioning, duration	≥ 48 h & until constant mass is achieved					
	Description of substrate	Fibre cement board, thickness 8 ± 2 mm, density 1800 ± 200 kg/m ³ conforming to EN 13238:2010					
	Flame application	Surface					
	Flame application time (s)	15					
	Requirements according EN 13501-1:2007+A1:2009	See clause 5					
	Test result(s)						
	Orientation	Length			Width		
	Test sample	1	2	3	1	2	3
	Ignition of the sample	No	No	No	No	No	No
	Flame tip reached 150 mm above the application point	No	No	No	No	No	No
	Duration after application when the flame tip reached the 150 mm above the application point (s)	N/A	N/A	N/A	N/A	N/A	N/A
	Extent of damaged area, length (mm)	31	25	26	29	27	30
	Extent of damaged area, width (mm)	13	12	13	12	13	13
	Material melts	Yes	Yes	Yes	Yes	Yes	Yes
Shrinks away from flame without being ignited	No	No	No	No	No	No	
After glowing	No	No	No	No	No	No	
Flaming droplets/particles which caused ignition of filter paper	No	No	No	No	No	No	

Prüfbericht-Nr.: 89212164.06br
Test Report No.:

Seite 5 von 14
Page 5 of 14

Absatz	EN 13501-1:2007+ A1:2009	Messergebnisse - Bemerkungen	Bewertung
Clause	Anforderungen - Prüfungen / Requirements - Tests	Measuring results - Remarks	Evaluation

3	Determination of the burning behaviour using a radiant heat source <i>EN ISO 9239-1:2010</i>						
	Date of testing		25.09.2017 & 28.09.2017				
	Pre-conditioning, climate		23 ± 2°C and 50 ± 4% relative humidity				
	Pre-conditioning, duration		≥ 48 h & until constant mass is achieved				
	Description of substrate		Fibre cement board, thickness 8 ± 2 mm, density 1800 ± 200 kg/m³ conforming to EN 13238:2010				
	Fixing method		The samples are glued to the substrate with Uzin KE2000 on 21.09.2017 & 25.09.2017				
	Requirements according EN 13501-1:2007+ A1:2009		See clause 5				
	Test result(s)						
	Test sample		1	2	3	4	Mean
	Orientation (Length: ↑ , Width: T)		↑	T	T	T	T
	Flame spread (cm)		12	13	13	13	13
	CHF / HF-30 (kW/m²)		10.4	10.3	10.3	10.3	10.3
	Maximum light attenuation (%)		47.0	46.8	47.1	51.4	48.4
	Smoke production (%.min)		115	120	114	106	113
	Observations: Specimen 1, 2, 3 and 4: There is flashing and transitory flaming observed but no sustained flaming. Specimen 1, 2, 3 and 4: Extinguished naturally before the end of the test duration.						

4	Classification of burning behaviour EN 13501-1:2007+A1:2009	
	The product, Allura 0.7 , in relation to its reaction to fire behaviour is classified:	B_{fl}
	The additional classification in relation to smoke production is:	s1
	Reaction to fire classification : B_{fl} – s1	
	Field of application <ul style="list-style-type: none"> - As a floor covering in accordance with the nominal product parameters given on page 3. - On end use substrates of classes A1 and A2-s1,d0 according to EN 13238:2010. - Glued down with Uzin KE2000. 	
	Statements <ul style="list-style-type: none"> - This document does not represent type approval or certification of the product. - The test results only relate to the behaviour of the test specimens of the examined product under the -particular conditions of the test in laboratory conditions; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use. - The validity of this report will expire directly after alterations or modifications of the examined product (combination)(s) and/or the criteria. 	

Prüfbericht-Nr.: 89212164.06br
Test Report No.:

Seite 6 von 14
Page 6 of 14

Absatz	EN 13501-1:2007+ A1:2009	Messergebnisse - Bemerkungen	Bewertung
Clause	Anforderungen - Prüfungen / Requirements - Tests	Measuring results - Remarks	Evaluation

5	Potential classes of reaction to fire performance for floorings EN 13501-1:2007+A1:2009			
	Class	Test method(s)	Classification criteria	Additional classifications
	A1 _{fl}	EN ISO 1182 ^a and	$\Delta T \leq 30\text{ }^{\circ}\text{C}$; and $\Delta m \leq 50\text{ }\%$; and $t_f = 0$ (i.e. no sustained flaming)	-
		EN ISO 1716	$PCS \leq 2.0\text{ MJ/kg}$ ^a and $PCS \leq 2.0\text{ MJ/m}^2$ ^b and $PCS \leq 1.4\text{ MJ/m}^2$ ^c and $PCS \leq 2.0\text{ MJ/kg}$ ^d	-
	A2 _{fl}	EN ISO 1182 ^a or	$\Delta T \leq 50\text{ }^{\circ}\text{C}$ and $\Delta m \leq 50\text{ }\%$ and $t_f \leq 20\text{ s}$	-
		EN ISO 1716 and	$PCS \leq 3.0\text{ MJ/kg}$ ^a and $PCS \leq 4.0\text{ MJ/m}^2$ ^b and $PCS \leq 4.0\text{ MJ/m}^2$ ^c and $PCS \leq 3.0\text{ MJ/kg}$ ^d	-
		EN ISO 9239-1 ^e	$CHF \geq 8.0\text{ kW/m}^2$	Smoke production ^g
	B _{fl}	EN ISO 9239-1 ^e and	$CHF \geq 8.0\text{ kW/m}^2$	Smoke production ^g
		EN ISO 11925-2 ^h : Exposure = 15 s	$F_s \leq 150\text{ mm}$ within 20 s	-
	C _{fl}	EN ISO 9239-1 ^e and	$CHF \geq 4.5\text{ kW/m}^2$	Smoke production ^g
		EN ISO 11925-2 ^h : Exposure = 15 s	$F_s \leq 150\text{ mm}$ within 20 s	-
	D _{fl}	EN ISO 9239-1 ^e and	$CHF \geq 3.0\text{ kW/m}^2$	Smoke production ^g
		EN ISO 11925-2 ^h : Exposure = 15 s	$F_s \leq 150\text{ mm}$ within 20 s	-
	E _{fl}	EN ISO 11925-2 ^h : Exposure = 15 s	$F_s \leq 150\text{ mm}$ within 20 s	-
	F _{fl}	No performance determined		
	^a For homogeneous products and substantial components of non-homogeneous products. ^b For any external non-substantial component of non-homogeneous products. ^c For any internal non-substantial component of non-homogeneous products. ^d For the product as a whole. ^e Test duration = 30 min. ^f Critical flux is defined as the radiant flux at which the flame extinguishes or the radiant flux after a test period of 30 min, whichever is the lower (i.e. the flux corresponding with the furthest extent of spread of flame). ^g s1 = Smoke $\leq 750\text{ }\%$ minutes; s2 = not s1. ^h Under conditions of surface flame attack and, if appropriate to the end use application of the product, edge flame attack.			

Prüfbericht-Nr.: 89212164.06br
Test Report No.:

Seite 7 von 14
Page 7 of 14

Absatz	EN 13501-1:2007+ A1:2009	Messergebnisse - Bemerkungen	Bewertung
Clause	Anforderungen - Prüfungen / Requirements - Tests	Measuring results - Remarks	Evaluation

6	Flooring Radiant Panel Single Specimen Report
	<p>Report produced with the Fire Testing Technology FRPSoft software page 1</p> <h3 style="text-align: center;">Flooring Radiant Panel Single Specimen Report</h3> <p>Standard : EN ISO 9239-1:2010 Laboratory : TÜV Rheinland Nederland B.V. Sponsor : Forbo Flooring Novilon 89212164 Date of test : Sep. 25 2017</p> <p>Specimen description : Allura 07 MT17-154951.07 Test name : # 1 Prod File name : D:\FRPFILES\17090046.CSV Test number in series : 4</p> <p>Flux calibration file name : C:\FRPSOFT2.9A\CALIB\FLX17010.CSV</p> <p>Thickness (mm) : 2.6 Density (kg/m³) : 1437</p> <p>Test duration : 12 minutes 05 seconds (725 s) Substrate used? : Yes Substrate : Calcium silicate Fixing method : adhesive Conditioned? : Yes Conditioning temp. (°C) : 23 Conditioning RH (%) : 50</p> <p>Test Results</p> <p>Time to ignition : 2 minutes 03 seconds (123 s) Time to flameout : 12 minutes 04 seconds (724 s) Extent of burning (mm) : 120 Critical flux at extinguishment (kW/m²) : 10.38 HF-10 (kW/m²) : 10.38 HF-20 (kW/m²) : Not calculated (test duration < 20 minutes) HF-30 (kW/m²) : Not calculated (test duration < 30 minutes) Flame spread at 10 minutes (mm) : 120 Flame spread at 20 minutes (mm) : Not measured Flame spread at 30 minutes (mm) : Not measured Peak light attenuation (%) : 46.99 Time to peak light attenuation : 4 minutes 23 seconds (263 s) Total integrated smoke (%.min) : 115.38</p> <p>Potential classification : A2(0)/B(0) Smoke production classification : s1</p> <p><small>These results relate only to the behaviour of the specimens of the product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.</small></p>


Prüfbericht-Nr.: 89212164.06br
Test Report No.:

Seite 8 von 14
Page 8 of 14

Absatz	EN 13501-1:2007+ A1:2009	Messergebnisse - Bemerkungen	Bewertung
Clause	Anforderungen - Prüfungen / Requirements - Tests	Measuring results - Remarks	Evaluation

Report produced with the Fire Testing Technology FRPSoft software

page 2



Test name : # 1 Prod

File name : D:\FRPFILES\17090046.CSV

Rake Results

Position (mm)	Time (s)	Flux (kW/m ²)	Qsb (MJ/m ²)	Position (mm)	Time (s)	Flux (kW/m ²)	Qsb (MJ/m ²)
60	202	11.2	2.259	510	-	3.6	-
110	275	10.5	2.886	560	-	3.0	-
160	-	9.9	-	610	-	2.5	-
210	-	9.2	-	660	-	2.1	-
260	-	8.2	-	710	-	1.8	-
310	-	7.3	-	760	-	1.5	-
360	-	6.3	-	810	-	1.3	-
410	-	5.3	-	860	-	1.2	-
460	-	4.4	-	910	-	1.0	-

Comments

Specimen extinguished naturally.

These results relate only to the behaviour of the specimens of the product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Prüfbericht-Nr.: 89212164.06br
Test Report No.:

Seite 9 von 14
Page 9 of 14

Absatz	EN 13501-1:2007+ A1:2009	Messergebnisse - Bemerkungen	Bewertung
Clause	Anforderungen - Prüfungen / Requirements - Tests	Measuring results - Remarks	Evaluation

Report produced with the Fire Testing Technology FRPSoft software

page 1

Flooring Radiant Panel Single Specimen Report

Standard : EN ISO 9239-1:2010
 Laboratory : TÜV Rheinland Nederland B.V.
 Sponsor : Forbo Flooring Novilon 89212164
 Date of test : Sep. 25 2017

Specimen description : Allura 07 MT17-154951.07
 Test name : # 2 Cross
 File name : D:\FRPFILES\17090047.CSV
 Test number in series : 4

Flux calibration file name : C:\FRPSOFT2.9A\CALIB\FLX17010.CSV

Thickness (mm) : 2.6
 Density (kg/m³) : 1437

Test duration : 12 minutes 10 seconds (730 s)
 Substrate used? : Yes
 Substrate : Calcium silicate
 Fixing method : adhesive
 Conditioned? : Yes
 Conditioning temp. (°C) : 23
 Conditioning RH (%) : 50

Test Results

Time to ignition : 2 minutes 04 seconds (124 s)
 Time to flameout : 12 minutes 09 seconds (729 s)
 Extent of burning (mm) : 130
 Critical flux at extinguishment (kW/m²) : 10.26
 HF-10 (kW/m²) : 10.26
 HF-20 (kW/m²) : Not calculated (test duration < 20 minutes)
 HF-30 (kW/m²) : Not calculated (test duration < 30 minutes)
 Flame spread at 10 minutes (mm) : 130
 Flame spread at 20 minutes (mm) : Not measured
 Flame spread at 30 minutes (mm) : Not measured
 Peak light attenuation (%) : 46.76
 Time to peak light attenuation : 4 minutes 23 seconds (263 s)
 Total integrated smoke (%.min) : 119.86

Potential classification : A2(0)/B(f)
Smoke production classification : s1

These results relate only to the behaviour of the specimens of the product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.


Prüfbericht-Nr.: 89212164.06br
Test Report No.:

Seite 10 von 14
Page 10 of 14

Absatz	EN 13501-1:2007+ A1:2009	Messergebnisse - Bemerkungen	Bewertung
Clause	Anforderungen - Prüfungen / Requirements - Tests	Measuring results - Remarks	Evaluation

Report produced with the Fire Testing Technology FRPSoft software

page 2



Test name : # 2 Cross

File name : D:\FRPFILES\17090047.CSV

Rake Results

Position (mm)	Time (s)	Flux (kW/m ²)	Qsb (MJ/m ²)	Position (mm)	Time (s)	Flux (kW/m ²)	Qsb (MJ/m ²)
60	220	11.2	2.460	510	-	3.6	-
110	281	10.5	2.949	560	-	3.0	-
160	-	9.9	-	610	-	2.5	-
210	-	9.2	-	660	-	2.1	-
260	-	8.2	-	710	-	1.8	-
310	-	7.3	-	760	-	1.5	-
360	-	6.3	-	810	-	1.3	-
410	-	5.3	-	860	-	1.2	-
460	-	4.4	-	910	-	1.0	-

Comments

Specimen extinguished naturally.

These results relate only to the behaviour of the specimens of the product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Prüfbericht-Nr.: 89212164.06br
Test Report No.:

Seite 11 von 14
Page 11 of 14

Absatz	EN 13501-1:2007+ A1:2009	Messergebnisse - Bemerkungen	Bewertung
Clause	Anforderungen - Prüfungen / Requirements - Tests	Measuring results - Remarks	Evaluation

Report produced with the Fire Testing Technology FRPSoft software

page 1

Flooring Radiant Panel Single Specimen Report

Standard : EN ISO 9239-1:2010
Laboratory : TÜV Rheinland Nederland B.V.
Sponsor : Forbo Flooring Novilon 89212164
Date of test : Sep. 28 2017

Specimen description : Allura 07 MT17-154951.07
Test name : # 3 Cross
File name : D:\FRPFILES\17090060.CSV
Test number in series : 4

Flux calibration file name : C:\FRPSOFT2.9A\CALIB\FLX17010.CSV

Thickness (mm) : 2.6
Density (kg/m³) : 1437

Test duration : 12 minutes 39 seconds (759 s)
Substrate used? : Yes
Substrate : Calcium silicate
Fixing method : adhesive
Conditioned? : Yes
Conditioning temp. (°C) : 23
Conditioning RH (%) : 50

Test Results

Time to ignition : 2 minutes 03 seconds (123 s)
Time to flameout : 12 minutes 37 seconds (757 s)
Extent of burning (mm) : 130
Critical flux at extinguishment (kW/m²) : 10.26
HF-10 (kW/m²) : 10.26
HF-20 (kW/m²) : Not calculated (test duration < 20 minutes)
HF-30 (kW/m²) : Not calculated (test duration < 30 minutes)
Flame spread at 10 minutes (mm) : 130
Flame spread at 20 minutes (mm) : Not measured
Flame spread at 30 minutes (mm) : Not measured
Peak light attenuation (%) : 47.06
Time to peak light attenuation : 3 minutes 53 seconds (233 s)
Total integrated smoke (%.min) : 114.33

Potential classification : A2(f1)/B(f1)
Smoke production classification : s1

These results relate only to the behaviour of the specimens of the product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.


Prüfbericht-Nr.: 89212164.06br
Test Report No.:

Seite 12 von 14
Page 12 of 14

Absatz	EN 13501-1:2007+ A1:2009	Messergebnisse - Bemerkungen	Bewertung
Clause	Anforderungen - Prüfungen / Requirements - Tests	Measuring results - Remarks	Evaluation

Report produced with the Fire Testing Technology FRPSoft software

page 2



Test name : # 3 Cross

File name : D:\FRPFILES\17090060.CSV

Rake Results

Position (mm)	Time (s)	Flux (kW/m²)	Qsb (MJ/m²)	Position (mm)	Time (s)	Flux (kW/m²)	Qsb (MJ/m²)
60	184	11.2	2.057	510	-	3.6	-
110	245	10.5	2.571	560	-	3.0	-
160	-	9.9	-	610	-	2.5	-
210	-	9.2	-	660	-	2.1	-
260	-	8.2	-	710	-	1.8	-
310	-	7.3	-	760	-	1.5	-
360	-	6.3	-	810	-	1.3	-
410	-	5.3	-	860	-	1.2	-
460	-	4.4	-	910	-	1.0	-

Comments

Specimen extinguished naturally.

These results relate only to the behaviour of the specimens of the product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Prüfbericht-Nr.: 89212164.06br
Test Report No.:

Seite 13 von 14
Page 13 of 14

Absatz	EN 13501-1:2007+ A1:2009	Messergebnisse - Bemerkungen	Bewertung
Clause	Anforderungen - Prüfungen / Requirements - Tests	Measuring results - Remarks	Evaluation

Report produced with the Fire Testing Technology FRPSoft software

page 1

Flooring Radiant Panel Single Specimen Report

Standard : EN ISO 9239-1:2010
 Laboratory : TÜV Rheinland Nederland B.V.
 Sponsor : Forbo Flooring Novilon 89212164
 Date of test : Sep. 28 2017

Specimen description : Allura 07 MT17-154951.07
 Test name : # 4 Cross
 File name : D:\FRPFILES\17090061.CSV
 Test number in series : 4

Flux calibration file name : C:\FRPSOFT2.9A\CALIB\FLX17010.CSV

Thickness (mm) : 2.6
 Density (kg/m³) : 1437

Test duration : 12 minutes 08 seconds (728 s)
 Substrate used? : Yes
 Substrate : Calcium silicate
 Fixing method : adhesive
 Conditioned? : Yes
 Conditioning temp. (°C) : 23
 Conditioning RH (%) : 50

Test Results

Time to ignition : 2 minutes 03 seconds (123 s)
 Time to flameout : 12 minutes 07 seconds (727 s)
 Extent of burning (mm) : 130
 Critical flux at extinguishment (kW/m²) : 10.26
 HF-10 (kW/m²) : 10.26
 HF-20 (kW/m²) : Not calculated (test duration < 20 minutes)
 HF-30 (kW/m²) : Not calculated (test duration < 30 minutes)
 Flame spread at 10 minutes (mm) : 130
 Flame spread at 20 minutes (mm) : Not measured
 Flame spread at 30 minutes (mm) : Not measured
 Peak light attenuation (%) : 51.36
 Time to peak light attenuation : 3 minutes 44 seconds (224 s)
 Total integrated smoke (%.min) : 105.67

Potential classification : A2(1)B(1)
Smoke production classification : s1

These results relate only to the behaviour of the specimens of the product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Prüfbericht-Nr.: 89212164.06br
Test Report No.:

Seite 14 von 14
Page 14 of 14

Absatz	EN 13501-1:2007+ A1:2009	Messergebnisse - Bemerkungen	Bewertung
Clause	Anforderungen - Prüfungen / Requirements - Tests	Measuring results - Remarks	Evaluation

Report produced with the Fire Testing Technology FRPSoft software

page 2

Smoke Graph

Test name : # 4 Cross
File name : D:\FRPFILES\17090061.CSV

Rake Results

Position (mm)	Time (s)	Flux (kW/m ²)	Qsb (MJ/m ²)	Position (mm)	Time (s)	Flux (kW/m ²)	Qsb (MJ/m ²)
60	192	11.2	2.147	510	-	3.6	-
110	277	10.5	2.907	560	-	3.0	-
160	-	9.9	-	610	-	2.5	-
210	-	9.2	-	660	-	2.1	-
260	-	8.2	-	710	-	1.8	-
310	-	7.3	-	760	-	1.5	-
360	-	6.3	-	810	-	1.3	-
410	-	5.3	-	860	-	1.2	-
460	-	4.4	-	910	-	1.0	-

Comments

Specimen extinguished naturally.

These results relate only to the behaviour of the specimens of the product under the particular conditions of the test, they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.