

FLOTEX® MODULAR TECHNICAL DATA

1. PRODUCT NAME & MANUFACTURER

1.1 Product:

Flotex® high performance modular floor covering

1.2 Manufacturer:

Forbo Flooring Systems Humboldt Industrial Park Hazleton, PA 18202 www.forboflooringNA.com

Phone: 1-800-842-7839 Fax: 570-450-0258

1.3 Product Description:

Construction: Flotex® is a flocked textile floor covering has 100% nylon type wear layer with an intermediate fiberglass layer and a recycled vinyl cushioned backing.

1.4 Physical Characteristics: (dimensions are approximate)

Size------ Approx. 19.69" x 19.69" (50 cm x 50 cm)
----- Approx. 9.8" x 39.37" (25 cm x 100 cm)

Gauge ----- 0.21" (5.3 mm)

Packaging ----- 19.69" x 19.69": 12 tiles (32.3 ft², 3 m²)
----- 9.8" x 39.37": 10 planks (26.91 ft², 2.5m²)

2. PRODUCT PERFORMANCE & TECHNICAL DATA

2.1 Environmental:

Compliant with CHPS 01350 requirements for VOC emissions and indoor air quality.

NSF/ANSI 140 Gold Certified

See Forbo's LEED® v4 sheet for additional information. Materials & Resources

EPD available at

http://productguide.ulenvironment.com/QuickSearch.aspx

ittp://productguide.dienvironment.com/QuickSearch.asp/

 $HPD\ available\ at\ \underline{www.forboflooringNA.com}$

Recycled Content (59% Pre-Consumer)

100% Recyclable Packaging

Indoor Environmental Quality

Low-Emitting Materials (www.chps.net)

Low-Emitting Materials (Adhesives comply with SCAQMD Rule #1168)

2.2 Wear Layer Density:

Over 70,000,000 fibers per square meter.

2.3 Durability/Appearance Retention:

Wear Layer Composition is 6.6 nylon type.

Class 4 (heavy duty) when tested in accordance to EN 1307, Classification of Pile Carpets (Wear Classification).

Achieves over 60,000 cycles when tested in accordance to the Wira Abrasion Test.

Achieves 95% recovery in 24 hours; 100% in one week when tested in accordance to ISO 3416-86, Determination of Thickness Loss after Prolonged Heavy Static Loading.

2.4 Castor Resistance:

Suitable for office chairs with castors when tested in accordance with EN 985, Castor Chair Test.

2.5 Slip Resistance:

Meets or exceeds the industry recommendation of >0.5 for flat surfaces when tested in accordance with ASTM D 2047, Standard Test Method for Static Coefficient of Friction.

Suitable for use on flat or inclined surfaces.

2.6 Colorfastness:

No color change when tested in accordance with AATCC 107, Colorfastness to Water.

No color change when tested in accordance with AATCC 16, Colorfastness to Light (Option 3).

Very slight color change when tested in accordance with AATCC 165, Colorfastness to Crocking Wet & Dry.

2.7 Acoustical Properties:

 $\Delta Lw = 17$ db when tested in accordance with ISO 140-8, Measurement of sound insulation in buildings and of building elements.

0.10 when tested in accordance with ISO 354, Measurement of Sound Absorption in a Reverberation Room.

IIC 59 when tested in accordance with ASTM E 492, Standard Test Method for Laboratory Measurement of Impact Sound Transmission Through Floor/Ceiling Assemblies using the Tapping Machine.

2.8 Bounce Rebound:

99.7% average rebound when tested in accordance to ASTM F 2117, Standard Test Method for Vertical Rebound Characteristics of Sports Surface.

2.9 Hygienic:

Flotex is a supplement to and not a substitute for standard infection control practices and has been shown to reduce microbial contamination based on Independent Laboratory Testing.

2.10 Fire Testing:

Class 1 when tested in accordance with ASTM E 648/NFPA 253, Standard Test Method for Critical Radiant Flux.

Meets 450 or less when tested in accordance with ASTM E 662/ NFPA 258, Standard Test Method for Smoke Density.

Passes when tested in accordance to ASTM D 2859, Standard Test Method for Ignition characteristics of Finished Textile Floor Coverings (Pill Test).

FSR – 195; SDC – 355 when tested in accordance to CAN/ULC S102.2, Standard Test Method for Flame Spread Rating and Smoke Development.

2.11 Electrostatic Propensity:

1.6 Kv when tested in accordance with AATCC 134, Electrostatic Propensity of Carpets.

2.12 Electrical Properties:

0.1 Kv when tested in accordance to ISO 6356, Assessment of Static Electrical Propensity.

>10⁹ ohms when tested in accordance to ISO 10965, Determination of Electrical Resistance.



3. INSTALLATION

3.1 Adhesive:

Use Forbo FRT 950 adhesive. Use a 3/8" nap roller. Spread Rate: Approximately 300 square feet/gallon.

3.2 Installation Guidelines:

Refer to Forbo Flooring's Installation Guide for complete installation guidelines.

4. WARRANTY

Limited 20-year warranty. For complete details, contact Forbo Flooring.

5. CARE & CLEANING

After installation is completed, allow a minimum of five (5) days for the adhesive to properly bond and cure before conducting wet cleaning procedures. See Forbo Flooring's Floor Care Guide for additional information.

Flotex® Modular Technical Data v3.20 09/17