

eurocol

043

the strong connection

26-8-2026



EUOPRIMER ALPHY

Primer to improve the adhesion of gypsum-based levelling compounds and to prevent the elephant skin effect in the levelling layer, when the top of the anhydrite floor is locally or as a whole very absorbent. Suitable for indoor use. Thanks to EMICODE EC 1PLUS (very low emission) suitable for BREEAM projects.

PRODUCT TYPING

Base	Acrylic dispersion.
Color	Green.
Consistency	Thin liquid.

- Very low emission
- EMICODE EC 1PLUS
- High coverage efficiency

PROPERTIES

Classification	Emicode EC 1PLUS tested conform EN 13999-2/4.
Consumption	100 – 200 g/m ² , for absorbant floors.*
Flammability	Non-flammable.
Sensitive to frost	Yes.
Specific weight	Approx. 1.02 kg/l.

APPLICATION

Primer for improving adhesion of plaster-bound levelling compounds to prevent elephant skin effects in the levelling layer, if the surface of an anhydrite floor is locally or globally highly absorbent.

PROCESSING

Storage	Store cool and free from frost.
Tools	Lambswool roller.
Drying	1 - 2 hours.*
Shelf Life	12 months, in unopened packaging.
Cleaner	Water.

** The stated values are laboratory values which, given the large variation in climatological conditions, subfloor compositions and layer thicknesses, are only guideline values.*

043 EUOPRIMER ALPHY

Forbo Eurocol Nederland B.V. | Industrieweg 1-2 | Postbus 130 | 1520 AC Wormerveer | Tel: +31 (0)75 627 16 00 | info.eurocol@forbo.com
Forbo Eurocol Deutschland GmbH | August-Röbling-Straße 2 | DE - 99091 Erfurt | PF 80 02 53 | Telefon: +49 361 730 41 0 | info.eurocol.de@forbo.com

Eurocol is part of the Forbo Group



Substrate:

- The anhydrite floor must be stable to pressure and traction. The subfloor must also be level, clean, permanently dry, and free of grease, dirt and dust, as per the requirements outlined in DIN 18 365.
- Always consult our technical product data sheets if in doubt. If you have any doubts about using a product, contact our Technical Advice department.

Instruction manual:

- Shake the packaging well before use.
- Apply 043 Europrimer Alphy evenly using a napped roller. Please ensure sufficient primer is applied by regularly loading the roller with fresh product.
- 043 Europrimer Alphy may also be sprayed if desired.
- Do not walk on the floor while the product is drying.
- Once the primer has dried, the floor can be finished further.
- Clean tools immediately with water.
- Remove fresh stains immediately with water.
- Avoid contact with eyes and skin and use suitable personal protection equipment (please refer to our safety sheet).
- Clean product trances and dispose of cleaning water according to locally applicable environmental regulation and do not dispose of in the sewer.

Working conditions:

Required surrounding temperature : 18 - 23 °C.

Temperature for material and subfloor : min. 15° – max. 20 °C.

Relative humidity : 40 - 70%.

Contains methylchloroisothiazolinone and methylisothiazolinone (3:1). May produce an allergic reaction.

QUALITY AND GUARANTEE



ENVIRONMENT AND HEALTH

Hazard Class None.

MSDS For detailed information about the safety measures please refer to the safety information sheet on our website www.eurocol.nl.

ITEM DATA

Article	Definition	Packaging	EAN-code
043	Europrimer Alphy	10 kg jerry can	8 710345 043014

043 EUROPRIMER ALPHY