eurocol

**the strong connection**

27-11-2026

# 897

## EUROCLEAN SPORT

Clean & care for sports floors, artified for sports floors according to DIN 18032, resistant to staining and discolouration.
Protects against fine scratches and typical signs of use and wear on the surface of the covering.

### PRODUCT TYPING

| | |
|---|---|
| Base | Water, polymers, water-soluble solvents, non-ionic surfactants, fragrances, preservative. |
| Color | Milky. |
| Consistency | Thin liquid. |

- Highly hard-wearing, dirt-repellent, anti-slip polymer dispersion according to DIN 18032.
- For the initial care of handcrafted parquet sealed with Eurocol water-based varnish.
- Also suitable for sports flooring made of PVC or linoleum flooring.
- After careful basic cleaning, it can be used to refresh the sports flooring to maintain the required sliding friction.
- Extends the life of the floor covering/sealing of parquet.
- Regenerates the existing coating during maintenance care and fills light scratches.
- For interior use.

### PROPERTIES

| | |
|---|---|
| Consumption | Initial care: 1 l for approx. 25 - 30 $m^2$ (undiluted, 1 application) |
| Flammability | Non-flammable. |
| Frost resistance | No. |
| Passableness | First careful use after 1 - 2 hrs. |
| Special quality | Meets DIN 18032. |
| Specific weight | 1.02 kg/ll. |

### APPLICATION

For initial and maintenance care of sports floors.

### PROCESSING

| | |
|---|---|
| Storage | Store cool and dry in unopened packaging. |
| Tools | Wiper. |
| Curing | Fully set after 12 hrs. |
| Shelf Life | Approx 24 Months, in unopened packaging. |
| Cleaner | Water. |
| Remarks | Technical information and safety data sheets of other laying materials and floorings/parquet must be observed!<br>Not for the treatment of rubber floorings, of elastic floorings/parquet with PUR coating and UV sealing.<br>The initial care or maintenance must be carried out before the first full load and, in the case of lacquered |



Forbo Eurocol Nederland B.V. | Industrieweg 1-2 | Postbus 130 | 1520 AC Wormerveer | Tel: +31 (0)75 627 16 00 | info.eurocol@forbo.com
Forbo Eurocol Deutschland GmbH | August-Röbling-Straße 2 | DE - 99091 Erfurt | PF 80 02 53 | Telefon: +49 361 730 41 0 | info.eurocol.de@forbo.com

Eurocol is part of the Forbo Group

surfaces, after the lacquer has dried completely.
For care, follow the corresponding care instructions.
Worn coating can be removed with 891 Euroclean Basic (professional cleaning).

** The stated values are laboratory values which, given the large variation in climatological conditions, subfloor compositions and layer thicknesses, are only guideline values.*

Substrate:

The sealing of parquet floors must be completely closed.

Coarse dirt must first be removed by sweeping or vacuuming.

Instruction manual:

Before use, temper the product according to the processing conditions.

- Shake carefully before use.
- The material can be applied with a lint-free cloth or weasel.
- Apply undiluted 1 - 2 times on the lined and freshly sealed or professionally cleaned floor. In the case of highly absorbent and open-pored floors, more coats may be useful to obtain a closed film.
- Always coat the surface to be treated in one go to avoid build-up.

The intermediate drying time is 1 - 2 hours at normal room climate, after that it can be walked on. If heavy loads are expected "overnight", allow to dry for approx. 12 hours.

- When using as a refresher for worn floors, make sure that old floors are carefully freed from old separating and care product residues (carry out professional basic cleaning). The floor must be left to dry for at least 12 - 24 hours.
  to leave.

Processing conditions:

at least 15 °C floor temperature,
at least 18°C material and room temperature,
35-75% relative humidity, recommended <65%.

## ENVIRONMENT AND HEALTH

| | |
|---|---|
| GISCODE | GE20 |
| LEED | VOC 0 g/l, meets: IEQ Credit 4.1 |
| DGNB | VOC 0 %, quality level: 4 |
| Safety and environment | Safety data sheets of Forbo Eurocol products according to EEG-guideline 91/155. Keep out of reach of children. Do not eat, drink or smoke while processing the product. Only give completely empty containers for recycling. Material residues can be disposed of as household waste. |
| Substances causing allergy | Contains reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one [EC no. 247-500-7] and 2- methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1). May produce an allergic reaction. |

## ITEM DATA

| artikel | productname | packaging | shipping unit |
|---|---|---|---|
| 897 | Euroclean Sport | PE jerrycan à 10 l | 60/pallet |

Any application method/ conditions other than specified in this Technical data sheet require explicit manufacturer's approval. In case of deviance in application method/ conditions liability by manufacturer cannot be guaranteed. This technical data sheet contains advice on handling and application of the product, based on experience and tests run by the manufacturer in laboratory and practical work. The information supplied by the manufacturer are non-binding and cannot be used as a basis for establishing the manufacturers liability for any damages caused. The values stated in this technical data sheet were measured under standard laboratory conditions. As application conditions outside the laboratory vary strongly this technical data sheet must be considered a guide only. Therefore the manufacturer does not take liability for damages caused by the customer's utilization of the technical data sheet content. As use, processing- and storage conditions on site are beyond manufacturers influence, a warranty for the processing result cannot be given. This also includes the infringement of any rights for the protection of third parties. Sufficient testing areas are to be provided before final application. Relevant national norms and regulations of the industry are to be observed. Outside Germany valid, relevant national norms and regulations, have to be taken into account and to be followed by the customer. It is the responsibility of the customer to check product suitability for the intended procedure and purposes prior to use.

This Technical Information supersedes all previously issued application data sheets and product information are no longer valid!

BG175227, Version V09, Stand 2023-02-06, ersetzt Version vom 2018-09-04



Forbo Eurocol Nederland B.V. | Industrieweg 1-2 | Postbus 130 | 1520 AC Wormerveer | Tel: +31 (0)75 627 16 00 | info.eurocol@forbo.com
Forbo Eurocol Deutschland GmbH | August-Röbling-Straße 2 | DE - 99091 Erfurt | PF 80 02 53 | Telefon: +49 361 730 41 0 | info.eurocol.de@forbo.com

Eurocol is part of the Forbo Group