

FORBO ETERNAL DECIBEL TECHNICAL DATA

1. PRODUCT NAME & MANUFACTURER

1.1 Product:

Forbo Eternal Decibel vinyl sheet resilient floor covering.

1.2 Manufacturer:

Forbo Flooring Systems US 8 Maplewood Drive Hazleton, PA 18202 1-800-842-7839

Forbo Flooring Systems Canada 3983 Nashua Drive, Unit 1 Mississauga, ON L4V 1P3 1-800-268-8108 (English) 1-800-567-9268 (French)

www.forboflooringNA.com

1.3 Product Description:

Construction: Forbo Eternal Decibel vinyl sheet floorcoverings have a highly compressed homogeneous vinyl wear layer with a high-performance urethane topcoat. A glass fiber interlayer, to ensure dimensional stability, and a calendared CDF backing with an applied acoustic comfort layer support the wear layer.

1.4 Physical Characteristics:

(dimensions are approximate)

Gauge ----- 0.118" (3.0 mm)
Width ----- 79" (2 meters)
Wear layer ----- 0.0275" (0.7 mm)
Length----- 82' (25 meters)
Roll Size ----- 60 yards² (50 meters²)

2. PRODUCT PERFORMANCE & TECHNICAL DATA

2.1 Reference Specification:

Meets or exceeds all technical requirements as set forth in ASTM F 1303, Standard Specification for Vinyl Sheet Floor Covering with Backing

Type 1, Grade 1, Class C Backing

2.2 Environmental:

Compliant with CDPH 01350 requirements for VOC emissions and indoor air quality.

Forbo Eternal Decibel contributes to LEED v4.1 credits. For additional information, contact Forbo Flooring Systems.

2.3 Static Load Limit:

Residual compression of 0.002" with 250 pounds per square inch when tested in accordance with ASTM F 970-17, Standard Test Method for Static Load Limit.

2.4 Slip Resistance:

Meets or exceeds the industry recommendation of >0.5 for flat surfaces when tested in accordance with ASTM D 2047, Standard Test Method for Static Coefficient of Friction.

2.5 Castor Resistance:

Suitable for office chairs with castors when tested in accordance with ISO 4918, Castor Chair Test.

2.6 Impact Sound Reduction

16dB when tested in accordance with ISO 717-2, Impact Sound Insulation Test.

IIC 56 when tested in accordance with ASTM E 492, Standard Test Method for Laboratory Measurement of Impact Sound Transmission Through Floor/Ceiling Assemblies using the Tapping Machine.

2.7 Fire Testing:

Class 1 when tested in accordance with ASTM E 648/ NFPA 253, Standard Test Method for Critical Radiant Flux.

2.8 Chemical Resistance:

(Exposure Time – 1h)

Acetic Acid (5%)	No Effoct
Acetone	
Ammonia (5%)	
Betadine	No Effect
Bleach	
Brown or Black Hair Dye	No Effect
Brown or Black Shoe Polish	No Effect
Gasoline	
Gel Hand Sanitizer	
Hot Chili Paste	
Hydrochloric Acid (5%)	No Effect
lodine	
Isopropyl Alcohol (70%)	No Effect
Kerosene	
Methylene Blue	
Mineral Oil	No Effect
Olive Oil	
Phenol (5%)	Slight Color Change
Sodium Hydroxide (5%)	No Effect
Sodium Hypochlorite (5%)	No Effect
Sulfuric Acid (5%)	No Effect
Tested in accordance with ASTM F 925, Standard Test	
Method for Resistance to Chemicals of Resilient Flooring.	
Method for nesistance to chemicals of Resilient Flooring.	

3. INSTALLATION

3.1 Adhesive:

Use Forbo V 885, Forbo Sustain 1195, or Forbo 660 adhesive.

3.2 Heat Welding:

Seams must be heat welded. Use only Forbo Eternal Decibel welding rod.

Welding rod dimensions: 4 mm; 165 linear feet per spool.

3.3 Flash Coving (OPTIONAL):

Flash cove up walls to the desired height. Use Forbo V 885, or Forbo Sustain 1195 adhesive.

3.4 Installation Guidelines:

Forbo does NOT recommend the application of adhesive tape on Eternal. Adhesive tape may cause damage to the factory coating of resilient flooring products. When using floor protection materials, tape the seams of the floor protection together and secure the floor protection by weighing down in corners and against walls. DO NOT secure floor protection materials by taping them directly to the surface of resilient floor coverings.

Refer to Forbo's Installation Guidelines for complete installation recommendations.



4. WARRANTY

Limited 10-year warranty. For complete details, contact Forbo Flooring.

5. CARE & CLEANING

Refer to Forbo's Floor Care Guidelines for complete care recommendations.