

eurocol

099

the strong connection

23-6-2026



DISPERSION PRIMER

Ready-to-use, highly impregnating primer for even better adhesion of sealants, tile adhesives and levelling compounds. The ideal bonding base on absorbent gypsum and cement-based walls and floors (indoors and outdoors), sheet material, etc. Thanks to GEV EMICODE EC 1PLUS (very low emission) also suitable for BREEAM projects.

PRODUCT TYPING

| | |
|-------|---------------------|
| Base | Acrylic dispersion. |
| Color | Light pink. |

- Very low emission
- EMICODE EC 1PLUS
- Non-flammable
- User friendly
- Favourable spreading capacity
- Multi-purpose application
- High penetration capacity
- For in- and outdoor use

PROPERTIES

| | |
|--------------------|---|
| Aging | 099 Dispersion Primer does not deteriorate with age. |
| Alkali resistance | 099 Dispersion Primer is resistant against alkaline moisture. |
| Classification | Emicode EC 1PLUS tested conform EN 13999-2/4. Suitable for BREEAM-projects. |
| Consumption | 6 - 9 m ² per kg. |
| Sensitive to frost | No. |
| Specific weight | 1.0 kg/l. |

APPLICATION

Primer for:

- improving the adhesion of sealants, tile adhesives and levelling compounds on absorbent gypsum or cement-based walls and floors, sheet material etc. Not suitable for impervious subfloors. Use 051 Europrimer Quartz.
- improving the top layer of cement screeds that tend to crumble on the surface.

PROCESSING

| | |
|---------|---|
| Storage | Store free from frost. Protect against high temperatures. |
|---------|---|

099 DISPERSIEPRIMER

| | |
|-------------------------|--|
| Tools | Lambswool roller, brush or spray-gun. |
| Drying | 1 - 2 hours, depending on temperature, relative humidity and subfloor. |
| Shelf Life | 12 Months, in unopened packaging. After use close the open packaging well. |
| Application temperature | From 5° to 25 °C (surrounding and subfloor temperature). |

*The stated values are laboratory values which, given the large variation in climatological conditions, subfloor compositions and layer thicknesses, are only guideline values.

Substrate:

- The subfloor should be clean, free from grease and dirt, dry and have a good tensile and compression strength, according to the requirements of DIN 18 353 and DIN 18 365.
- In advance always seek our technical data sheets. In doubt about the application ask for technical advice.

Instruction manual:

- Apply 099 Dispersion Primer thinly and evenly with a brush and/or lambswool roller.
- 099 Dispersion Primer can also be sprayed.
- Drying time 1 - 2 hours.
- Sandpaper old adhesive residues carefully and make dust-free.
- When installing tiles with 725 Alphycol on anhydrite floors keep a drying time of approx. 1 hour.
- Spreading capacity 100 - 150 g/m².

Contains methylchloroisothiazolinone and methylisothiazolinone (3:1). May produce an allergic reaction.

QUALITY AND GUARANTEE



ENVIRONMENT AND HEALTH

Safety and environment MSDS Safety data sheets of Forbo Eurocol products according to EEG-guideline 91/155.
 For extensive information about safety and environment we refer to our website www.eurocol.nl.

ITEM DATA

| Article | Definition | Packaging | EAN-code |
|---------|-------------------|---------------------------|-----------------|
| 099 | Dispersion Primer | 10 kg jerry can | 8 710345 056502 |
| 099 | Dispersion Primer | Box of 12 bottles of 1 kg | 8 710345 099035 |
| 099 | Dispersion Primer | 1 kg bottle | 8 710345 056519 |



Package 1 kg

099 DISPERSIEPRIMER