

Stichting TCKI Florijnweg 6, Velp-Arnhem, The Netherlands +31 26 3845600 PO Box 27, NL-6880 AA Velp KvK 41047499 info@tcki.nl www.tcki.nl



ANTI-SLIP PROPERTIES OF FLOOR COVERINGS

Customer : Forbo Novilon B.V.

J. Jeuring Postbus 148

7740 AC COEVORDEN

Manufacturer : Forbo Novilon B.V.

Postbus 148

7740 AC COEVORDEN

TCKI order number : 19.03.01117

Sample test number : Eternal Wood (MOP embossing)

(Also invoice indication)

Sampling date : 14-03-2019
Date of receipt : 15-03-2019
Sample taken by : The customer

Supplied by : Customer, per mail

Type of material : Carpeting

Colour : Brown

Sort : Thickness 2.00 mm, weight 2900 g/m2

1. Shod Ramp Test

Yours faithfully, Velp, 20-03-2019

mrs. Ineke Geist, Head of laboratory.

* The laboratory management can give you, on request, supplementary information concerning the test procedure and the measurement uncertainty of the results or can be found in the clarification document.

- * Results from this report only have reference to the tested material.
- * Duplication of this document is only allowed with preliminary permission of TCKI or client.



Stichting TCKI Florijnweg 6, Velp-Arnhem, The Netherlands +31 26 3845600 PO Box 27, NL-6880 AA Velp KvK 41047499 info@tcki.nl www.tcki.nl



Q' 1. Determination of the anti-slip properties (CEN/TS16165, annex B and DIN 51130)

Testing of floor coverings - Determination of the anti-slip properties - workrooms and fields of activities with slip danger, walking method - Ramp test in accordance with CEN/TS 16165, annex B and DIN 51130.

TCKI order number : 19.03.01117

Sample test number: Eternal Wood (MOP embossing)

Test date : 19-03-2019

Type of floor covering material:

See cover page

Size individual products (length x width) : 1000 x 500 mm

Description of the surface charateristics of the floor covering:

Flat

Joint width :

Contaminant: SAE motor oil, viscosity category 10W-30 1

Footwear: Leipzig safety shoes

Test results:

Maximum angle of inclination in degrees:		
Test walker 1		Test walker 2
	12.0 12.7 12.2	12.1 12.5 11.9
Mean	12.3	12.2
Average maximum angle of inclination: 12.3 (12 according CEN/TS 16165) Category assessment DIN 51130: R10		

Assessment table for slip resistance characteristics DIN 51130:

Average maximum angle of inclination	Slip resistance category
6° to 10° more than 10° to 19° more than 19° to 27° more than 27° to 35° more than 35°	R9 R10 R11 R12 R13