

# eurocol

# 099

the strong connection

17-4-2026



## DISPERSION PRIMER

Ready-to-use, highly impregnating primer for even better adhesion of sealants, tile adhesives and levelling compounds. The ideal bonding base on absorbent gypsum and cement-based walls and floors (indoors and outdoors), sheet material, etc. Thanks to GEV EMICODE EC 1PLUS (very low emission) also suitable for BREEAM projects.

### PRODUCT TYPING

Base	Acrylic dispersion.
Color	Light pink.

- Very low emission
- EMICODE EC 1PLUS
- Non-flammable
- User friendly
- Favourable spreading capacity
- Multi-purpose application
- High penetration capacity
- For in- and outdoor use

### PROPERTIES

Aging	099 Dispersion Primer does not deteriorate with age.
Alkali resistance	099 Dispersion Primer is resistant against alkaline moisture.
Classification	Emicode EC 1PLUS tested conform EN 13999-2/4. Suitable for BREEAM-projects.
Consumption	6 - 9 m <sup>2</sup> per kg.
Sensitive to frost	No.
Specific weight	1.0 kg/l.

### APPLICATION

Primer for:

- improving the adhesion of sealants, tile adhesives and levelling compounds on absorbent gypsum or cement-based walls and floors, sheet material etc. Not suitable for impervious subfloors. Use 051 Europrimer Quartz.
- improving the top layer of cement screeds that tend to crumble on the surface.

### PROCESSING

Storage	Store free from frost. Protect against high temperatures.
---------	---

**099 DISPERSIEPRIMER**

<b>Tools</b>	Lambswool roller, brush or spray-gun.
<b>Drying</b>	1 - 2 hours, depending on temperature, relative humidity and subfloor.
<b>Shelf Life</b>	12 Months, in unopened packaging. After use close the open packaging well.
<b>Application temperature</b>	From 5° to 25 °C (surrounding and subfloor temperature).

\* The stated values are laboratory values which, given the large variation in climatological conditions, subfloor compositions and layer thicknesses, are only guideline values.

Substrate:

- The subfloor should be clean, free from grease and dirt, dry and have a good tensile and compression strength, according to the requirements of DIN 18 353 and DIN 18 365.
- In advance always seek our technical data sheets. In doubt about the application ask for technical advice.

Instruction manual:

- Apply 099 Dispersion Primer thinly and evenly with a brush and/or lambswool roller.
- 099 Dispersion Primer can also be sprayed.
- Drying time 1 - 2 hours.
- Sandpaper old adhesive residues carefully and make dust-free.
- When installing tiles with 725 Alphycol on anhydrite floors keep a drying time of approx. 1 hour.
- Spreading capacity 100 - 150 g/m<sup>2</sup>.

Contains methylchloroisothiazolinone and methylisothiazolinone (3:1). May produce an allergic reaction.

---

## QUALITY AND GUARANTEE

---




---

## ENVIRONMENT AND HEALTH

---

Safety and environment Safety data sheets of Forbo Eurocol products according to EEG-guideline 91/155.

MSDS For extensive information about safety and environment we refer to our website [www.eurocol.nl](http://www.eurocol.nl).

---

## ITEM DATA

---

Article	Definition	Packaging	EAN-code
099	Dispersion Primer	10 kg jerry can	8 710345 056502
099	Dispersion Primer	Box of 12 bottles of 1 kg	8 710345 099035
099	Dispersion Primer	1 kg bottle	8 710345 056519



Package 1 kg

### 099 DISPERSIEPRIMER