

eurocol

044-1

the strong connection

14-7-2026



EUROPRIMER MULTI PLUS

Universal primer, dilutable concentrate, fast drying, highly water resistant and ideal before levelling works.

PRODUCT TYPING

Base	Styrene acrylate copolymer dispersions, water, wetting, defoaming and preservative agents.
Color	White.
Consistency	Liquid.

- Primer to be diluted with water for priming of absorbent and non-absorbent, mineral-based subfloors, wooden composites, mastic asphalt before levelling or adhesion works.
- Water resistant, especially for application of levelling compound in thick layers. Ensures overall equal absorbency.
- Fast film building and drying.
- Can be applied on underfloor heating systems.
- For indoor use.
- Very low emission certified EMICODE EC1 Plus.
- Low emission, low solvent according to Blue Angel UZ 113.
- Declares by [baubook](#), "ecological building product".

PROPERTIES

Consumption	depending on substrate and dilution approx. 50 - 150 g/m ² .
Flammability	Non-flammable.
Frost resistance	No.

APPLICATION

- as a dust-binding primer on absorbent surfaces,
- as adhesion promoter on dense substrates

before filling or gluing work.

PROCESSING

Storage	Store cool and free from frost (5°- 30 °C).
Tools	Foam roller or lambswool roller.
Mixing ratio	undeluted on impervious subfloors and wooden subfloors. 1 : 2 on stony absorbent subfloors. 1 : 1 on anhydrite floors.
Drying	4 - 6 hour on impervious subfloors. 0,5 hours on stony absorbent subfloors. App. 15 hours on anhydrite- or wooden floors.*
Shelf Life	Approx 15 months, in unopened packaging. After use close the open packaging well.
Cleaner	Water.
Remarks	Please pay attention to the technical data sheet and safety data sheet issued by the floor covering manufacturer Relevant norms and regulations are to be respected. Please pay attention to the technical

044-1 EUROPRIMER MULTI PLUS

and safety data sheets. Cannot be applied on old stone panel screeds and magnesia screeds and under 1 and 2 component parquet adhesives. Not suitable for water-soluble adhesive residues (such as sulfite waste adhesives) or fixings. For subsequent self-levelling and bonding of parquet use Eurocol 048 Europrimer Plus. For self-levelling thicker than 10 mm, released Eurocol reactive primers are to be used.

EMICODE, for more information: www.emicode.com

**The stated values are laboratory values which, given the large variation in climatological conditions, subfloor compositions and layer thicknesses, are only guideline values.*

Substrate:

- The substrate must be pressure- and tension-resistant, permanently dry, free of cracks and dust, even and free of layers that reduce adhesion.
- Adhesion-reducing layers, old material residues must be removed by suitable mechanical measures in accordance with the specifications of DIN 18365/DIN 18356.
- Old fixed floors, such as ceramic tiles, terrazzo, stone floors, must be thoroughly cleaned and sanded matt after drying.
- Cracks or joints (except structural expansion joints) are to be closed with Eurocol Europlan 913 Silicate sealing compound.
- In case of defects, objections are to be reported in writing.

Instruction manual:

- Shake the container before use!
- Before application, let product acclimatize to room temperature.
- Depending on the application area, dilute and mix carefully.
- Apply evenly without creating puddles.
- The drying time depends on the quantity applied, as well as the room temperature and humidity. Let the primer fully dry before continuing further.

Pay attention to the table:

Subfloor	Dilution	Maximum layer thickness of the subsequent levelling	Drying time
To use with cementitious Eurocol levelling compounds			
Absorbent cement-based screeds	1:2	10 mm	0,5 hrs
Calciumsulfate-based screeds (Anhydrite)	1:1	10 mm	15 hrs
Dry screeds	1:1	10 mm	15 hrs
Dense subfloors, ceramic tiles.	undiluted	10 mm	4 - 6 hrs
Mastic asphalt	undiluted	5 mm	4 - 6 hrs
Wooden composite boards	undiluted	10 mm	15 hrs
To use with calcium-sulphate Eurocol levelling compounds			
Absorbent cement-based screeds	1:2	10 mm	15 hrs
Calciumsulfate-based screeds	1:1	10 mm	1 hrs
Dry screeds	1:1	10 mm	1 hrs
Dense subfloors, ceramic tiles	undiluted	10 mm	15 hrs
Mastic asphalt	undiluted	8 mm	15 hrs
Wooden composite boards	undiluted	10 mm	15 hrs

For intermediate priming of cementitious, self-levelling or stable levelling compounds in their multi-layer installation, the first levelling layer must be completely dry. The intermediate primer is applied with a dilution of 1:5 with water!

For direct bonding of textile flooring on standard screed, dilute 1:5 (water) to bind residual dust.

After dilution, use the resulting mixture immediately. The shelf life is limited by dilution.

Working conditions:

Required surrounding temperature: min. 18°C.
Material and subfloor temperature: min. 15°C.
Relative humidity: 35 - 75%, recommended <65%.

QUALITY AND GUARANTEE

044-1 EUROPRIMER MULTI PLUS

Forbo Eurocol Nederland B.V. | Industrieweg 1-2 | Postbus 130 | 1520 AC Wormerveer | Tel: +31 (0)75 627 16 00 | info.eurocol@forbo.com
Forbo Eurocol Deutschland GmbH | August-Röbling-Straße 2 | DE - 99091 Erfurt | PF 80 02 53 | Telefon: +49 361 730 41 0 | info.eurocol.de@forbo.com

Eurocol is part of the Forbo Group



ENVIRONMENT AND HEALTH

GISCODE	D1
LEED	VOC 0 g/l, meets: IEQ Credit 4.1
DGNB	VOC 0 %, quality level: 4
Hazard Class	None.
Safety and environment	Safety data sheets of Forbo Eurocol products according to EEG-guideline 91/155. Keep out of reach of children. Do not eat, drink or smoke while processing the product. Only give completely empty containers for recycling. Material residues can be disposed of as household waste.
MSDS	Available on request.
Substances causing allergy	Contains reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one [EC no. 247-500-7] and 2- methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1), 1,2-benzisothiazol-3(2H)-one. May produce an allergic reaction.

ITEM DATA

Article	productname	packaging	shipping unit
044-1	Europrimer Multi Plus	PE jerry can à 10 kg	60/pallet
044-1	Europrimer Multi Plus	PE jerry can à 2,5 kg	120/pallet

Any application method/ conditions other than specified in this Technical data sheet require explicit manufacturer's approval. In case of deviance in application method/ conditions liability by manufacturer cannot be guaranteed. This technical data sheet contains advice on handling and application of the product, based on experience and tests run by the manufacturer in laboratory and practical work. The information supplied by the manufacturer are non-binding and cannot be used as a basis for establishing the manufacturers liability for any damages caused. The values stated in this technical data sheet were measured under standard laboratory conditions. As application conditions outside the laboratory vary strongly this technical data sheet must be considered a guide only. Therefore the manufacturer does not take liability for damages caused by the customer's utilization of the technical data sheet content. As use, processing- and storage conditions on site are beyond manufacturers influence, a warranty for the processing result cannot be given. This also includes the infringement of any rights for the protection of third parties. Sufficient testing areas are to be provided before final application. Relevant national norms and regulations of the industry are to be observed. Outside Germany valid, relevant national norms and regulations, have to be taken into account and to be followed by the customer. It is the responsibility of the customer to check product suitability for the intended procedure and purposes prior to use.

This Technical Information supersedes all previously issued application data sheets and product information are no longer valid!

BG134504, Version 06, Stand 2021-05-25, ersetzt: Ausgabe vom 2020-01-16

044-1 EUROPRIMER MULTI PLUS