

# eurocol

# 795

the strong connection

23-3-2026



## UNI-QUICK

Fast setting powder tile adhesive for fast bonding of ceramic wall and floor tiles, mosaic and dark-coloured natural stone on dimensionally stable floors. Suitable for use in wet areas, swimming pools and outdoor applications.

### PRODUCT TYPING

Base	Cement-based powder with additives to be mixed with water.
Color	Grey.
Consistency	Powder.

- Passable after 3 hours at 20 °C
- Moisture- and frost-resistant
- Easy to apply
- For wall and floor
- For in- and outdoor use
- Suitable for fixing tiles with a moisture-absorption capacity of 1% or less
- High initial adhesion strength
- High final bond strength
- Does not deteriorate with age
- Low chromate

### PROPERTIES

Aging	795 Uni-Quick does not deteriorate with age.
Classification	Flexible cement-based tile adhesive, which as far as final bond strength, moisture- and frost-resistance complies with C2FE, according to NEN EN 12004.
Consumption	1.2 - 3,5 kg/m <sup>2</sup> , depending on the smoothness of the subfloor and type of tile.

### APPLICATION

- For a fast fixing of tiling, mosaic and dark-coloured natural stone on solid floors.
- Suitable for application in the so-called "wet areas", swimming pools and outdoor use.
- Also suitable for tiles with a moisture-absorption capacity of 1% or less, tested in accordance with EN 99.
- Because of the possibility of discoloration not suitable for fixing glass-mosaic and light-coloured natural stone, such as marble. For these applications we recommend 711 Uniflex or 681 Marmorcol.

### PROCESSING

Storage	Store cool and dry in unopened packaging.
Mixing ratio	Add 25 kg of 795 Uni-Quick to 5-5,5 litres of water. 5 kg of 795 Uni-Quick to 1-1.1 litres of water.
Curing	3-5 Hours, depending of the subfloor and temperature. Lower temperatures will slow down the drying time.

795 UNI-QUICK

<b>Open time</b>	Place the tiles within 10 minutes into the wet adhesive, depending on the subfloor and temperature.
<b>Processing time</b>	Use within 20 minutes after mixing.*
<b>Waiting time</b>	After mixing with water wait for a few minutes, stir once again and apply the mixture on the subfloor.
<b>Shelf Life</b>	9 Months, in unopened packaging. After use close the open packaging well.
<b>Application temperature</b>	From 5° to 25 °C (temperature of the surrounding as well as the subfloor).

\* The stated values are laboratory values which, given the large variation in climatological conditions, subfloor compositions and layer thicknesses, are only guideline values.

#### Substrate:

- The subfloor must have a good tensile and compression strength. The subfloor should also be smooth, dry and free from grease, dirt and dust, according to the requirements of DIN 18 352.
- When using the adhesive outdoors apply 740 Isoflex 2K. Also remove all old ceramic finishing.
- In advance always seek our technical data sheets. In doubt about the application ask for technical advice.

#### Instruction manual:

- Add 25 kg of 795 Uni-Quick to 5-5.5 litres of cool and clean tap water and stir the mortar for 1 minute, by using an electric stirrer (approx. 600 rpm), to a smooth and homogeneous mixture.
- After stirring wait for a few minutes, stir once again and apply the adhesive on the subfloor with the recommended adhesive spreader (see spreading capacity/notched spreader).
- Press the tiles within 10 minutes with a shuffling movement into the adhesive. Check regularly to ensure that the entire back of the tile is in full contact with the adhesive. Remove excess adhesive immediately from the joints.
- Apply the mixed adhesive within 20 minutes. Do not add extra water!
- Under normal circumstances, i.e. a temperature of 20 °C and a relative humidity of 65%, the joints may be filled after 3-5 hours.

#### Spreading capacity/notched spreader for powder tile adhesives:

The smoothness of the subfloor and type of tile are determining for the adhesive spreader to be used. Selection of the notched spreader should be made in such way that a minimum adhesive contact of 80% is guaranteed (equally divided over the back of the tile). For outdoor purposes this contact must be 100%. Also counts for heavy-duty indoor floors, e.g. store and warehouse floors. Check the adhesive contact regularly.

Spreader , 4x4 mm : Spreading capacity approx. 1.2 kg/m<sup>2</sup>  
 Spreader , 6x6 mm : Spreading capacity approx. 2.0 kg/m<sup>2</sup>  
 Spreader , 8x8 mm : Spreading capacity approx. 2.7 kg/m<sup>2</sup>  
 Spreader , 10x10 mm : Spreading capacity approx. 3.5 kg/m<sup>2</sup>

---

## QUALITY AND GUARANTEE

---




---

## ENVIRONMENT AND HEALTH

---

Safety and environment Safety data sheets of Forbo Eurocol products according to EEG-guideline 91/155.  
 MSDS For extensive information about safety and environment we refer to our website [www.eurocol.nl](http://www.eurocol.nl).

---

## ITEM DATA

---

Article	Definition	Packaging	EAN-code	Min. order
795	Uni-Quick	25 kg bag	8 710345 795012	
795	Uni-Quick	5x5 kg box	8 710345 795029	
795	Uni-Quick	5 kg box	8 710345 795036	5 pieces

**795 UNI-QUICK**



Package 25  
kg



Package 5  
kg

**795 UNI-QUICK**

Forbo Eurocol Nederland B.V. | Industrieweg 1-2 | Postbus 130 | 1520 AC Wormerveer | Tel: +31 (0)75 627 16 00 | [info.eurocol@forbo.com](mailto:info.eurocol@forbo.com)  
Forbo Eurocol Deutschland GmbH | August-Röbling-Straße 2 | DE - 99091 Erfurt | PF 80 02 53 | Telefon: +49 361 730 41 0 | [info.eurocol.de@forbo.com](mailto:info.eurocol.de@forbo.com)

Eurocol is part of the Forbo Group

