

eurocol

711

the strong connection



UNIFLEX

Water- and frost-resistant cement-based tile adhesive for natural stone and glass-mosaic.

PRODUCT TYPING

Base	Cement-based white powder with a high synthetic binder content to be mixed with water.
Color	White.

- Dust reduced
- Very low emission
- Emission EC 1PLUS
- For in- and outdoor use
- Permanent flexible
- Moisture- and frost-resistant
- High initial adhesion strength
- High final bond strength
- Does not deteriorate with age
- Easy to apply
- Low chromate
- For wall and floor

PROPERTIES

Aging	711 Uniflex does not deteriorate with age.
Classification	High flexible cement-based tile adhesive, which as far as final bond strength, moisture- and frost-resistance complies with C2TE, according to NEN EN 12004.
Consumption	1.2 - 3.5 kg/m ² , depending on the smoothness of the subfloor and type of tile.

APPLICATION

- For the flexible and water-resistant fixing of ceramic wall and floor tiles, glassmosaic, flat natural stone, flagstones, fully vitrified tiles and other tiles with an minor absorption capacity on almost any subfloor e.g. concrete, cement screed, wood, old tiles, granito, underfloor heating systems etc.
- Very suitable application in the so-called "wet areas", swimming pools and outdoor use.

PROCESSING

Mixing ratio	Add 25 kg 711 Uniflex to approx. 6 litres of water. 5 kg 711 Uniflex to approx. 1.2 litres of water.
Curing	24 Hours, depending on the subfloor and temperature.
Open time	Place the tiles within 15 to 20 minutes into the wet adhesive, depending on the subfloor and temperature.
Processing time	Apply the mixture within 60 minutes.

711 UNIFLEX

Waiting time	After mixing with water wait for a few minutes, stir once again and apply the mixture on the subfloor.
Shelf Life	12 Months, in unopened packaging. After use close the open packaging well.
Application temperature	From 5° to 25 °C (temperature of the surrounding as well as the subfloor).

* The stated values are laboratory values which, given the large variation in climatological conditions, subfloor compositions and layer thicknesses, are only guideline values.

Substrate:

- The subfloor must have a good tensile and compression strength. The subfloor should also be smooth, dry and free from grease, dirt and dust, according to the requirements of DIN 18 352.
- When using the adhesive outdoors apply two layers of 730 Isoflex. Also remove all old ceramic finishing.
- Wooden floors, made of floorboards, should be sufficiently supported underneath (distance between the beam maximum 60 cm). To attain a fixed construction screw water-resistant plywood (minimum 12 mm thickness) on top of this layer. Thereafter apply 099 Dispersion Primer and prime completely with 685 Eurocoat. Maximum tile size 30x30 cm.
- Prime moisture-sensitive or absorbent subfloors e.g. gypsum-based walls wit 099 Dispersion Primer. Apply 685 Eurocoat in the shower area to attain an impervious layer between the tile adhesive and subfloor.
- Prime self-levelling anhydrite floors with a residual construction moisture percentage of 0.5% with 099 Dispersion Primer (drying time minimum 12 hours).
- In advance always seek our technical data sheets. In doubt about the application ask for technical advice.

Instruction manual:

- Add 25 kg of 711 Uniflex to approx. 6 litres of cool and clean tap water and stir the mortar for 1 minute, by using an electric stirrer (approx. 600 rpm), to a smooth and homogeneous mixture.
- After stirring wait for a few minutes, stir once again and apply the adhesive on the subfloor with the recommended adhesive spreader (see spreading capacity/notched spreader).
- In wet areas, first apply an impervious water-resistant layer of adhesive (approx. 3 mm thickness) with a flat trowel. This layer has to dry for at least 5 hours.
- Press the tiles within 15 to 20 minutes with a shuffling movement into the adhesive. Check regularly to ensure that the back of the tile is in full contact with the adhesive. Remove excess adhesive immediately from the joints.
- Apply the mixed adhesive within 60 minutes. Do not add extra water!
- Under normal circumstances, i.e. a temperature of 20 °C and a relative humidity of 65%, the joints may be filled after minimum 24 hours.

Spreading capacity/notched spreader for powder tile adhesives:

The smoothness of the subfloor and type of tile are determining for the adhesive spreader to be used. Selection of the notched spreader should be made in such way that a minimum adhesive contact of 80% is guaranteed (equally divided over the back of the tile). For outdoor purposes this contact must be 100%. Also counts for heavy-duty indoor floors, e.g. store and warehouse floors. Check the adhesive contact regularly.

Spreader no. 19, 4x4 mm : Spreading capacity approx. 1.2 kg/m²
 Spreader no. 12, 6x6 mm : Spreading capacity approx. 2.0 kg/m²
 Spreader no. 13, 8x8 mm : Spreading capacity approx. 2.7 kg/m²
 Spreader no. 14, 10x10 mm : Spreading capacity approx. 3.5 kg/m²

QUALITY AND GUARANTEE



ENVIRONMENT AND HEALTH

Safety and environment Safety data sheets of Forbo Eurocol products according to EEG-guideline 91/155.

MSDS For extensive information about safety and environment we refer to our website www.eurocol.nl.

ITEM DATA

Article	Definition	Packaging	EAN-code	Min. order
711	Uniflex	25 kg bag	8 710345 052405	

711 UNIFLEX

711 Uniflex 5x5 kg box 8 710345 711036
711 Uniflex 5 kg box 8 710345 000048 5 pieces

711 UNIFLEX

Forbo Eurocol Nederland B.V. | Industrieweg 1-2 | Postbus 130 | 1520 AC Wormerveer | Tel: +31 (0)75 627 16 00 | info.eurocol@forbo.com
Forbo Eurocol Deutschland GmbH | August-Röbling-Straße 2 | DE - 99091 Erfurt | PF 80 02 53 | Telefon: +49 361 730 41 0 | info.eurocol.de@forbo.com

Eurocol is part of the Forbo Group

