

eurocol

876

the strong connection



EUROFILLER WOOD PERFECT

Wood filler solution, waterbased, for joints up to 2 mm width.

PRODUCT TYPING

Base	Copolymer dispersion of acrylic acid ester and styrene, pre-filled.
Color	White.
Consistency	Liquid.

- optimal closing of fine joints
- high flank adhesion in the joint, optimised sandability
- high filling capacity even with wider joints
- no sagging in the joints
- optimised wood colour, especially for dark woods
- prefilled, but does not need to be stirred - shaking is sufficient
- canister goods, therefore safe transport
- very low emission installation material, certified according to EMICODE EC 1 Plus
- certified by baubook, "ecological building product"

PROPERTIES

Consumption	Approx. 50 - 150 g/m ² depending on joint width.
Flammability	Non-flammable.
Frost resistance	No.
Specific weight	1.02 kg/l.

APPLICATION

For filling joints in fully bonded parquet.

PROCESSING

Storage	Store cool and dry in unopened packaging.
Tools	Spatula.
Drying	Approx 30 - 60 minutes. *
Shelf Life	Approx 12 months, in unopened packaging. After use close the open packaging well.
Cleaner	Water.
Remarks	Observe the technical information and safety data sheets of other installation materials and the parquet manufacturer!

In the case of unknown types of wood, the suitability of the products to be used should be checked by

876 EUROFILLER WOOD PERFECT

preliminary tests.

Nailed or screwed parquet floors are usually not puttied to avoid breakouts of the putty due to the movable construction.

If the joint edges are very dirty or waxed, adhesion problems can occur.

EMICODE, for more information visit www.emicode.com.

** The stated values are laboratory values which, given the large variation in climatological conditions, subfloor compositions and layer thicknesses, are only guideline values.*

Substrate:

- The surfaces to be sealed must be clean and free of residues of oil, wax, silicone and other adhesion-reducing layers.
- The wood surface is roughly sanded.

Instruction manual:

Before use, temper the product according to the processing conditions.

- Stir well and thoroughly before use.
- Mix the solution with approximately 15 % of sanding dust of the same wood as the parquet floor (grit: 80 – 120) to an easily applicable paste (consistency similar to dough).

If the consistency of the mixture is too thick, the wood putty mix will not sick well in the joint and may separate while sanding. If the consistency of the mixture is too wet, the joints may not be filled 100%. The finer the sanding dust, the better is the filling ability and the adhesion in the joint.

- We recommend mixing the solution with sanding dust in a clean bucket to a homogenous mixture and not on the floor! Too much sanding dust can lead to cracks not being filled sufficiently, please reduce the dust quantity.
- Apply the mixture on the whole parquet floor equally diagonal with a rust free double sided spatula and push the material into the joints forcefully. Repeat the procedure to fill the joints if necessary.
- After a drying time of approximately. 30 – 60 min., grind the floor and continue with fine grinding. Make sure that no residues of the wood-putty mixture remain on the surface.

Now you can start sealing the parquet with all types of Eurocol parquet varnishes, parquet oils or parquet oil-waxes.

Processing conditions:

at least 15 °C floor temperature,
at least 18°C material and room temperature,
35-75% relative humidity, recommended <65%.

QUALITY AND GUARANTEE



ENVIRONMENT AND HEALTH

GISCODE	W2+
LEED	VOC 12,2 g/l, meets: IEQ Credit 4.1
DGNB	VOC 0,27 %, quality level: 3
Hazard Class	None.
Safety and environment	Safety data sheets of Forbo Eurocol products according to EEG-guideline 91/155. Keep out of reach of children. Do not eat, drink or smoke while processing the product. Only give completely empty containers for recycling. Bound material residues can be disposed of as household waste.
MSDS	For detailed information about the safety measures please refer to the safety information sheet on our website www.forbo-eurocol.de .
Substances causing allergy	Contains reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1), 1,2-benzisothiazol-3(2H)-one, 2-methyl-2H-isothiazol-3-one. May produce an allergic reaction.

ITEM DATA

876 EUROFILLER WOOD PERFECT

artikel	productname	packaging	shipping unit
876	Eurofiller Wood Perfect	PE jerrycan à 5 kg	102/pallet

Any application method/ conditions other than specified in this Technical data sheet require explicit manufacturer's approval. In case of deviance in application method/ conditions liability by manufacturer cannot be guaranteed. This technical data sheet contains advice on handling and application of the product, based on experience and tests run by the manufacturer in laboratory and practical work. The information supplied by the manufacturer are non-binding and cannot be used as a basis for establishing the manufacturers liability for any damages caused. The values stated in this technical data sheet were measured under standard laboratory conditions. As application conditions outside the laboratory vary strongly this technical data sheet must be considered a guide only. Therefore the manufacturer does not take liability for damages caused by the customer's utilization of the technical data sheet content. As use, processing- and storage conditions on site are beyond manufacturers influence, a warranty for the processing result cannot be given. This also includes the infringement of any rights for the protection of third parties. Sufficient testing areas are to be provided before final application. Relevant national norms and regulations of the industry are to be observed. Outside Germany valid, relevant national norms and regulations, have to be taken into account and to be followed by the customer. It is the responsibility of the customer to check product suitability for the intended procedure and purposes prior to use.

This Technical Information supersedes all previously issued application data sheets and product information are no longer valid!

BG175876, Version 04, Stand 2022-04-27, ersetzt Ausgabe vom 2021-05-19

876 EUROFILLER WOOD PERFECT

Forbo Eurocol Nederland B.V. | Industrieweg 1-2 | Postbus 130 | 1520 AC Wormerveer | Tel: +31 (0)75 627 16 00 | info.eurocol@forbo.com
Forbo Eurocol Deutschland GmbH | August-Röbling-Straße 2 | DE - 99091 Erfurt | PF 80 02 53 | Telefon: +49 361 730 41 0 | info.eurocol.de@forbo.com

Eurocol is part of the Forbo Group

