

eurocol

870

the strong connection

EUROFILLER WOOD

Wood filler solution, for joint-filling up to 2 mm.



PRODUCT TYPING

Base	Nitrocellulose dissolved.
Color	Transparent.
Consistency	Liquid.

- Aromatic-free wood filler solution, miscible with sanding dust (grain 80 - 100) of all wood types.
- For filling joints in fully glued parquet up to 2 mm.
- Especially for the renovation of old parquet floors and fatty woods.
- Quick-drying.
- Transparent setting.
- Good sanding properties.
- Before using Eurocol surface materials.
- For interior use.
- The product can be used on underfloor heating.
- Observe the protective information in the safety data sheet!

PROPERTIES

Consumption	Approx. 50 - 100 ml/m ² depending on the joint width.
Flammability	Highly flammable liquid
Frost resistance	Yes.
Special quality	Quick drying.
Specific weight	0,8 kg/l

APPLICATION

For filling joints in fully glued parquet.

PROCESSING

Storage	Store cool and dry in unopened packaging.
Tools	Spatula
Drying	Application with spatula appr. 15 -30 minutes.
Shelf Life	Approx 12 months, in unopened packaging. After use close the open packaging well.
Remarks	The technical data sheets and safety data sheets of the other laying materials and parquets used must be observed. In the case of unknown types of wood, the suitability of the products to be used must be checked by

870 EUROFILLER WOOD

preliminary tests. If the joint edges are very dirty or waxed, adhesion problems may occur. During the drying process, uniform ventilation must be ensured. Draughts and direct sunlight must be avoided. Hazardous material: Observe safety instructions and hazardous material regulations! Eurocol recommends the use of aqueous wood filler solution.

** The stated values are laboratory values which, given the large variation in climatological conditions, subfloor compositions and layer thicknesses, are only guideline values.*

Substrate:

- The surfaces to be sealed must be clean and free of residues of oil, wax, silicone and other adhesion-reducing layers.
- The wood surface is roughly sanded.

Instruction manual:

Before use, temper the product according to the processing conditions.

- Stir well and thoroughly before use.
- Mix the solution with approximately 30% of sanding dust of the same wood as the parquet floor (grit: 80 – 120) to an easily applicable paste (consistency similar to dough).

If the consistency of the mixture is too thick, the wood putty mix will not stick well in the joint and may separate while sanding. If the consistency of the mixture is too wet, the joints may not be filled 100%. The finer the sanding dust, the better is the filling ability and the adhesion in the joint.

- We recommend mixing the solution with sanding dust in a clean bucket to a homogenous mixture and not on the floor! Too much sanding dust can lead to cracks not being filled sufficiently, please reduce the dust quantity.
- Apply the mixture on the whole parquet floor equally diagonal with a rust free double sided spatula and push the material into the joints forcefully. Repeat the procedure to fill the joints if necessary.
- After a drying time of approximately. 15 - 30 min., grind the floor find (grit: 100 – 120). Make sure that no residues of the wood-putty mixture remain on the surface.

Now you can start sealing the parquet with all types of Eurocol parquet varnishes, parquet oils or parquet oil-waxes.

Processing conditions:

at least 15 °C floor temperature,
at least 18°C material and room temperature,
35-75% relative humidity, recommended <65%.

ENVIRONMENT AND HEALTH

GISCODE	G2
Safety and environment	Safety data sheets of Forbo Eurocol products according to EEG-guideline 91/155. Keep out of reach of children. Do not eat, drink or smoke while processing the product. Only give completely empty containers for recycling. Bound material residues can be disposed of as household waste.
MSDS	For extensive information about safety and environment we refer to our website www.eurocol.nl .

ITEM DATA

artitel	productname	packaging	shipping unit
870	Eurofiller Wood	tin bucket à 10 l	42/pallet

Any application method/ conditions other than specified in this Technical data sheet require explicit manufacturer's approval. In case of deviance in application method/ conditions liability by manufacturer cannot be guaranteed. This technical data sheet contains advice on handling and application of the product, based on experience and tests run by the manufacturer in laboratory and practical work. The information supplied by the manufacturer are non-binding and cannot be used as a basis for establishing the manufacturers liability for any damages caused. The values stated in this technical data sheet were measured under standard laboratory conditions. As application conditions outside the laboratory vary strongly this technical data sheet must be considered a guide only. Therefore the manufacturer does not take liability for damages caused by the customer's utilization of the technical data sheet content. As use, processing- and storage conditions on site are beyond manufacturers influence, a warranty for the processing result cannot be given. This also includes the infringement of any rights for the protection of third parties. Sufficient testing areas are to be provided before final application. Relevant national norms and regulations of the industry are to be observed. Outside Germany valid, relevant national norms and regulations, have to be taken into account and to be followed by the customer. It is the responsibility of the customer to check product suitability for the intended procedure and purposes prior to use.

This Technical Information supersedes all previously issued application data sheets and product information are no longer valid!

870 EUROFILLER WOOD

870 EUROFILLERWOOD

Forbo Eurocol Nederland B.V. | Industrieweg 1-2 | Postbus 130 | 1520 AC Wormerveer | Tel: +31 (0)75 627 16 00 | info.eurocol@forbo.com
Forbo Eurocol Deutschland GmbH | August-Röbling-Straße 2 | DE - 99091 Erfurt | PF 80 02 53 | Telefon: +49 361 730 41 0 | info.eurocol.de@forbo.com

Eurocol is part of the Forbo Group

