eurocol

the strong connection

8-11-2026

898

EUROCLEAN LONGLIFE

Full area refreshment of old and new floor coverings and parquet. Extremely resistant to footprints, dirt, easy to clean. Protects against fine scratches and typical signs of use and wear on the surface of the covering.



PRODUCT TYPING

Base	Water, polymers, water-soluble solvents, fragrances, preservatives.
Color	Milky.
Consistency	Thin liquid.

- Highly durable maintenance coating.
- For the initial care and refreshing of parquet and cork floorings sealed by hand with water-based Eurocol products, for PVC, CV and linoleum flooring without special PUR coating.
- After careful, professional basic cleaning, it can be used to freshen up used, waterproof floor coverings.
- Resistant to soiling, paint, footprints.
- Extends the life of the floor covering / sealing of parquet.
- Regenerates the existing coating during maintenance care and fills light scratches.
- Low influence on the gloss behaviour of the floor covering to be coated.

PROPERTIES

Consumption	Initial care: 1 l for approx. 30 m^2 (1 application)
Flammability	Non-flammable.
Frost resistance	No.
Passableness	First careful use after 1- 2 hrs.
Special quality	Can be used as refresher and protective sealant.
Specific weight	1.02 kg/ll.

APPLICATION

Care coating for initial care and refreshing of floor coverings and parquet.

PROCESSING

Storage	Store in a cool and frost-free place (between 5^0 - 30 ^{0}C.
Tools	Wiper.
Curing	Walkable after 1 - 2 hours. Fully set after 12 hrs.
By drying	1 - 2 hrs.
Shelf Life	Approx 24 Months, in unopened packaging.

Forbo Eurocol Nederland B.V. | Industrieweg 1-2 | Postbus 130 | 1520 AC Wormerveer | Tel: +31 (0)75 627 16 00 | info.eurocol@forbo.com
Forbo Eurocol Deutschland GmbH | August-Röbling-Straße 2 | DE - 99091 Erfurt | PF 80 02 53 | Telefon: +49 361 730 41 0 | info.eurocol.de@forbo.com

Eurocol is part of the Forbo Group

Cleaner	Water.
Remarks	Technical information and safety data sheets of other laying materials and floorings/parquet must be observed! Technical notes of other surface finishes or care instructions of floor coverings are to be observed! Not for the treatment of resilient coverings/parquet with factory PUR coating and parquet or cork floors with UV sealing. Not for the application on elastomeric coverings. The initial care or maintenance must be carried out before the first full load and, in the case of lacquered surfaces, after the lacquer has completely dried through. The guaranteed properties, such as soiling behaviour and moisture resistance, are achieved after 12 - 24 hours, depending on the number of applications of the care product. Until then, the surface must be protected from moisture. For care, follow the corresponding care instructions. Worn coating can be removed with Eurocol 891 Euroclean Basic (professional cleaning).

** The stated values are laboratory values which, given the large variation in climatological conditions, subfloor compositions and layer thicknesses, are only guideline values.*

Substrate:

- The sealing of parquet and cork floors must be completely closed.
- Coarse dirt must first be removed by sweeping or vacuuming.

Instruction manual:

Before use, temper the product according to the processing conditions.

- Shake carefully before use.
- The material can be applied with a lint-free cloth or weasel.
- Apply undiluted 1 - 2 times on the lined and freshly sealed or professionally cleaned floor. In the case of highly absorbent and open-pored floors, more coats may be useful to obtain a closed film.
- Work from wall to wall in the direction of the door.
- Always coat the surface to be treated in one go to avoid build-up.
- The intermediate drying time is 1 - 2 hours at normal room climate, after that it can be walked on. If heavy loads are expected "overnight", allow to dry for approx. 12 hours.
- When using as a refresher for worn floors, make sure that old floors are carefully freed from old separating and care product residues (carry out professional basic cleaning). The floor must be left to dry for at least 12 - 24 hours. to leave.

Processing conditions:

at least 15 °C floor temperature,
at least 18°C material and room temperature,
35-75% relative humidity, recommended <65%.

ENVIRONMENT AND HEALTH

GISCODE	GE20
LEED	VOC 0 g/l
DGNB	VOC 0 %, quality level: 3
Safety and environment	Safety data sheets of Forbo Eurocol products according to EEG-guideline 91/155. Keep out of reach of children. Do not eat, drink or smoke while processing the product. Only give completely empty containers for recycling. Material residues can be disposed of as household waste.
MSDS	For extensive information about safety and environment we refer to our website www.forbo-eurocol.de.
Substances causing allergy	Contains: mixture from 5-Chlor-2-methyl-2H-isothiazol-3-on [EG nr. 247-500-7] und 2-Methyl-2Hisothiazol- 3-on [EG nr. 220-239-6] (3:1). May produce an allergic reaction.

ITEM DATA

artikel	productname	packaging	shipping unit
898	Euroclean Longlife	PE jerrycan à 2,5 l	8/box 120/pallet

Other types of packaging may be possible.

Any application method/ conditions other than specified in this Technical data sheet require explicit manufacturer's approval. In case of deviance in application method/ conditions liability by manufacturer cannot be guaranteed. This technical data sheet contains advice on handling and application of the product, based on experience and tests run by the manufacturer in laboratory and practical work. The

Forbo Eurocol Nederland B.V. | Industrieweg 1-2 | Postbus 130 | 1520 AC Wormerveer | Tel: +31 (0)75 627 16 00 | info.eurocol@forbo.com
Forbo Eurocol Deutschland GmbH | August-Röbling-Straße 2 | DE - 99091 Erfurt | PF 80 02 53 | Telefon: +49 361 730 41 0 | info.eurocol.de@forbo.com

Eurocol is part of the Forbo Group

information supplied by the manufacturer are non-binding and cannot be used as a basis for establishing the manufacturers liability for any damages caused. The values stated in this technical data sheet were measured under standard laboratory conditions. As application conditions outside the laboratory vary strongly this technical data sheet must be considered a guide only. Therefore the manufacturer does not take liability for damages caused by the customer's utilization of the technical data sheet content. As use, processing- and storage conditions on site are beyond manufacturers influence, a warranty for the processing result cannot be given. This also includes the infringement of any rights for the protection of third parties. Sufficient testing areas are to be provided before final application. Relevant national norms and regulations of the industry are to be observed. Outside Germany valid, relevant national norms and regulations, have to be taken into account and to be followed by the customer. It is the responsibility of the customer to check product suitability for the intended procedure and purposes prior to use.

This Technical Information supersedes all previously issued application data sheets and product information are no longer valid!

BG175224, Version V11, Stand 2023-02-03, ersetzt Version vom 2021-06-16

Forbo Eurocol Nederland B.V. | Industrieweg 1-2 | Postbus 130 | 1520 AC Wormerveer | Tel: +31 (0)75 627 16 00 | info.eurocol@forbo.com
Forbo Eurocol Deutschland GmbH | August-Röbling-Straße 2 | DE - 99091 Erfurt | PF 80 02 53 | Telefon: +49 361 730 41 0 | info.eurocol.de@forbo.com

Eurocol is part of the Forbo Group