

# eurocol

# 883

the strong connection



## EUOPRIME PERFECT

Aqua primer, Reduces side gluing. High neutrality of the wood tint. Long wet - in wet workability (rollability). No visible transitions during rolling and troweling.

### PRODUCT TYPING

Base	Polyacrylat dispersion.
Color	White.
Consistency	Thin liquid.

- Ready to use, rollable and spatulaable, filling, one-component, dispersion-based primer.
- Use prior to Eurocol lacquers to ensure perfect surface appearance.
- For all standard, fully bonded parquet types and parquet woods, also on upright lamella, planks, swing floors and for cork floors. Not for application on exotic, smoked oak.
- High neutrality of the wood tint.
- Long wet - in wet workability (rollability).
- No visible transitions during rolling and troweling.
- High elasticity.
- Reduces side gluing.
- For interior use.
- The product can be used on underfloor heating.
- Very low emission laying material corresponding to EMICODE EC1 Plus.
- Declared by baubook, "ecological building product".

### PROPERTIES

Consumption	Spatula ca. 30 ml/m <sup>2</sup> per coat, Roller ca. 90 ml/m <sup>2</sup> per coat
Flammability	Non-flammable.
Frost resistance	No.
Special quality	Low side gluing. High neutrality of the wood tint. Long wet - in wet workability (rollability). No visible transitions during rolling and troweling.
Specific weight	1.01 kg/l

### APPLICATION

### PROCESSING

Storage	Store cool and dry in unopened packaging.
Tools	Spatula, microfibre roller

883 EUOPRIME PERFECT

Waiting time	Application with spatula appr. 20 - 30 minutes, applikation with roller appr. 1-2 hours. *
Shelf Life	Approx 12 months, in unopened packaging. After use close the open packaging well.
Cleaner	Water.
Remarks	EMICODE, for more information visit <a href="http://www.emicode.com">www.emicode.com</a> .

\* The stated values are laboratory values which, given the large variation in climatological conditions, subfloor compositions and layer thicknesses, are only guideline values.

Substrate:

Instruction manual:

Before use, temper the product according to the processing conditions.

- Shake well before use!
- Preferably decant the varnish into a sealing bucket and use a scraper grid when applying.
- The application has to be done with a clean Eurocol Aqua microfibre roller 25 cm. Alternatively, apply 2 even coats using a double-surface trowel. An evenly closed surface must be created in order to avoid differences in colouring caused by the top coat.
- During application on the prepared parquet floor, use shoe covers for the shoes to avoid footprints.
- After complete drying, seal with approved Eurocol water-based varnishes.

During the drying process, ensure even ventilation. Avoid draughts and direct sunlight.

#### **Working conditions:**

Required surrounding temperature: min. 18°C.

Material and subfloor temperature: min. 15°C.

Relative humidity: 35 - 75%, recommended <65%.

## **QUALITY AND GUARANTEE**



## **ENVIRONMENT AND HEALTH**

GISCODE	W2+
LEED	VOC 56,4 g/l, meets: IEQ Credit 4.1
DGNB	VOC 3,92 %, quality level: 4
Safety and environment	Safety data sheets of Forbo Eurocol products according to EEG-guideline 91/155. Keep out of reach of children. Do not eat, drink or smoke while processing the product. Only give completely empty containers for recycling. Bound material residues can be disposed of as household waste.
MSDS	For detailed information about the safety measures please refer to the safety information sheet on our website <a href="http://www.forbo-eurocol.de">www.forbo-eurocol.de</a> .
Substances causing allergy	Contains 1,2-benzisothiazol-3(2H)-one, reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1). May produce an allergic reaction.

## **ITEM DATA**

artikel	productname	packaging	shipping unit
883	Europrime Perfect	PE jerrycan à 5 l	102/pallet

Any application method/ conditions other than specified in this Technical data sheet require explicit manufacturer's approval. In case of deviance in application method/ conditions liability by manufacturer cannot be guaranteed. This technical data sheet contains advice on handling and application of the product, based on experience and tests run by the manufacturer in laboratory and practical work. The information supplied by the manufacturer are non-binding and cannot be used as a basis for establishing the manufacturers liability for any damages caused. The values stated in this technical data sheet were measured under standard laboratory conditions. As application conditions outside the laboratory vary strongly this technical data sheet must be considered a guide only. Therefore the manufacturer does not take liability for damages caused by the customer's utilization of the technical data sheet content. As use, processing- and storage

**883 EUROPRIME PERFECT**

conditions on site are beyond manufacturers influence, a warranty for the processing result cannot be given. This also includes the infringement of any rights for the protection of third parties. Sufficient testing areas are to be provided before final application. Relevant national norms and regulations of the industry are to be observed. Outside Germany valid, relevant national norms and regulations, have to be taken into account and to be followed by the customer. It is the responsibility of the customer to check product suitability for the intended procedure and purposes prior to use.

This Technical Information supersedes all previously issued application data sheets and product information are no longer valid!

BG175102, Version 03, Stand 2021-05-26, ersetzt Ausgabe vom 2021-05-05

#### **883 EUROPRIME PERFECT**

Forbo Eurocol Nederland B.V. | Industrieweg 1-2 | Postbus 130 | 1520 AC Wormerveer | Tel: +31 (0)75 627 16 00 | [info.eurocol@forbo.com](mailto:info.eurocol@forbo.com)  
Forbo Eurocol Deutschland GmbH | August-Röbling-Straße 2 | DE - 99091 Erfurt | PF 80 02 53 | Telefon: +49 361 730 41 0 | [info.eurocol.de@forbo.com](mailto:info.eurocol.de@forbo.com)

Eurocol is part of the Forbo Group

