



**Forbo Flooring Coral nv**  
**Postbus 17**  
**1560 AA KROMMENIE**  
**Netherlands**

**Your notice of**  
17-11-2020

**Your reference**

**Date**  
18-01-2021

## Analysis Report 20.07046.03


Required tests :

**EN 13501-1 (2019)**

Sample id	Information given by the client	Date of receipt
T2024822	Coral Grip MD EV	17-11-2020

**Kristina De Temmerman**  
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.  
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.  
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



**Reference: T2024822 - Coral Grip MD EV**

**Information given by the client**

Product standard	EN 13501-1 (2019)
Production batch/piece number	1275150400
Date of carpet finishing	11-09-2020
FR treated	yes
FR-surface treatment	no
Use-surface	PVC non-woven
Backing layer	Vinyl
Total mass	6500 g/m <sup>2</sup>
Total thickness	12 mm
Surface structure	Loop pile

**Notified body No: 0493**

**Reference:** T2024822 - Coral Grip MD EV

**Reaction to fire tests – Ignitability of building products subjected to direct impingement of flame - Single-flame source test**

Date of ending the test 15-01-2021  
Standard used EN ISO 11925-2 (2010)  
Product standard EN 13501-1 (2019)

**Floor covering**

Deviation from the standard -

Conditioning 23°C, relative humidity 50%  
Minimum 14 days or until constant mass is achieved

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Substrate Fibre cement board - density (1800 ± 200) kg/m<sup>3</sup>  
Mounting Loose-laid

Specimens have not been cleaned

Flame application time (s) 15  
Flame application Surface

	Length			Width		
	1	2	3	4	5	6
Time to reach 150 mm mark (s)	*	*	*	*	*	*

\* = time to reach the mark > 20 s or mark not reached


**Criteria Floorcoverings**

time to reach the mark: - > 20 s : Class Efl  
- ≤ 20 s : Class Ffl

**Classification** Class E<sub>n</sub>

**Limitations**

This classification document does not represent type approval or certification of the product.



**Reference:** T2024822 - Coral Grip MD EV

**Reaction to fire tests for floorings - Determination of the burning behaviour using a radiant heat source**

Date of ending the test	14-01-2021
Standard used	EN ISO 9239-1 (2010)
Product standard	EN 13501-1 (2019)
Deviation from the standard	-
Conditioning	23°C, relative humidity 50% Minimum 14 days or until constant mass is achieved

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

**Test specimen**

Substrate	Fibre cement board - density (1800 ± 200) kg/m <sup>3</sup>
Mounting	Stuck down with Eurocol 640 with spatula A2
Specimens have not been cleaned	

### Radiant heat flux

	Flame spread distance (cm)			Flame time	Heat flux * kW/m <sup>2</sup>
	10 min	20 min	30 min		
Width					
#1	11	20	20	20 min 38 s	9.5
Length					
#1	<11	20	20	20 min 45 s	9.5
#2	<11	17	17	17 min 18 s	10.0
#3	<11	15	15	14 min 43 s	10.4
Average					10.0

\* Heat flux at the time of flame extinguishment or after a test duration of 30 minutes.

Fire classification in accordance with EN 13501-1 (2019)		
Class	EN ISO 11925-2 or CWFT	EN ISO 9239-1 (test duration = 30 min)
B <sub>fl</sub>	E <sub>fl</sub>	heat flux ≥ 8,0 kW/m <sup>2</sup>
C <sub>fl</sub>	E <sub>fl</sub>	heat flux ≥ 4,5 kW/m <sup>2</sup>
D <sub>fl</sub>	E <sub>fl</sub>	heat flux ≥ 3,0 kW/m <sup>2</sup>

### Smoke production: Light attenuation

	Maximum (%)	Total (%.min)
Width		
#1	36	333
Length		
#1	37	355
#2	40	352
#3	49	361
Average		356

Additional classification in accordance with EN 13501-1 (2019)	
smoke production ≤ 750%.min	s1
smoke production > 750%.min	s2



**Reaction to fire classification : B<sub>n</sub>/ s1**  
*Glued on a non-combustible substrate\**

*\* End use substrates of classes A1 or A2-s1,d0 (EN 13238:2010 § 5.2.2)*

**Limitations**

This classification document does not represent type approval or certification of the product.